

Plaadiliimid. Kasutusaja määramine

Adhesives for tiles - Determination of open time

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 1346:2007 sisaldab Euroopa standardi EN 1346:2007 ingliskeelset teksti. Käesolev dokument on jõustatud 30.10.2007 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes. Standard on kättesaadav Eesti standardiorganisatsioonist.	This Estonian standard EVS-EN 1346:2007 consists of the English text of the European standard EN 1346:2007. This document is endorsed on 30.10.2007 with the notification being published in the official publication of the Estonian national standardisation organisation. The standard is available from Estonian standardisation organisation.
--	---

Käsitlusala: See Euroopa standard kirjeldab teimimeetodit, mida kasutatakse kahliliimide kasutusaja määramiseks. Seda standardit saab rakendada kõigi tsementeerivate kahliliimide ja -mörtide korral kahlite paigaldamiseks seintele ja põrandatele sise- ja välistingimustes. See Euroopa standard ei sisalda käitusnõudeid ega soovitusi kahlite projekteerimiseks ja paigaldamiseks. MÄRKUS: Kahliliime võib kasutada ka teist tüüpi plaatide korral (loodus- ja aglomeraatkivid jne).	Scope: This European Standard specifies the test method to be used to determine the open time of ceramic tile adhesives. This European Standard is applicable to all ceramic tile adhesives for internal or external tile installations on walls and floors.
---	---

ICS 83.180, 91.100.10

Võtmesõnad: adhesioon, ajamõõtmised, ettevalmistus, liim, plaadid, põrandakatted, seinakatted, teimid, teimiolud

English Version

Adhesives for tiles - Determination of open time

Colles à carrelage - Détermination du temps ouvert

Mörtel und Klebstoffe für Fliesen und Platten - Bestimmung
der offenen Zeit

This European Standard was approved by CEN on 21 January 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Sampling	4
4 Test conditions	4
5 Test materials.....	4
5.1 General.....	4
5.2 Ceramic tiles.....	5
5.3 Concrete slab	5
6 Apparatus	5
6.1 Notched trowel.....	5
6.2 Weight	5
6.3 Pull-head plates	5
6.4 Test machine	5
7 Mixing of adhesive.....	5
8 Procedure	6
9 Evaluation and expression of results.....	6
10 Test report	7

Foreword

This document (EN 1346:2007) has been prepared by Technical Committee CEN/TC 67 “Ceramic tiles”, the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2008, and conflicting national standards shall be withdrawn at the latest by February 2008.

This document supersedes EN 1346:1996.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

This European Standard specifies the test method for the determination of the open time of ceramic tile adhesives.

This European Standard is applicable to all ceramic tile adhesives for internal or external tile installations on walls and floors.

This European Standard does not contain performance requirements or recommendations for the design and installation of ceramic tiles.

NOTE Ceramic tile adhesives can also be used for other types of tiles (natural and agglomerated stones etc.), if they do not adversely affect the stones.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 196-1:2005, *Methods of testing cement — Part 1: Determination of strength*

EN 1067, *Adhesives — Examination and preparation of samples for testing*

EN 1323, *Adhesives for tiles — Concrete slabs for tests*

EN 12004, *Adhesives for tiles — Requirements, evaluation of conformity, classification and designation*

EN 14411, *Ceramic tiles — Definitions, classification, characteristics and marking*

EN ISO 15605, *Adhesives — Sampling (ISO 15605:2000)*

3 Sampling

Take a 2 kg sample of the adhesive in accordance with EN ISO 15605 and EN 1067.

4 Test conditions

Standard conditions shall be $(23 \pm 2) ^\circ\text{C}$ and $(50 \pm 5) \%$ relative humidity and the air speed in the testing area less than 0,2 m/s.

5 Test materials

5.1 General

Condition all test materials (adhesive etc.) for at least 24 h under standard conditions. The adhesive to be tested shall be within its shelf life, where this is specified.