

Plaadiliimid. Märgamisvõime määramine

Adhesives for tiles - Determination of wetting
capability

EESTI STANDARDI EESSÖNA**NATIONAL FOREWORD**

Käesolev Eesti standard EVS-EN 1347:2007 sisaldb Euroopa standardi EN 1347:2007 ingliskeelset teksti.	This Estonian standard EVS-EN 1347:2007 consists of the English text of the European standard EN 1347:2007.
Käesolev dokument on jõustatud 30.10.2007 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.	This document is endorsed on 30.10.2007 with the notification being published in the official publication of the Estonian national standardisation organisation.
Standard on kättesaadav Eesti standardiorganisatsioonist.	The standard is available from Estonian standardisation organisation.

Käsitlusala: See Euroopa standard kirjeldab teimimeetodit, mida kasutatakse kahliliimide märgamisvõime määramiseks. Seda standardit saab rakendada kõigi kahliliimide korral kahlite paigaldamiseks seintele ja põrandatele sise- ja välistingimustes. See Euroopa standard ei sisalda käitusnöudeid ega soovitusi kahlite projekteerimiseks ja paigaldamiseks. MÄRKUS: Kahliliime võib kasutada ka teist tüüpi plaatide korral (loodus- ja aglomeraatkivid jne).	Scope: This European Standard describes the test method to be used to determine the wetting capability of ceramic tile adhesives. This European Standard is applicable to all ceramic tile adhesives for internal or external tile installations on walls and floors. This European Standard does not contain performance requirements or recommendations for the design and installation of ceramic tiles.
---	---

ICS 83.180, 91.100.10

Võtmesõnad: ettevalmistus, kindlaksmääramine, liim, märgavus, plaadid, põrandakatted, seinakatted, teimid, teimiolud

EUROPEAN STANDARD

EN 1347

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 2007

ICS 83.180; 91.100.10

Supersedes EN 1347:1996

English Version

Adhesives for tiles - Determination of wetting capability

Colles à carrelage - Détermination du pouvoir mouillant

Mörtel und Klebstoffe für Fliesen und Platten - Bestimmung
der Benetzungsfähigkeit

This European Standard was approved by CEN on 11 June 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents	Page
Foreword	3
1 Scope	4
2 Normative references	4
3 Sampling	4
4 Test conditions	4
5 Test materials and apparatus	4
5.1 General	4
5.2 Glass plates	4
5.3 Concrete slab	4
5.4 Notched trowel	5
5.5 Weight	5
6 Mixing of adhesive	5
7 Procedure	5
8 Test report	6

Foreword

This document (EN 1347:2007) has been prepared by Technical Committee CEN/TC 67 "Ceramic tiles", the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2008, and conflicting national standards shall be withdrawn at the latest by February 2008.

This document supersedes EN 1347:1996.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

This European Standard specifies the method for the determination of the wetting capability of ceramic tile adhesives.

This European Standard is applicable to all ceramic tile adhesives for internal or external tile installations on walls and floors.

This European Standard does not contain performance requirements or recommendations for the design and installation of ceramic tiles.

NOTE Ceramic tile adhesives can also be used for other types of tiles (natural and agglomerated stones etc.), if they do not adversely affect the stones.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 196-1:2005, *Method of testing cement — Part 1: Determination of strength*

EN 1067, *Adhesives — Examination and preparation of samples for testing*

EN 1323, *Adhesives for tiles — Concrete slabs for test*

EN ISO 15605, *Adhesives — Sampling (ISO 15605:2000)*

3 Sampling

Take a sample of at least 2 kg of the adhesive in accordance with EN ISO 15605 and EN 1067.

4 Test conditions

Standard conditions shall be $(23 \pm 2)^\circ\text{C}$ and $(50 \pm 5)\%$ R.H. and a speed of air in the testing area less than 0,2 m/s.

5 Test materials and apparatus

5.1 General

Condition all test materials (adhesive etc.) for at least 24 h under standard conditions. The adhesive to be tested shall be within its shelf life, where this is specified.

5.2 Glass plates

Clean, dry glass plates of dimensions $(100 \pm 1) \text{ mm} \times (100 \pm 1) \text{ mm} \times (6 \pm 0,5) \text{ mm}$, with ground edges.

5.3 Concrete slab

The concrete slab shall comply with EN 1323.