
**Jewellery — Determination of
silver in silver jewellery alloys —
Volumetric (potentiometric) method
using sodium chloride or potassium
chloride**

*Joannerie — Dosage de l'argent dans les alliages d'argent pour la
bijouterie-joannerie — Méthode volumétrique (potentiométrique)
utilisant le chlorure de sodium ou le chlorure de potassium*



This document is a preview generated by EBS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Principle	1
4 Reagents	1
5 Apparatus	2
6 Sampling	2
7 Procedure	2
7.1 Determination of sodium chloride or potassium chloride standard solution factor	2
7.1.1 Preparation of silver standards.....	2
7.1.2 Titration of standard silver solution.....	2
7.1.3 Calculation of sodium chloride or potassium chloride standard solution factor	3
7.2 Determination	3
7.2.1 Preparation of the sample solution	3
7.2.2 Elimination of palladium	3
7.2.3 Titration of the sample solution	3
8 Calculation and expression of results	3
8.1 Calculation	3
8.2 Repeatability	4
9 Test report	4
Bibliography	5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword — Supplementary information](#).

The committee responsible for this document is ISO/TC 174, *Jewellery*.

This second edition cancels and replaces the first edition (ISO 13756:1997), which has been technically revised with the following changes:

- addition of an analytical balance in [Clause 5](#);
- change of requirement for sampling in [Clause 6](#);
- addition of a warning in [Clause 7](#) that suitable health and safety procedures should be followed;
- International Standard editorially revised.

Introduction

The following definitions apply in understanding how to implement an ISO International Standard and other normative ISO deliverables (TS, PAS, IWA):

- “shall” indicates a requirement;
- “should” indicates a recommendation;
- “may” is used to indicate that something is permitted;
- “can” is used to indicate that something is possible, for example, that an organization or individual is able to do something.

ISO/IEC Directives, Part 2 (sixth edition, 2011), 3.3.1 defines a requirement as an “expression in the content of a document conveying criteria to be fulfilled if compliance with the document is to be claimed and from which no deviation is permitted.”

ISO/IEC Directives, Part 2 (sixth edition, 2011), 3.3.2 defines a recommendation as an “expression in the content of a document conveying that among several possibilities one is recommended as particularly suitable, without mentioning or excluding others, or that a certain course of action is preferred but not necessarily required, or that (in the negative form) a certain possibility or course of action is deprecated but not prohibited.”

Jewellery — Determination of silver in silver jewellery alloys — Volumetric (potentiometric) method using sodium chloride or potassium chloride

1 Scope

This International Standard specifies a volumetric method for the determination of silver in silver jewellery alloys, preferably within the range of fineness stated in ISO 9202. These alloys may contain copper, zinc, cadmium, and palladium. Apart from palladium, which must be precipitated before commencing titration, these elements do not interfere with this method of determination.

NOTE This method is an alternative recommended method to ISO 11427.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11596, *Jewellery — Sampling of precious metal alloys for and in jewellery and associated products*

3 Principle

The sample is dissolved in dilute nitric acid. The silver content of the resulting solution is determined by titration with standard sodium chloride or potassium chloride solution using a potentiometric indication of the equivalence point.

4 Reagents

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

4.1 Nitric acid (HNO_3), 33 % HNO_3 (mass fraction), with sufficiently low content of halides (check with silver nitrate test).

4.2 Sodium chloride solution, $c(\text{NaCl}) = 0,1 \text{ mol/l}$.

Dissolve 5,84 g of sodium chloride (dried at 105 °C) in water and dilute to 1 000 ml.

4.3 Potassium chloride solution, $c(\text{KCl}) = 0,1 \text{ mol/l}$.

Dissolve 7,44 g of potassium chloride (dried at 105 °C) in water and dilute to 1 000 ml.

4.4 Disodium dimethylglyoxime octahydrate solution.

Dissolve 10 g of disodium dimethylglyoxime octahydrate in 1 000 ml of water.

4.5 Silver, minimum purity 999,9 parts per thousand (‰) by mass.