Tsiviilkäibes olevad lõhkeained. Püssirohud ja raketipüssirohud. Osa 3: Deflagratsiooniprotsessi muutumine detonatsiooniks määramine määramine

Explosives for civil uses - Propellants and rocket propellants - Part 3: Determination of deflagration to detonation transition



EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 13938-	This Estonian standard EVS-EN 13938-
3:2003 sisaldah Euroona standardi EN	3:2003 consists of the English text of the
13038-3.2003 indiskeelset teksti	European standard EN 13938-3:2003
Käeselev dokument on jõustatud	This document is endorsed on 15.04.2003
15.04.2002 is calle kehts on avaldatud	with the potification being published in the
15.04.2005 ja selle konta on avaluatuu	official publication of the Estenion pational
ametiikus valjaandes.	standardisation organisation.
Oten dend on Lätterse den Frati	The standard is sucilable from Estadion
Standard on kattesaadav Eesti	The standard is available from Estonian
standardiorganisatsioonist.	standardisation organisation.
	-
Käsitlusala:	Scope:
Käsitlusala: This European Standard specifies a	Scope: This European Standard specifies a
Käsitlusala: This European Standard specifies a method to determine the tendency of a	Scope: This European Standard specifies a method to determine the tendency of a
Käsitlusala: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from	Scope: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from
Käsitlusala: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to	Scope: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to
Käsitlusala: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to propellants of a grain size up to 8 mm.	Scope: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to propellants of a grain size up to 8 mm.
Käsitlusala: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to propellants of a grain size up to 8 mm. This method does not apply to black	Scope: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to propellants of a grain size up to 8 mm. This method does not apply to black
Käsitlusala: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to propellants of a grain size up to 8 mm. This method does not apply to black powder	Scope: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to propellants of a grain size up to 8 mm. This method does not apply to black powder
Käsitlusala: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to propellants of a grain size up to 8 mm. This method does not apply to black powder	Scope: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to propellants of a grain size up to 8 mm. This method does not apply to black powder
Käsitlusala: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to propellants of a grain size up to 8 mm. This method does not apply to black powder	Scope: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to propellants of a grain size up to 8 mm. This method does not apply to black powder
Käsitlusala: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to propellants of a grain size up to 8 mm. This method does not apply to black powder	Scope: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to propellants of a grain size up to 8 mm. This method does not apply to black powder
Käsitlusala: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to propellants of a grain size up to 8 mm. This method does not apply to black powder	Scope: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to propellants of a grain size up to 8 mm. This method does not apply to black powder
Käsitlusala: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to propellants of a grain size up to 8 mm. This method does not apply to black powder	Scope: This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to propellants of a grain size up to 8 mm. This method does not apply to black powder

ICS 71.100.30

Võtmesõnad: checking equipment, deflagration, detonation, explosives, materials testing, mining, propellants, rocket propellant, safety, specimen preparation, stability, testing, transition time

T

EUROPEAN STANDARD NORME EUROPÉENNE **EUROPÄISCHE NORM**

EN 13938-3

March 2003

ICS 71.100.30

English version

Explosives for civil uses - Propellants and rocket propellants -Part 3: Determination of deflagration to detonation transition

Explosifs à usage civil - Poudre propulsive et propergol -Partie 3: Méthode de détermination du passage de la déflagration à la détonation

Explosivstoffe für zivile Zwecke - Treibladungspulver und Raketentreibstoffe - Teil 3: Bestimmung des Überganges der Deflagration in die Detonation

This European Standard was approved by CEN on 28 November 2002.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Forewo	ord	3
1	Scope	4
2	Normative references	4
3	Terms and definitions	4

page

2	Normative references	4
3	Terms and definitions	4
4	Apparatus	4
5	Test sample	6
6	Preparation of test sample	6
7	Procedure	6
8	Test report	7
Annex	A (informative) Range of applicability of the test method	8
Annex	ZA (informative) Clauses of this European Standard addressing essential requirements or other provisions of EU Directives	9

Foreword

This document (EN 13938-3:2003) has been prepared by Technical Committee CEN /TC 321 "Explosives for civil uses", the secretariat of which is held by AENOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2003, and conflicting national standards shall be withdrawn at the latest by September 2003.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For the relationship with EU Directive(s), see informative annex ZA, which is an integral part of this document.

This European Standard is one of a series of standards on *Explosives for civil uses – Propellants and rocket propellants*. The other parts of this series are listed below:

WI 00321046 Part 1: *Requirements*.

WI 00321050 Part 2: Determination of resistance to electrostatic energy.

- prEN 13938-4 Part 4: Determination of burning rate under ambient conditions.
- prEN 13938-5 Part 5: Solid rocket propellants. Guide for the determination of voids and fissures.
- prEN 13938-6 Part 6: Solid rocket propellants. Guide for the determination of integrity of inhibitor coatings.

prEN 13938-7 Part 7: Determination of the properties of black powder.

Annex A is informative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies a method to determine the tendency of a propellant to undergo transition from deflagration to detonation. It applies to propellants of a grain size up to 8 mm. This method does not apply to black powder.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN ISO/IEC 17025, General requirements for the competence of testing and calibration laboratories (ISO/IEC 17025:1999).

prEN 13857-1:2001, Explosives for civil uses – Part 1: Terminology.

ISO 3304, Plain and seamless precision steel tubes – Technical conditions for delivery.

3 Terms and definitions

For the purposes of this European Standard, the terms and definitions given in prEN 13857-1:2001 apply.

4 Apparatus

The apparatus is shown in Figures 1 and 2.

4.1 Seamless steel tube conforming to ISO 3304, external diameter 48,3 mm \pm 0,5 mm, thickness 4,0 mm \pm 0,6 mm and length 1200^{+5}_{0} mm. The tube is threaded at both ends and it is closed by two cast-iron screw caps.

4.2 Lead witness plate(s), thickness 30 mm ± 10 mm.

4.3 Ignition device consisting of an insulated Ni/Cr wire, diameter 0,40 mm \pm 0,05 mm, length 15 mm \pm 1 mm, located at one end of the tube and internally attached to the cap.

4.4 Inert rod, of at least 1300 mm length, with major length indications at every 100 mm and minor length indications at every 5 mm and a diameter slightly smaller than the inner diameter of the steel tube.

4.5 Inert fill plate, consisting of an inert non-metallic material for filling the free space in caps.

4.6 Anvil, consisting of a steel plate, minimum thickness 80 mm, to be put on the ground for supporting lead witness plate(s).