
**Plastics — Polycarbonate (PC) moulding
and extrusion materials —**

**Part 1:
Designation system and basis
for specifications**

Plastiques — Polycarbonate (PC) pour moulage et extrusion —

Partie 1: Système de désignation et base de spécification



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

This document is a preview generated by EVS

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Designation system	2
3.1 General	2
3.2 Data block 1	2
3.3 Data block 2	2
3.4 Data block 3	3
3.4.1 General	3
3.4.2 Viscosity number	3
3.4.3 Melt volume-flow rate	4
3.4.4 Charpy impact strength	4
3.5 Data block 4	5
3.6 Data block 5	5
4 Examples of designations	6
4.1 Designation only	6
4.2 Designation transformed into a specification	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 7391-1 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

This third edition cancels and replaces the second edition (ISO 7391-1:1996), which has been technically revised.

ISO 7391 consists of the following parts, under the general title *Plastics — Polycarbonate (PC) moulding and extrusion materials*:

- *Part 1: Designation system and basis for specifications*
- *Part 2: Preparation of test specimens and determination of properties*

Plastics — Polycarbonate (PC) moulding and extrusion materials —

Part 1: Designation system and basis for specifications

1 Scope

1.1 This part of ISO 7391 establishes a system of designation for polycarbonate thermoplastic material, which may be used as the basis for specifications.

1.2 The types of polycarbonate plastic are differentiated from each other by a classification system based on appropriate levels of the designatory properties

- a) viscosity number;
- b) melt volume-flow rate;
- c) Charpy impact strength;

and on information about the intended application and/or method of processing, important properties, additives, colorants, fillers and reinforcing materials.

1.3 This part of ISO 7391 is applicable to thermoplastic polyesters of carbonic acid and aromatic dihydroxy compounds. The polyester may be a homopolymer, a copolymer or a mixture of the two.

It applies to materials ready for normal use in the form of powder, granules or pellets and to materials unmodified or modified by colorants, additives, fillers, etc.

1.4 It is not intended to imply that materials having the same designation give necessarily the same performance. This part of ISO 7391 does not provide engineering data, performance data or data on processing conditions which may be required to specify a material for a particular application and/or method of processing.

If such additional properties are required, they shall be determined in accordance with the test methods specified in Part 2 of this International Standard, if suitable.

1.5 In order to specify a thermoplastic material for a particular application or to ensure reproducible processing, additional requirements may be given in data block 5 (see 3.1).

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics*

ISO 7391-2, *Plastics — Polycarbonate (PC) moulding and extrusion materials — Part 2: Preparation of test specimens and determination of properties*

3 Designation system

3.1 General

The designation system for thermoplastics is based on the following standard pattern:

Designation						
Description block (optional)	Identity block					
	International Standard number block	Individual-item block				
		Data block 1	Data block 2	Data block 3	Data block 4	Data block 5

The designation consists of an optional description block, reading “Thermoplastics”, and an identity block comprising the International Standard number and an individual-item block. For unambiguous designation, the individual-item block is subdivided into five data blocks comprising the following information:

- Data block 1: Identification of the plastic by its symbol PC in accordance with ISO 1043-1 (see 3.2).
- Data block 2: Position 1: Intended application or method of processing (see 3.3).
Positions 2 to 8: Important properties, additives and supplementary information (see 3.3).
- Data block 3: Designatory properties (see 3.4).
- Data block 4: Fillers or reinforcing materials and their nominal content (see 3.5).
- Data block 5: For the purpose of specifications, a fifth data block may be added containing additional information.

The first character of the individual-item block shall be a hyphen. The data blocks shall be separated from each other by commas.

If a data block is not used, this shall be indicated by doubling the separation sign, i.e. by two commas (,,).

3.2 Data block 1

In this data block, after the hyphen, polycarbonate plastics are identified by the symbol “PC” in accordance with ISO 1043-1.

3.3 Data block 2

In this data block, information about intended application and/or method of processing is given in position 1 and information about important properties, additives and colour in positions 2 to 8. The code-letters used are specified in Table 1.

If information is presented in positions 2 to 8 and no specific information is given in position 1, the letter X shall be inserted in position 1.