
**Pigments and extenders — Methods
of dispersion and assessment of
dispersibility in plastics —**

**Part 2:
Determination of colouristic properties
and ease of dispersion in plasticized
polyvinyl chloride by two-roll milling**

*Pigments et matières de charge — Méthodes de dispersion et
évaluation de l'aptitude à la dispersion dans les plastiques —*

*Partie 2: Détermination des propriétés colorimétriques et de la facilité
de dispersion dans le polychlorure de vinyle plastifié par calandrage
sur bicylindre*



This document is a preview generated by EBS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Material	2
6 Apparatus	2
7 Sampling	2
8 Procedure	3
8.1 Milling at $(160 \pm 5) ^\circ\text{C}$	3
8.1.1 Premixing of the test materials	3
8.1.2 Two-roll milling	3
8.1.3 Pressing	3
8.2 Milling at $(130 \pm 5) ^\circ\text{C}$	4
9 Photometric measurement	4
10 Evaluation	4
10.1 Evaluation of colouristic properties in a white reduction	4
10.2 Evaluation of the ease of dispersion	4
11 Test report	4
12 Precision	5
Annex A (informative) Description of the basic compound	6
Bibliography	8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword — Supplementary information](#).

The committee responsible for this document is ISO/TC 256, *Pigments, dyestuffs and extenders*.

ISO 23900 consists of the following parts, under the general title *Pigments and extenders — Methods of dispersion and assessment of dispersibility in plastics*:

- *Part 1: General introduction*
- *Part 2: Determination of colouristic properties and ease of dispersion in plasticized polyvinyl chloride by two-roll milling*
- *Part 3: Determination of colouristic properties and ease of dispersion of black and colour pigments in polyethylene by two-roll milling*
- *Part 4: Determination of colouristic properties and ease of dispersion of white pigments in polyethylene by two-roll milling*
- *Part 5: Determination by filter pressure value test*
- *Part 6: Determination by film test*

Pigments and extenders — Methods of dispersion and assessment of dispersibility in plastics —

Part 2:

Determination of colouristic properties and ease of dispersion in plasticized polyvinyl chloride by two-roll milling

1 Scope

This part of this ISO 23900 specifies a method of determining the colouristic properties of a test pigment relative to a standard, and the ease of dispersion DH_{PVC-P} of pigments from the differences in colour strength on dispersing colouring materials under various conditions in plasticized polyvinyl chloride (PVC-P) compounds.

The method is appropriate for use with organic and inorganic black and colour pigments and for pigment preparations.

The ease of dispersion determined in this way is valid only for the dispersion equipment, dispersion conditions and dispersion medium being used. The use of test conditions differing from those specified may give different results; this applies both to the absolute magnitude and to the relation between values of the ease of dispersion of various pigments. The subscript DH_{PVC-P} is therefore used to designate the value obtained as specified in this part of ISO 23900.

The principle of this part of ISO 23900 may also be used for routine quality control purposes by reference to the photometric data generated from the sheets milled at 130 °C. For quality control purposes, the ratio of pigment to TiO_2 may be agreed between the interested parties. Ratios of 1:10 for organic pigments and 0,2 to 0,5:1 for inorganic pigments are suggested as convenient and widely used standard ratios.

[Annex A](#) is informative and gives a description of a suitable basic compound.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 787-24:1985, *General methods of test for pigments and extenders — Part 24: Determination of relative tinting strength of coloured pigments and relative scattering power of white pigments — Photometric methods*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

ISO 18314-1¹⁾, *Analytical colorimetry — Part 1: Practical colour measurement*

EN 12877-1, *Colouring materials in plastics — Determination of colour stability to heat during processing of colouring materials in plastics — Part 1: General introduction*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

1) To be published.