INTERNATIONAL **STANDARD**

ISO 1456

Third edition 2003-02-15

Metallic coatings — Electrodeposited coatings of nickel plus chromium and of copper plus nickel plus chromium

ents n.
e plus nic. Revêtements métalliques — Dépôts électrolytiques de nickel plus chrome et



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

very care has to see the very care has to see that the very care has the very care h Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org

Printed in Switzerland

C	ontents	Page
1	Scope	
2	Normative references	
3	Terms and definitions	
4 5	Information to be supplied by the purchaser to the electroplater	
5 6	Designation	
7	Requirements	
8	Sampling	
Αı	nnexes	
Α	Examples of service conditions for which the various service condition numbers are appropriate	. 13
В	Determination of cracks and pores in chromium coatings	. 14
С	Methods of test for the determination of thickness	
D	Ductility test	. 17
Ε	Determination of the sulfur content of electrodeposited nickel	
Bik	bliography	. 19
	4	
	0,	

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 1456 was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*, Subcommittee SC 3, *Electrodeposited coatings and related finishes*.

This third edition cancels and replaces the second edition (ISO 1456:1988), which has been editorially and technically revised.

Annexes B to E form a normative part of this International Standard. Annex A is for information only.

Introduction

Decorative, electrodeposited nickel plus chromium and copper plus nickel plus chromium coatings are applied to atings. If equal to a second s manufactured articles to enhance their appearance and corrosion resistance. Corrosion resistance depends on the type and thickness of the coatings. In general, multilayer nickel coatings provide better corrosion resistance than single-layer nickel coatings of equal thickness, and microdiscontinuous chromium coatings provide better protection than conventional chromium.

© ISO 2003 – All rights reserved

This document is a previous general ded to the

Metallic coatings — Electrodeposited coatings of nickel plus chromium and of copper plus nickel plus chromium

1 Scope

This International Standard specifies the requirements for decorative, electroplated nickel plus chromium, and copper plus nickel plus chromium coatings on iron, steel, zinc alloys, copper and copper alloys, and aluminium and aluminium alloys to provide an attractive appearance and enhanced corrosion resistance. Coating designations are specified that differ in thickness and type, and guidance is given in selecting the coating designation appropriate to the service conditions to which the coated product will be exposed.

This International Standard does not specify the surface condition required by the base metal prior to the coating process, and is not applicable to coatings on sheet, strip or wire in the non-fabricated form nor to threaded fasteners or coil springs.

Requirements for decorative, electroplated copper plus nickel plus chromium coatings on plastic materials are specified in ISO 4525. Similar coatings, except for the absence of a top-coat of chromium, are specified in ISO 1458.

ISO 4526 and ISO 6158 specify requirements for coatings of nickel and chromium, respectively, for engineering purposes.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 1463, Metallic and oxide coatings — Measurement of coating thickness — Microscopical method

ISO 2064, Metallic and other inorganic coatings — Definitions and conventions concerning the measurement of thickness

ISO 2079, Surface treatment and metallic coatings — General classification of terms

ISO 2080, Surface treatment, metallic and other inorganic coatings — Vocabulary

ISO 2177, Metallic coatings — Measurement of coating thickness — Coulometric method by anodic dissolution

ISO 2361, Electrodeposited nickel coatings on magnetic and non-magnetic substrates — Measurement of coating thickness — Magnetic method

ISO 2819, Metallic coatings on metallic substrates — Electrodeposited and chemically deposited coatings — Review of methods available for testing adhesion

ISO 3497, Metallic coatings — Measurement of coating thickness — X-ray spectrometric methods

ISO 3543, Metallic and non-metallic coatings — Measurement of thickness — Beta backscatter method

© ISO 2003 – All rights reserved

ISO 3882, Metallic and other inorganic coatings — Review of methods of measurement of thickness

ISO 4519, Electrodeposited metallic coatings and related finishes — Sampling procedures for inspection by attributes

ISO 4541:1978, Metallic and other non-organic coatings — Corrodkote corrosion test (CORR test)

ISO 9220, Metallic coatings — Measurement of coating thickness — Scanning electron microscope method

ISO 9227:1990, Corrosion tests in artificial atmospheres — Salt spray tests

ISO 9587, Metallic and other inorganic coatings — Pretreatments of iron or steel to reduce the risk of hydrogen embrittlement

ISO 9588, Metallic and other inorganic coatings — Post-coating treatments of iron or steel to reduce the risk of hydrogen embrittlement

ISO 10289:1999, Methods for corrosion testing of metallic and other inorganic coatings on metallic substrates — Rating of test specimens and manufactured articles subjected to corrosion tests

ISO 10587, Metallic and other inorganic coatings — Test for residual embrittlement in both metallic-coated and uncoated externally-threaded articles and rods — Inclined wedge method

ISO 16348, Metallic and other inorganic coatings — Definitions and conventions concerning appearance

ASTM B764-94, Standard Test Method for Simultaneous Thickness and Electrochemical Potential Determination of Individual Layers in Multilayer Nickel Deposit (STEP Test)

3 Terms and definitions

For the purposes of this International Standard, the terms and definitions given in ISO 2064, ISO 2079, ISO 2080 and ISO 16348 apply.

4 Information to be supplied by the purchaser to the electroplater

4.1 Essential information

When ordering articles to be electroplated in accordance with this International Standard, the purchaser shall provide the following information in writing, in e.g., the contract or purchase order, or on engineering drawings:

- a) the designation (see clause 6);
- b) the appearance required, e.g., bright, dull or satin (see 6.3 and 7.1). Alternatively, samples showing the required finish or range of finishes shall be supplied or approved by the purchaser, and used for comparison purposes (see 7.1);
- c) the significant surfaces, to be indicated on drawings of the parts or by providing suitably marked specimens;
- d) the type of corrosion test to be used (see 7.5 and Table 8);
- e) the type of adhesion test to be used (see 7.4);
- f) the extent to which defects shall be tolerated on non-significant surfaces (see 7.1);
- g) positions on the significant surface for rack or contact marks, where such marks are unavoidable (see 7.1);
- h) sampling methods and acceptance levels (see clause 8);
- i) the tensile strength of the steel and any requirement for prior or post treatments of iron or steel to reduce the risk of hydrogen embrittlement, as well as hydrogen embrittlement test methods (see 7.8 and 7.9).