Profileeritud laed. Nõuded ja katsemeetodid

Stretched ceilings - Requirements and test methods



EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 14716:2005 sisaldab Euroopa standardi EN 14716:2004 ingliskeelset teksti.

Käesolev dokument on jõustatud 25.01.2005 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 14716:2005 consists of the English text of the European standard EN 14716:2004.

This document is endorsed on 25.01.2005 with the notification being published in the official publication of the Estonian national standardisation organisation.

The standard is available from Estonian standardisation organisation.

Käsitlusala:

This document specifies the characteristics, specifications and test methods for stretched ceilings made up of single or multi-layer sheets, coated fabrics or fabrics made up of coated or monofilament yarn with a fastening system. It also specifies the method of conformity assessment for stretched ceilings.

Scope:

This document specifies the characteristics, specifications and test methods for stretched ceilings made up of single or multi-layer sheets, coated fabrics or fabrics made up of coated or monofilament yarn with a fastening system. It also specifies the method of conformity assessment for stretched ceilings.

ICS 91.060.30

Võtmesõnad:

EUROPEAN STANDARD

EN 14716

NORME EUROPÉENNE EUROPÄISCHE NORM

December 2004

ICS 91.060.30

English version

Stretched ceilings - Requirements and test methods

Plafonds tendus - Exigences et méthodes d'essai

Spanndecken - Anforderungen und Prüfverfahren

This European Standard was approved by CEN on 22 October 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Cont		rage
Forewo	ord	<u></u>
1	Scope	6
2	Normative references	
- 3	Terms and definitions	
4		
4	Requirements relating to sheets and coated fabrics or fabrics made up of coated yarn or monofilaments	7
4.1	Essential requirements	
4.1.1	Reaction to fire	
4.1.2	Release of other dangerous substances	
4.1.3	Water vapour permeability	
4.2	Requirements of single or multi-layered sheets	
4.3	Requirements of coated fabrics and fabrics made up of coated yarn or monofilaments	
4.4	Requirements of attachment systems (edge profiles and anchoring devices)	
4.4.1 4.4.2	Suitability for dismantling and re- assembly Mechanical strength	
4.4.2		
5	Assessment of conformity	
5.1	General	
5.2	Type tests	
5.2.1	Initial type tests	
5.2.2	Sampling, tests and conformity criteria	
6	Marking and data sheet	13
6.1	Marking of the product	
6.2	Data sheet	13
Annex	A (normative) SBI test	14
	B (normative) Determination of the mass per unit area and thickness of the sheets	
B.1	Determination of the mass per unit area	
B.1.1	Apparatus	
B.1.2	Test pieces	
B.1.3	Conditioning	
B.1.4	Procedure	
B.1.5	Calculation and expression of results	18
B.2	Determination of the thickness	
B.2.1	Apparatus	
B.2.2	Conditioning	
B.2.3	Procedure	
B.2.4	Calculation and expression of results	
B.3	Test report	
Annex	C (normative) Determination of dimensional stability after exposure to moisture	20
C.1	Scope	20
C.2	Principle	
C.3	Apparatus and reagents	
C.3.1	Enclosure (see Figure C.1)	
C.3.2	Test solution	
C.4 C.4.1	Preparation of the test pieces	
C.4.1 C.4.2	Stretched ceiling	
_	Polated materials	Z

C.5	Procedure	
C.6	Expression of results	
C.7	Test report	21
Annex	D Determination of the operating stress	24
D.1	Determination of the tensile strain at break	
D.1.1	Preparation of the test pieces	
D.1.2	Procedure	
D.2	Calculation of the rate of elongation resulting in the length and the width of a sample of	
	single or multi-layered sheet (see Figure D.6)	
D.2.1	Definition	
D.2.2	Schematic presentation of the calculation	
D.2.3	Calculation of the reduction of I_o (Rv_I %) during the elongation of L_o	
D.2.4	Calculation of the reduction of L_o (Rv_L %) during the elongation of I_o	30
D.2.5	Calculation of the percentage elongation resulting in the length and the width of the sheet	31
D.3	Numerical application	31
D.3.1	Hypothesis	31
D.3.2	Calculation of I ₀ and L ₀	32
D.3.3	Calculation of A_1 % and A_2 %	
D.3.4	Calculation of the percentage reduction Rv_I % of I_0 according to Poisson's ratio	
D.3.5	Calculation of the width /' reduced by Poisson's ratio	
D.3.6	Calculation of the resulting percentage elongation in width: A_{IR} %	
D.3.7	Calculation of the percentage reduction $Rv_1\%$ of L_0 according to Poisson's ratio	
D.3.8	Calculation of the reduced width /' by Poisson's ratio	
D.3.9	Calculation of the resulting percentage elongation in the length and the width of the	
D.4	sample Determination of the operating stress	34 3 <i>4</i>
		0
Annex	E (normative) Determination of dimensional changes after exposure to heat (kaolin bed	
	method)	
E.1	Principle	
E.2	Apparatus	
E.3	Test pieces	
E.3.1	Shape and dimensions	
E.3.2	Taking of test pieces	
E.4	Procedure	
E.4.1 E.4.2	Test temperature	
E.4.2 E.5	Test	
E.6	Expression of results Test report	
_		30
Annex	F (normative) Method of assessing the weldability of sheets assembled by the high	
- 4	frequency welding process	
F.1	Scope	
F.2	Definitions	
F.2.1	General	
F.3	Principles used for assessing HF weldability	
F.3.1	Methodology	
F.3.2	HF welding criteria	
F.4	Welding strips	
F.4.1	Shape and dimensions of the strips	
F.4.2 F.5	Taking of test pieces	
F.5.3	Procedure Weld quality	
F.5.3 F.6		
F.6.1	Expression of results	
_	·	
	G Factory production control	
G.1	General	50

EN 14716:2004 (E)

G.2	Control of the raw materials	
G.3	Control of the procedure	
G.4 G.5	Calibration plan Testing of the finished products	
G.5.1	Direct testing	
G.5.2	Indirect evaluation	
G.6	Inspection and testing	
G.7	Traceability	51
Annex	ZA (informative) Clauses of this European Standard addressing provisions of the EU	
	Construction Products Directive	
ZA.1	Scope and relevant characteristics	
ZA.2 7Δ 2 1	Procedure for attestation of conformity of stretched ceilings Systems of attestation of conformity	
	EC certificate and declaration of conformity	
ZA.3	CE marking and labelling	
Biblio	graphy	59
DIDIIO;	graphy	
		/_
		(),

Foreword

This document (EN 14716:2004) has been prepared by Technical Committee CEN/TC BT/TF 119 "Stretched ceilings", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2005, and conflicting national standards shall be withdrawn at the latest by June 2005.

This European Standard has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EC Directive(s).

For relationship with EC Directive(s), see informative Annex ZA, which is an integral part of this standard.

It does not supersede any existing standard.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, y, pland, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This document specifies the characteristics, specifications and test methods for stretched ceilings made up of single or multi-layer sheets, coated fabrics or fabrics made up of coated or monofilament yarn with a fastening system.

It also specifies the method of conformity assessment for stretched ceilings.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1875-3, Rubber- or plastics-coated fabrics - Determination of tear strength. Part 3: Trapezoidal method.

EN 12149, Wall coverings in roll form - Determination of migration of heavy metals and certain other elements, of vinyl chloride monomer and of formaldehyde release.

EN 12280-1, Rubber- or plastics-coated fabrics - Accelerated ageing tests - Part 1: Heat ageing.

EN 13238, Reaction to fire tests for building products - Conditioning procedures and general rules for selection of substrates.

EN 13501-1, Fire classification of construction products and building elements - Part 1: Classification using test data from reaction to fire tests.

EN 13823, Reaction to fire tests for building products - Building products excluding floorings exposed to the hermal attack by a single burning item.

EN ISO 105-B02, Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test (ISO 105-B02:1994, including Amendment 1:1998).

EN ISO 527-1, Plastics - Determination of tensile properties - Part 1: General principles (ISO 527-1:1993 including Corr 1:1994).

EN ISO 527-3, Determination of tensile properties - Part 3: Test conditions for films and sheets (ISO 527-3:1995).

EN ISO 846, Plastics - Evaluation of the action of microorganisms (ISO 846:1997).

EN ISO 1182, Reaction to fire tests for building products - Non-combustibility test (ISO 1182:2002).

EN ISO 1421, Rubber- or plastics-coated fabrics - Determination of tensile strength and elongation at break (ISO 1421:1998).

EN ISO 1716, Reaction to fire tests for building products - Determination of the heat of combustion (ISO 1716:2002).

EN ISO 2286-2, Rubber- or plastics-coated fabrics - Determination of roll characteristics - Part 2: Methods for determination of total mass per unit area, mass per unit area of coating and mass per unit area of substrate (ISO 2286-2:1998).

EN ISO 9001, Quality management systems - Requirements (ISO 9001:2000).

EN ISO 11925-2, Reaction to fire tests - Ignitability of building products subjected to direct impingement of flame - Part 2: Single-flame source (ISO 11925-2:2002).

ISO 2528:1995, Sheet materials - Determination of water vapour transmission rate - Gravimetric (dish) method.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply:

3.1

stretched ceilings

ceiling coverings comprising a continuous area obtained from one width or assembled widths kept under tension at its edges by a fastening system permitting dismantling and re-assembly

These widths may be single or multi-layered sheets, coated fabrics or fabrics made up of coated yarn or monofilaments. Stretched ceilings may be perforated or not

3.2

product family

total range of products within specific variability limits (defined by the manufacturer or a technical specification) of the product parameters and, if appropriate, of the final use parameters for which the specified safety characteristics do not change (do not deteriorate)

This means that the test results obtained for one product in the family remain valid for all the products in the family

3.3

edge profile

element fixed at the periphery of the ceiling to keep the ceiling stretched

3.4

anchoring device

element connecting the stretched ceiling to the edge profile

4 Requirements relating to sheets and coated fabrics or fabrics made up of coated yarn or monofilaments

4.1 Essential requirements

4.1.1 Reaction to fire

4.1.1.1 Preparation and conditioning of test pieces

The test pieces shall be conditioned prior to the test in accordance with EN 13238.

4.1.1.2 Ignitability test

The ignitability test shall be carried out in accordance with EN ISO 11925-2.

The flame shall be applied to the surface of the test piece fixed on the test piece holder by means of small pins incorporated in the surface of the U-shaped frame