

Paints and varnishes - Powder organic coatings for hot dip galvanised or sherardised steel products for construction purposes

This document is a preview generated by EVS

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 13438:2013 sisaldab Euroopa standardi EN 13438:2013 ingliskeelset teksti.	This Estonian standard EVS-EN 13438:2013 consists of the English text of the European standard EN 13438:2013.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 04.09.2013.	Date of Availability of the European standard is 04.09.2013.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 25.220.60

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

English Version

Paints and varnishes - Powder organic coatings for hot dip galvanised or sherardised steel products for construction purposes

Peintures et vernis - Revêtements de poudre organique pour produits en acier galvanisé à chaud ou shérardisé utilisés dans la construction

Beschichtungsstoffe - Pulverbeschichtungen für feuerverzinkte oder sherardisierte Stahlerzeugnisse für Bauzwecke

This European Standard was approved by CEN on 19 July 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	4
Introduction	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions	7
4 Substrate material.....	8
5 Coating powder.....	8
5.1 Identification.....	8
5.2 Storage	8
5.3 Performance requirements	9
5.3.1 General	9
5.3.2 Colour	9
5.3.3 Gloss.....	9
5.3.4 Adhesion	9
5.3.5 Resistance to scratching	9
5.3.6 Resistance to deformation.....	9
5.3.7 Resistance to mortar.....	9
5.3.8 Resistance to weathering	9
5.3.9 Resistance to humidity	10
5.3.10 Resistance to sulfur dioxide.....	10
5.3.11 Permeability.....	10
5.3.12 Resistance to salt spray	10
5.4 Health and safety information	10
6 Application	11
6.1 Cleaning and pretreatment of the hot dip galvanised or sherardised substrate.....	11
6.2 Coating powder.....	11
6.3 Application of coating powder	11
6.4 Significant surfaces of coated article.....	11
6.5 Performance requirements of the powder coated article.....	11
6.5.1 General	11
6.5.2 Surface appearance	11
6.5.3 Colour	11
6.5.4 Thickness	11
6.5.5 Gloss.....	12
6.5.6 Adhesion	12
7 Certificate of conformity	12
Annex A (normative) Methods of test for coating powders	15
A.1 General	15
A.2 Sampling.....	15
A.3 Coated test panels	15
A.3.1 Material and dimensions.....	15
A.3.2 Pretreatment.....	15
A.3.3 Coating of the test panels.....	15
A.3.4 Determination of thickness.....	15
A.3.5 Appearance and conditioning	16
A.4 Test procedures on coated test panels.....	16
A.4.1 Surface	16

A.4.2	Colour	16
A.4.3	Gloss	16
A.4.4	Adhesion	16
A.4.5	Resistance to scratching	17
A.4.6	Resistance to deformation	17
A.4.7	Resistance to mortar	17
A.4.8	Resistance to weathering	17
A.4.9	Resistance to humidity	17
A.4.10	Resistance to sulfur dioxide	18
A.4.11	Permeability	18
A.4.12	Resistance to salt spray	18
Annex B	(informative) Guidance on cleaning and pretreatment processes	19
B.1	Cleaning	19
B.2	Pretreatment	19
B.3	Types of pretreatment	19
B.3.1	Conversion and drying of the conversion coating (chemical pretreatment)	19
B.3.2	Mechanical pretreatment	20
Annex C	(informative) Guidelines on the powder coating process	21
Annex D	(normative) Methods of test for powder coatings	22
D.1	General	22
D.2	Test piece preparation	22
D.3	Test procedures on finished articles	22
D.3.1	Surface appearance	22
D.3.2	Colour	22
D.3.3	Thickness	22
D.3.4	Gloss	22
D.3.5	Adhesion	22
D.4	Test procedures on test panels	23
Annex E	(informative) Guidelines on the care and protection of powder coated hot dip galvanised or sherardised steel components	24
E.1	Packing and handling	24
E.2	Tapes	24
Bibliography	25

Foreword

This document (EN 13438:2013) has been prepared by Technical Committee CEN/TC 139 "Paints and varnishes", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2014, and conflicting national standards shall be withdrawn at the latest by March 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13438:2005.

In relation to EN 13438:2005, the following main amendments have been made:

- a) the term defined as "test sample" has been removed;
- b) a new term "substrate" has been introduced;
- c) a paragraph in Clause 4 includes references to EN ISO 14713-2 and EN ISO 14713-3 to optimise design of articles sent for processing to this standard;
- d) tolerance limits on gloss requirements has been tightened slightly for gloss levels over 50 units (reduced from ± 10 units to ± 7 units) and "Table 1 — Gloss requirements" removed;
- e) Clause 6 has been edited to clarify references to "cleaning" as distinct from "preparation" or "pretreatment";
- f) reference to (old) Table 1 in 6.5.5 "Gloss" has been removed;
- g) an adhesion test on the finished powder coated article is now not mandatory (see revised 6.5.6) and if required should be specified;
- h) a new "Table 1 — Summary of tests" has been included for ease of reference, after Clause 7;
- i) the minimum thickness of coated test panels used for tests for mechanical properties has been increased from 0,3 mm to 1,0 mm (see A.3.1);
- j) reference to updated standards have been included, e.g. replacement of ISO 7724-3 with EN ISO 11664-4 (see A.4.2) and replacement of ISO 1518 with EN ISO 1518-1 (see A.4.5);
- k) Annex B has been edited to clarify references to "cleaning" and "pretreatment" and the content reduced;
- l) the possibility of an adhesion test on finished article now included in Annex D (see D.3.5);
- m) the content of Annex E has been reduced – reference has been made to EN 15773 for further information.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

This European Standard has been produced as a result of the growing demand for products made of powder coated hot dip galvanised or sherardised steel. These products offer a combination of corrosion resistance and decorative appearance.

It is assumed in the drafting of this standard that the specified test methods will be applied by those who are suitably trained and supervised.

This European Standard has been written from a coating performance perspective and does not seek to set out one method of powder coating hot dip galvanised or sherardised steel products. Nevertheless, in order to facilitate production of the best quality powder coated hot dip galvanised or sherardised articles, experience has shown how important it is that sufficient dialogue between the client, specifier, designer, fabricator, galvaniser or sherardiser and powder coating applicator takes place at the earliest stages of the project and that, where possible, timescales set out for processing of the work are practical and adhered to.

It is strongly recommended that the guidance document for supply of duplex coatings, EN 15773, *Industrial application of powder organic coatings to hot dip galvanized or sherardized steel articles [duplex systems] — Specifications, recommendations and guidelines*, is used in combination with this standard when specifying for duplex systems.

1 Scope

This European Standard specifies performance requirements for organic coating powders and powder organic coatings as applied to finished articles (hot dip galvanised or sherardised steel products) for construction purposes. Hot dip galvanised steel products can be articles that have been batch hot dip galvanised (hot dip galvanised after fabrication) or articles consisting of continuously hot dip galvanised sheet which is then subsequently fabricated.

This European Standard does not set out any performance requirements for the powder coating process itself. Guidance on cleaning and pretreatment of the hot dip galvanised or sherardised steel products prior to powder coating is provided.

This European Standard does not apply to articles with zinc-aluminium coatings or aluminium-zinc coatings, or to continuously hot dip galvanised wire. This standard does not apply to organic coating powders and powder organic coatings as applied to hot dip galvanised or sherardised steel products (i.e. duplex coated articles) for which there are specific standards, which might include additional requirements or requirements which are different from those of this standard.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10346, *Continuously hot-dip coated steel flat products — Technical delivery conditions*

EN 13811, *Sherardizing — Zinc diffusion coatings on ferrous products — Specification*

EN ISO 1461, *Hot dip galvanized coatings on fabricated iron and steel articles — Specifications and test methods (ISO 1461)*

EN ISO 1518-1, *Paints and varnishes — Determination of scratch resistance — Part 1: Constant loading method (ISO 1518-1)*

EN ISO 1519, *Paints and varnishes — Bend test (cylindrical mandrel) (ISO 1519)*

EN ISO 2178, *Non-magnetic coatings on magnetic substrates — Measurement of coating thickness — Magnetic method (ISO 2178)*

EN ISO 2409, *Paints and varnishes — Cross-cut test (ISO 2409)*

EN ISO 2808, *Paints and varnishes — Determination of film thickness (ISO 2808)*

EN ISO 2810, *Paints and varnishes — Natural weathering of coatings — Exposure and assessment (ISO 2810)*

EN ISO 2813, *Paints and varnishes — Determination of specular gloss of non-metallic paint films at 20°, 60° and 85° (ISO 2813)*

EN ISO 3231, *Paints and varnishes — Determination of resistance to humid atmospheres containing sulfur dioxide (ISO 3231)*

EN ISO 3668, *Paints and varnishes — Visual comparison of the colour of paints (ISO 3668)*

EN ISO 4618:2006, *Paints and varnishes — Terms and definitions (ISO 4618:2006)*

EN ISO 6270-1, *Paints and varnishes — Determination of resistance to humidity — Part 1: Continuous condensation (ISO 6270-1)*

EN ISO 8130-9, *Coating powders — Part 9: Sampling (ISO 8130-9)*

EN ISO 9227, *Corrosion tests in artificial atmospheres — Salt spray tests (ISO 9227)*

EN ISO 11341:2004, *Paints and varnishes — Artificial weathering and exposure to artificial radiation — Exposure to filtered xenon-arc radiation (ISO 11341:2004)*

EN ISO 11664-4, *Colorimetry — Part 4: CIE 1976 L*a*b Colour space (ISO 11664-4)*

ISO 10474, *Steel and steel products — Inspection documents*

3 Terms and definitions

For the purposes of this document, the terms and definitions contained in EN ISO 4618:2006 and the following apply.

3.1

finishing coat

final coat of a coating system

[SOURCE: EN ISO 4618:2006, 2.108]

3.2

conversion coating

layer produced on a hot dip galvanised or sherardised steel surface by a chemical treatment

3.3

powder coating

dry film obtained by application and fusing of a coating powder

3.4

coating powder

solvent-free coating material in powder form which, after fusing and possible curing, gives a continuous film

3.5

test piece

single item, representative of the work being processed

3.6

significant surface

part of the coated article on which the coating is essential for serviceability of the article

3.7

specifier

person specifying the performance requirements for the coating and significant surfaces of the article

3.8

coating applicator

company responsible for applying the coating powder onto a substrate

3.9

substrate

surface to which a coating material is applied or is to be applied