
**Petroleum and natural gas industries —
Cements and materials for well
cementing —**

**Part 2:
Testing of well cements**

*Industries du pétrole et du gaz naturel — Ciments et matériaux pour la
cimentation des puits —*

Partie 2: Essais de ciment pour puits



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

This document is a preview generated by EVS

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	vi
Introduction	vii
1 Scope.....	1
2 Normative references	1
3 Terms, definitions and symbols	1
3.1 Terms and definitions	1
3.2 Symbols	7
4 Sampling	8
4.1 General	8
4.2 Sampling cement at field location	8
4.3 Sampling cement blends at field location	8
4.4 Sampling dry cement additives at field location	8
4.5 Sampling liquid cement additives at field location	8
4.6 Sampling mixing water	8
4.7 Shipping and storage	10
4.8 Sample preparation prior to testing	10
4.9 Sample disposal	10
5 Preparation of slurry	10
5.1 General	10
5.2 Apparatus	10
5.3 Procedure	12
6 Determination of slurry density	14
6.1 Preferred apparatus	14
6.2 Calibration	14
6.3 Procedure	14
6.4 Alternative apparatus and procedure	16
7 Well-simulation compressive strength tests	16
7.1 General	16
7.2 Sampling	16
7.3 Preparation of slurry	17
7.4 Apparatus	17
7.5 Procedure	18
7.6 Determination of cement compressive strength at the top of long cement columns	20
8 Non-destructive sonic testing of cement	26
8.1 General	26
8.2 Apparatus	26
8.3 Sampling	26
8.4 Preparation of slurry	26
8.5 Procedure	26
8.6 Curing time	26
8.7 Curing schedules	26
8.8 Data reporting	27
9 Well-simulation thickening-time tests	27
9.1 General	27
9.2 Apparatus and material	27
9.3 Calibration	28
9.4 Test procedure	30

9.5	Determination of test schedule	32
10	Static fluid-loss tests	38
10.1	General	38
10.2	Apparatus	38
10.3	Safety	39
10.4	Mixing procedure	39
10.5	Conditioning procedures	39
10.6	Procedures for testing at temperatures $\leq 88\text{ }^{\circ}\text{C}$ ($190\text{ }^{\circ}\text{F}$)	39
10.7	Procedures for testing at temperatures $> 88\text{ }^{\circ}\text{C}$ ($190\text{ }^{\circ}\text{F}$)	40
10.8	Filling the static fluid-loss cell	42
10.9	Fluid loss test	43
10.10	Test completion and clean-up	43
11	Permeability tests	45
11.1	General	45
11.2	Apparatus	45
11.3	Sample preparation	46
11.4	Liquid permeability (cement permeameter)	46
11.5	Alternative procedure (core permeameter) for liquid permeability	47
11.6	Calculating liquid permeability	50
11.7	Gas permeability (core permeameter)	50
11.8	Calculating gas permeability	51
12	Determination of rheological properties and gel strength using a rotational viscometer	52
12.1	General	52
12.2	Apparatus	52
12.3	Calibration	54
12.4	Determination of rheological properties	54
12.5	Determination of gel strength	56
12.6	Modelling of the rheological behaviour	57
13	Calculation of pressure drop and flow regime for cement slurries in pipes and annuli	65
13.1	General	65
13.2	Newtonian fluids	67
13.3	Power Law fluids	71
13.4	Bingham Plastic fluids	77
13.5	Conversion factors	87
14	Test procedure for arctic cementing slurries	87
14.1	General	87
14.2	Preparation of cement slurry	87
14.3	Fluid fraction	87
14.4	Thickening time	87
14.5	Compressive strength	87
14.6	Freeze-thaw cycling at atmospheric pressure	88
14.7	Compressive strength cyclic testing	88
15	Well-simulation slurry stability tests	88
15.1	Introduction	88
15.2	Slurry mixing	89
15.3	Slurry conditioning	89
15.4	Free-fluid test with heated static period	89
15.5	Free-fluid test with ambient temperature static period	90
15.6	Sedimentation test	90
16	Compatibility of wellbore fluids	94
16.1	General	94
16.2	Preparation of test fluids	94
16.3	Rheology	95
16.4	Thickening time	95
16.5	Compressive strength	95
16.6	Solids suspension and static gel strength	96

16.7	Fluid loss.....	96
17	Pozzolans.....	98
17.1	General.....	98
17.2	Types of pozzolan.....	98
17.3	Physical and chemical properties.....	98
17.4	Slurry calculations.....	99
17.5	Bulk volume of a blend.....	100
Annex A	(normative) Procedure for preparation of large slurry volumes.....	102
Annex B	(normative) Calibration procedures for thermocouples, temperature-measuring systems and controllers.....	104
Annex C	(informative) Additional information relating to temperature determination.....	106
Annex D	(normative) Alternative apparatus for well thickening-time tests.....	113
Annex E	(informative) Cementing schedules.....	116
Bibliography		171

Foreword

ISO (the International Organisation for Standardisation) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organisations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardisation.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10426-2 was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, Subcommittee SC 3, *Drilling and completion fluids and well cements*.

ISO 10426 consists of the following parts, under the general title *Petroleum and natural gas industries — Cements and materials for well cementing*:

- *Part 1: Specification*
- *Part 2: Testing of well cements*
- *Part 3: Testing of deepwater well cement formulations*
- *Part 4: Preparation and testing of foamed cement slurries at atmospheric pressure*

The following part is under preparation:

- *Part 5: Determination of shrinkage and expansion of well cement formulations at atmospheric pressure*

Introduction

This part of ISO 10426 is based on API RP 10B, 22nd edition, December 1997, addendum 1, October 1999.

Users of this part of ISO 10426 should be aware that further or differing requirements may be needed for individual applications. This part of ISO 10426 is not intended to inhibit a vendor from offering, or the purchaser from accepting, alternative equipment or engineering solutions for the individual application. This may be particularly applicable where there is innovative or developing technology. Where an alternative is offered, the vendor should identify any variations from this part of ISO 10426 and provide details.

In this part of ISO 10426, where practical, US Customary units are included in brackets for information.

Well cement classes and grades are defined in ISO 10426-1.

This document is a preview generated by EVS

Petroleum and natural gas industries — Cements and materials for well cementing —

Part 2: Testing of well cements

1 Scope

This part of ISO 10426 specifies requirements and gives recommendations for the testing of cement slurries and related materials under simulated well conditions.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10414-1, *Petroleum and natural gas industries — Field testing of drilling fluids — Part 1: Water-based fluids*

API RP 13J, *Testing of heavy brines (second edition)*, March 1996

ASTM C 109, *Standard test method for compressive strength of hydraulic cement mortars (using 2 in. or [50 mm] cube specimens)*

ASTM C 188, *Standard test method for density of hydraulic cement*

3 Terms, definitions and symbols

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1.1

absolute volume

reciprocal of absolute density

NOTE It is expressed as volume per unit mass.

3.1.2

additive

material added to a cement slurry to modify or enhance some desired property

NOTE Common properties that are modified include: setting time (by use of retarders or accelerators), fluid loss control, viscosity, etc.