

Structural timber - Sizes, permitted deviations

This document is a preview generated by EVS

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 336:2013 sisaldab Euroopa standardi EN 336:2013 ingliskeelset teksti.	This Estonian standard EVS-EN 336:2013 consists of the English text of the European standard EN 336:2013.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 02.10.2013.	Date of Availability of the European standard is 02.10.2013.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 79.040

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

English Version

Structural timber - Sizes, permitted deviations

Bois de structure - Dimensions, écarts admissibles

Bauholz für tragende Zwecke - Maße, zulässige
Abweichungen

This European Standard was approved by CEN on 24 August 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
Introduction	4
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions	5
4 Sizes for structural timber	5
4.1 General	5
4.2 Changes in size due to changes in moisture content	6
4.3 Permitted cross-sectional deviations.....	6
4.4 Permitted length deviations.....	6
5 Moisture content measurement.....	6
Bibliography.....	7

Foreword

This document (EN 336:2013) has been prepared by Technical Committee CEN/TC 124 "Timber structures", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2014, and conflicting national standards shall be withdrawn at the latest by April 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document will supersede EN 336:2003.

Compared to EN 336:2003, the following modifications have been made:

- a) in the scope, the limit to 300 mm is deleted so the standard is available for large cross section;
- b) minimum size changed from 22 mm to 6 mm;
- c) in subclause 4.2, the changes in size due to changes in moisture content are given for hardwoods;
- d) in subclause 4.3, the permitted cross sectional deviations are given for thicknesses and widths above 300 mm;
- e) in Clause 5, moisture content measurement in accordance with the three parts of EN 13183.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

Target size is the basis for the standard.

A method of calculating sizes at other moisture levels is provided.

The standard also stipulates a method for the measurement of moisture content.

This document is a preview generated by EVS

1 Scope

This European Standard specifies two classes of permitted deviations from target sizes for structural timber of softwood and hardwood species.

It also specifies the moisture content to be used as a reference point for the measurement of sizes, and gives average values for changes in size due to changes in moisture content.

It is applicable to sawn and prepared square-edged structural timber with parallel edges having sawn thicknesses or widths greater than 6 mm.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1309-1, *Round and sawn timber — Method of measurement of dimensions — Part 1: Sawn timber*

EN 13183-1, *Moisture content of a piece of sawn timber — Part 1: Determination by oven dry method*

EN 13183-2, *Moisture content of a piece of sawn timber — Part 2: Estimation by electrical resistance method*

EN 13183-3, *Moisture content of a piece of sawn timber — Part 3: Estimation by capacitance method*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

target size

size specified (at the reference moisture content), and to which the deviations, which would ideally be zero, are to be related

3.2

deviation

difference between actual size and the corresponding target size, making allowance for the difference in size due to difference in moisture content (see Clause 5)

3.3

moisture content

amount of water present in timber, expressed as a percentage of the oven-dry mass

4 Sizes for structural timber

4.1 General

Sizes shall be measured in accordance with EN 1309-1.

For the purposes of this European Standard, the reference moisture content is 20 %.

NOTE The reference moisture content is the moisture content at which sizes are given. It is different from target moisture contents which are defined in EN 14298.