

Wood-based panels - Determination of formaldehyde release - Part 3: Gas analysis method (ISO 12460-3:2015)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 12460-3:2015 sisaldab Euroopa standardi EN ISO 12460-3:2015 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 12460-3:2015 consists of the English text of the European standard EN ISO 12460-3:2015.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 18.11.2015.	Date of Availability of the European standard is 18.11.2015.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 79.060.01

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Aru 10, 10317 Tallinn, Eesti; koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Wood-based panels - Determination of formaldehyde
release - Part 3: Gas analysis method (ISO 12460-3:2015)

Panneaux à base de bois - Détermination du
dégagement de formaldéhyde - Partie 3: Méthode
d'analyse de gaz (ISO 12460-3:2015)

Holzwerkstoffe - Bestimmung der Formaldehydabgabe
- Teil 3: Gasanalyse-Verfahren (ISO 12460-3:2015)

This European Standard was approved by CEN on 29 August 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 12460-3:2015) has been prepared by Technical Committee ISO/TC 89 “Wood-based panels” in collaboration with Technical Committee CEN/TC 112 “Wood-based panels” the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2016, and conflicting national standards shall be withdrawn at the latest by May 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 717-2:1994.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 12460-3:2015 has been approved by CEN as EN ISO 12460-3:2015 without any modification.

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Reagents	1
5 Apparatus	2
5.1 Main composites of test apparatus (see Figure 1).....	2
5.2 Laboratory equipment.....	2
6 Sampling and preparation of test pieces	3
6.1 Preparation of test pieces.....	3
6.2 Selection of test pieces for factory production control.....	3
6.3 Selection of test pieces for other purposes.....	4
6.4 Selection of test pieces in case of dispute.....	4
7 Procedure	4
7.1 Number of determinations.....	4
7.2 Determination of moisture content.....	4
7.3 Determination of formaldehyde release.....	4
7.4 Determination of formaldehyde content of the aqueous solutions.....	5
7.4.1 General.....	5
7.4.2 Principle.....	5
7.4.3 Analytical Procedure.....	5
7.4.4 Calibration curve.....	5
8 Expression of results	7
8.1 Gas analysis value.....	7
8.2 Calculation of results.....	7
8.2.1 Calculation of results of test pieces.....	7
8.2.2 Calculation of emission report value.....	8
8.3 Moisture content.....	8
9 Test report	8
Bibliography	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 89, *Wood-based panels*.

This second edition cancels and replaces the first edition (ISO 12460-3:2008), which has been technically revised.

The objective of the revision was to improve the detection limit and the reproducibility of the method with regard to boards with low formaldehyde content.

Compared to ISO 12460-3:2008, the following modifications have been made:

- a) in [6.1](#) preparation of test pieces is described more in detail;
- b) in [6.2](#) recommendation of maximum time 72 h after sampling for formaldehyde determination is added;
- c) in [6.4](#) conditioning for sampling and testing in case of dispute is added;
- d) in [7.1](#) and [8.2.2](#) procedure and evaluation of third determination are modified;
- e) in [7.3](#) use of smaller gas wash bottles and volumetric flasks to improve the sensitivity is included as an option;
- f) in [7.4.3](#) the use of a mixed reagent is included as an option to reduce the amounts of aqueous solution and hence improve the sensitivity;
- g) in [7.4.3](#) temperature of water bath increased to 60 °C and cooling procedure is modified;
- h) in [7.4.4.1](#) minimum interval of check of the calibration curve is extended to once a month;
- i) in [Clause 9](#) age and treatment of the sample are included in the test report;
- j) in [Figure 2](#) calibration curve is modified.

ISO 12460 consists of the following parts, under the general title *Wood-based panels — Determination of formaldehyde release*:

- *Part 1: Formaldehyde emission by the 1-cubic-metre chamber method*
- *Part 3: Gas analysis method*
- *Part 4: Desiccator method*
- *Part 5: Extraction method (called the perforator method)*

Additional parts dealing with small-scale chamber method is planned.

Wood-based panels — Determination of formaldehyde release —

Part 3: Gas analysis method

1 Scope

This part of ISO 12460 specifies a procedure for determination of accelerated formaldehyde release from uncoated and coated wood-based panels using the gas analysis method. The procedure is also suitable for the testing of other materials (e.g. edge bands, floor coverings, foams, foils, laminated wood products, veneered wood products, coated wood products).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 16979, *Wood-based panels — Determination of moisture content*

ISO 16999, *Wood-based panels — Sampling and cutting of test pieces*

3 Principle

A test piece of known surface area is placed in a closed chamber in which the temperature, humidity, airflow, and pressure are controlled to defined values. Formaldehyde released from the test pieces mixes with the air in the chamber. This air is continually drawn from the chamber and passes through gas wash bottles, containing water, which absorbs the released formaldehyde. At the end of the test, the formaldehyde concentration is determined photometrically or fluorimetrically. The formaldehyde release is calculated from this concentration, the sampling time, and the exposed area of the test pieces and is expressed in milligrams per square meter and hour ($\text{mg}/\text{m}^2\text{h}$).

4 Reagents

Reagents of recognized analytical purity and distilled or demineralised water (referred throughout the following text as distilled water) shall be used for the analysis.

4.1 4 ml Acetylacetone solution are added to a 1 000 ml volumetric flask and made up to the mark with distilled water.

4.2 200 g ammonium acetate solution are dissolved with distilled water in a 1 000 ml volumetric flask and made up to the mark.

Optionally, a premixed reagent of acetylacetone and ammonium acetate as described in ISO 12460-4 can be used.

4.3 Formaldehyde solution commercially available (concentration typically between 35 % mass fraction to 40 % mass fraction).