
**Thermoplastics valves for industrial
applications — Pressure test methods
and requirements —**

**Part 2:
Test conditions and basic requirements**

*Robinets en matières thermoplastiques pour les applications
industrielles — Méthodes d'essai de pression et exigences —*

Partie 2: Conditions d'essai et exigences de base



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

This document is a preview generated by EVS

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 9393-2 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 7, *Valves and auxiliary equipment of plastics materials*.

This second edition cancels and replaces the first edition (ISO 9393-2:1997), which has been technically revised. It also incorporates the Technical Corrigendum ISO 9393-2:1997/Cor 1:1997.

ISO 9393 consists of the following parts, under the general title *Thermoplastics valves for industrial applications — Pressure test methods and requirements*:

- *Part 1: General*
- *Part 2: Test conditions and basic requirements*

This document is a preview generated by EVS

Thermoplastics valves for industrial applications — Pressure test methods and requirements —

Part 2: Test conditions and basic requirements

1 Scope

This part of ISO 9393 specifies the test parameters and conditions for hydrostatic-pressure tests on valves made of the following thermoplastic materials:

- ABS, as defined in ISO 15493
- PE 80, as defined in ISO 15494
- PE 100, as defined in ISO 15494
- PP-H, as defined in ISO 15494
- PP-B, as defined in ISO 15494
- PP-R, as defined in ISO 15494
- PP-R-GF
- PVC-C, as defined in ISO 15493
- PVC-U, as defined in ISO 15493
- PVDF, as defined in ISO 10931

NOTE Materials designation according to ISO 1043-1 and ISO 1043-2 for reinforcing materials.

The tests cover the following aspects:

- the material used for manufacturing valves;
- the pressurized valve components;
- the complete valve.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5208, *Industrial valves — Pressure testing of valves*

ISO 9080, *Plastics piping and ducting systems — Determination of the long-term hydrostatic strength of thermoplastics materials in pipe form by extrapolation*

ISO 9393-1:2004, *Thermoplastics valves for industrial applications — Pressure test methods and requirements — Part 1: General*

ISO 10931¹⁾, *Plastics piping systems for industrial applications — Poly(vinylidene fluoride) (PVDF) — Specifications for components and the system*

ISO 15493:2003, *Plastics piping systems for industrial applications — Acrylonitrile-butadiene-styrene (ABS), unplasticized poly(vinyl chloride) (PVC-U) and chlorinated poly(vinyl chloride) (PVC-C) — Specifications for components and the system — Metric series*

ISO 15494, *Plastics piping systems for industrial applications — Polybutene (PB), polyethylene (PE) and polypropylene (PP) — Specifications for components and the system — Metric series*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 9393-1 apply.

4 Materials test

4.1 The material shall be tested in accordance with the conditions and requirements given in ISO 9080 or equivalent.

4.2 It is not necessary to retest material which has already been tested by the material supplier.

5 Shell test

5.1 Test conditions

The test specimen described in ISO 9393-1:2004, 5.2, shall be subjected to the applicable test conditions as given in Table 1.

5.2 Requirements

The test specimen shall be considered satisfactory if no leakage from the valve is noted, and no rupture or other visible failure occurs during the test period. The test specimen shall be regarded as unsatisfactory if the valve body bursts before the end of the test period.

If a pipe or a connection fails, the test shall be considered null and void and shall be repeated using a different specimen.

1) To be published. (Revision of ISO 10931-1:1997, ISO 10931-2:1997, ISO 10931-3:1996, ISO 10931-4:1997 and ISO 10931-5:1998)