

Solid biofuels - Determination of particle size distribution - Part 1: Oscillating screen method using sieve apertures of 1 mm and above

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 15149-1:2010 sisaldab Euroopa standardi EN 15149-1:2010 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 30.11.2010 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 27.10.2010.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 15149-1:2010 consists of the English text of the European standard EN 15149-1:2010.

This standard is ratified with the order of Estonian Centre for Standardisation dated 30.11.2010 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 27.10.2010.

The standard is available from Estonian standardisation organisation.

ICS 75.160.10

Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

Right to reproduce and distribute belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:
Aru str 10 Tallinn 10317 Estonia; www.evs.ee; Phone: 605 5050; E-mail: info@evs.ee

English Version

**Solid biofuels - Determination of particle size distribution - Part
1: Oscillating screen method using sieve apertures of 1 mm and
above**

Biocombustibles solides - Détermination de la distribution
granulométrique - Partie 1: Méthode au tamis oscillant
d'ouverture de maille égale ou supérieure à 1 mm

Feste Biobrennstoffe - Bestimmung der
Partikelgrößenverteilung - Teil 1: Rüttelsiebverfahren mit
Sieb-Lochgrößen von 1 mm und darüber

This European Standard was approved by CEN on 26 September 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principle.....	5
5 Apparatus	5
6 Sample preparation	7
6.1 Sample size	7
6.2 Moisture conditions.....	8
7 Procedure	8
8 Calculation.....	8
9 Precision	10
9.1 Repeatability.....	10
9.2 Reproducibility.....	10
10 Test report	10
Annex A (normative) Determination of the median value of a particle size distribution.....	11
A.1 Definition	11
A.2 Procedure (example)	12
A.3 Calculation.....	12
Bibliography	13

Foreword

This document (EN 15149-1:2010) has been prepared by Technical Committee CEN/TC 335 “Solid biofuels”, the secretariat of which is held by SIS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2011, and conflicting national standards shall be withdrawn at the latest by April 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes CEN/TS 15149-1:2006.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

EN 15149, *Solid biofuels — Determination of particle size distribution*, consists of the following parts:

- *Part 1: Oscillating screen method using sieve apertures of 1 mm and above;*
- *Part 2: Vibrating screen method using sieve apertures of 3,15 mm and below.*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Introduction

Part 1 describes the reference method for size classification of samples with a nominal top size of 1 mm and above.

Part 2 describes the reference method for size classification of samples with a nominal top size below 3,15 mm.

Manual sieving is not included in this standard, as no data is available which supports that manual sieving operations are comparable to the here described mechanical sieving operations.

1 Scope

This European Standard specifies a method for the determination of the size distribution of particulate biofuels by the horizontally oscillating screen method. It applies to particulate uncompressed fuels with a nominal top size of 1 mm and above as e.g. wood chips, hog fuel, olive stones, etc.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 14588:2010, *Solid biofuels — Terminology, definitions and descriptions*

EN 14774-1:2009, *Solid biofuels — Determination of moisture content — Oven dry method — Part 1: Total moisture — Reference method*

EN 14774-2:2009, *Solid biofuels — Determination of moisture content — Oven dry method — Part 2: Total moisture — Simplified method*

prEN 14778, *Solid biofuels — Sampling*

prEN 14780, *Solid biofuels — Sample preparation*

EN 14961-1, *Solid biofuels — Fuel specifications and classes — Part 1: General requirements*

EN 15149-2, *Solid biofuels — Determination of particle size distribution — Part 2: Vibrating screen method using sieve apertures of 3,15 mm and below*

ISO 3310-1, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

ISO 3310-2, *Test sieves — Technical requirements and testing — Part 2: Test sieves of perforated metal plate*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 14588:2010 and the following apply.

3.1

median value of the size distribution

value [d₅₀] that separates a distribution into two equal parts and that is graphically the intercept point of the cumulative size distribution curve with the 50 %-horizontal line

4 Principle

A sample is subjected to sieving through horizontally oscillating sieves, sorting the particles in decreasing size classes by mechanical means.

5 Apparatus

5.1 Sieves.

For the test an appropriate number of either circular or rectangular sieves with a minimum effective sieve area of 1 200 cm² is required. The geometry of the apertures shall be in accordance with the requirements of ISO 3310-1 and -2, respectively. The frame of the sieves shall have a height that enables the sieves to contain the sample and allows a free movement of the sample during the sieving process.