

Steel tubes for precision applications - Technical
delivery conditions - Part 2: Welded cold drawn tubes

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 10305-2:2016 sisaldab Euroopa standardi EN 10305-2:2016 ingliskeelset teksti.	This Estonian standard EVS-EN 10305-2:2016 consists of the English text of the European standard EN 10305-2:2016.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 30.03.2016.	Date of Availability of the European standard is 30.03.2016.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 77.140.75

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Aru 10, 10317 Tallinn, Eesti; koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Steel tubes for precision applications - Technical delivery
conditions - Part 2: Welded cold drawn tubes

Tubes de précision en acier - Conditions techniques de
livraison - Partie 2 : Tubes soudés étirés à froid

Präzisionsstahlrohre - Technische Lieferbedingungen -
Teil 2: Geschweißte kaltgezogene Rohre

This European Standard was approved by CEN on 18 January 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	4
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions	6
4 Symbols.....	6
5 Classification and designation.....	7
5.1 Classification.....	7
5.2 Designation.....	7
6 Information to be supplied by the purchaser	7
6.1 Mandatory information	7
6.2 Options.....	7
6.3 Example of an order	8
7 Manufacturing process.....	8
7.1 Steelmaking process	8
7.2 Tube manufacture and delivery conditions.....	8
8 Requirements.....	9
8.1 General.....	9
8.2 Chemical composition	9
8.3 Mechanical properties.....	10
8.4 Appearance and internal soundness.....	11
8.5 Dimensions and tolerances	12
8.5.1 Outside diameter, inside diameter, wall thickness and eccentricity	12
8.5.2 Lengths.....	15
8.5.3 Straightness.....	16
8.5.4 Preparation of ends.....	17
9 Inspection	17
9.1 Types of inspection.....	17
9.2 Inspection documents	17
9.2.1 Types of inspection documents.....	17
9.2.2 Content of inspection documents.....	17
9.3 Summary of inspection and testing	18
10 Sampling.....	18
10.1 Test unit.....	18
10.2 Preparation of samples and test pieces	19
10.2.1 Location, orientation and preparation of samples and test pieces for mechanical tests	19
10.2.2 Test pieces for roughness measurement.....	19
11 Test methods	19
11.1 Tensile test	19
11.2 Flattening test.....	19
11.3 Drift expanding test.....	20
11.4 Dimensional inspection	20
11.5 Roughness measurement.....	20

11.6	Visual examination	21
11.7	Non-destructive testing.....	21
11.7.1	Testing for longitudinal imperfections.....	21
11.7.2	Leak tightness	21
11.8	Retests, sorting and reprocessing	21
12	Marking	21
13	Protection and packaging.....	21
	Bibliography	23

European foreword

This document (EN 10305-2:2016) has been prepared by Technical Committee ECISS/TC 110 “Steel tubes and iron and steel fittings”, the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2016 and conflicting national standards shall be withdrawn at the latest by September 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10305-2:2010.

In comparison with the previous edition, the following technical changes have been made:

- a) References were adapted;
- b) The options were renumbered in such a way that now throughout all parts the number of options are the same;
- c) Editorial updates.

EN 10305, *Steel tubes for precision applications — Technical delivery conditions*, consists of the following parts:

- *Part 1: Seamless cold drawn tubes*
- *Part 2: Welded cold drawn tubes*
- *Part 3: Welded cold sized tubes*
- *Part 4: Seamless cold drawn tubes for hydraulic and pneumatic power systems*
- *Part 5: Welded cold sized square and rectangular tubes*
- *Part 6: Welded cold drawn tubes for hydraulic and pneumatic power systems*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies the technical delivery conditions for welded cold drawn steel tubes of circular cross section for precision applications with specified outside diameter $D \leq 150$ mm.

This document may also be applied to other types of cross section.

Tubes according to this document are characterized by having precisely defined tolerances on dimensions and a specified maximum surface roughness. Typical fields of application are in the automotive, furniture and general engineering industries.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10020:2000, *Definition and classification of grades of steel*

EN 10021:2006, *General technical delivery conditions for steel products*

EN 10027-1, *Designation systems for steels - Part 1: Steel names*

EN 10027-2, *Designation systems for steels - Part 2: Numerical system*

EN 10052:1993, *Vocabulary of heat treatment terms for ferrous products*

EN 10168, *Steel products - Inspection documents - List of information and description*

EN 10204, *Metallic products - Types of inspection documents*

EN 10266:2003, *Steel tubes, fittings and structural hollow sections - Symbols and definitions of terms for use in product standards*

EN ISO 377, *Steel and steel products - Location and preparation of samples and test pieces for mechanical testing (ISO 377)*

EN ISO 2566-1, *Steel - Conversion of elongation values - Part 1: Carbon and low alloy steels (ISO 2566-1)*

EN ISO 4287, *Geometrical product specifications (GPS) - Surface texture: Profile method - Terms, definitions and surface texture parameters (ISO 4287)*

EN ISO 6892-1, *Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1)*

EN ISO 8492, *Metallic materials - Tube - Flattening test (ISO 8492)*

EN ISO 8493, *Metallic materials - Tube - Drift-expanding test (ISO 8493)*

EN ISO 10893-1, *Non-destructive testing of steel tubes - Part 1: Automated electromagnetic testing of seamless and welded (except submerged arc-welded) steel tubes for the verification of hydraulic leaktightness (ISO 10893-1)*

EN ISO 10893-2, *Non-destructive testing of steel tubes - Part 2: Automated eddy current testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of imperfections (ISO 10893-2)*

EN ISO 10893-3, *Non-destructive testing of steel tubes - Part 3: Automated full peripheral flux leakage testing of seamless and welded (except submerged arc-welded) ferromagnetic steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-3)*

EN ISO 10893-10, *Non-destructive testing of steel tubes - Part 10: Automated full peripheral ultrasonic testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-10)*

ISO 11484, *Steel products - Employer's qualification system for non-destructive testing (NDT) personnel*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 10020:2000, EN 10021:2006, EN 10052:1993, EN 10266:2003 and the following apply.

3.1

employer

organization for which a person works on a regular basis

Note 1 to entry: The employer can be either the tube manufacturer or a third party organization providing services, such as non-destructive testing (NDT).

3.2

manufacturer

party to produce and to deliver tubes in accordance with this document

Note 1 to entry: Where tubes are delivered by an intermediary, see EN 10021:2006, Clause 6.

3.3

imperfection

discontinuity in the wall or on the pipe surfaces detectable by methods described in this document

Note 1 to entry: Imperfections with a size complying with the acceptance criteria specified in this document are considered to have no practical implication on the intended use of the product.

3.4

defect

imperfection of a size not complying with the acceptance criteria specified in this document

Note 1 to entry: Defects are considered to adversely affect or limit the intended use of the product.

3.5

parent coil

coil originating from the hot rolling process prior to any further operation (pickling, slitting, cold rolling or coating)

4 Symbols

For the purposes of this document, the symbols in EN 10266:2003 apply.

NOTE For tubes specified by the outside diameter and by the inside diameter, "T" is the specified or the calculated wall thickness in this document.