

Plastics piping systems for hot and cold water
installations - Polybutene (PB) - Part 2: Pipes (ISO
15876-2:2017)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 15876-2:2017 sisaldab Euroopa standardi EN ISO 15876-2:2017 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 15876-2:2017 consists of the English text of the European standard EN ISO 15876-2:2017.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 08.02.2017.	Date of Availability of the European standard is 08.02.2017.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 23.040.20, 91.140.60

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Plastics piping systems for hot and cold water installations
- Polybutene (PB) - Part 2: Pipes (ISO 15876-2:2017)

Systèmes de canalisations en plastique pour les
installations d'eau chaude et froide - Polybutène (PB) -
Partie 2: Tubes (ISO 15876-2:2017)

Kunststoff-Rohrleitungssysteme für die Warm- und
Kaltwasserinstallation - Polybuten (PB) - Teil 2: Rohre
(ISO 15876-2:2017)

This European Standard was approved by CEN on 24 December 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 15876-2:2017) has been prepared by Technical Committee CEN/TC 155 “Plastics piping systems and ducting systems” the secretariat of which is held by NEN, in collaboration with Technical Committee ISO/TC 138 “Plastics pipes, fittings and valves for the transport of fluids”.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2017, and conflicting national standards shall be withdrawn at the latest by August 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 15876-2:2003.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 15876-2:2017 has been approved by CEN as EN ISO 15876-2:2017 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions, symbols and abbreviated terms	2
4 Pipe material	2
4.1 General	2
4.2 Evaluation of σ_{LPL} -curves	2
4.3 Influence on water intended for human consumption	5
5 General characteristics	6
5.1 Appearance	6
5.2 Opacity	6
6 Geometrical characteristics	6
6.1 General	6
6.2 Dimensions of pipes	7
6.2.1 Outside diameters	7
6.2.2 Wall thicknesses and their tolerances	7
7 Mechanical characteristics	10
8 Physical and chemical characteristics	10
9 Performance requirements	11
10 Marking	11
10.1 General requirements	11
10.2 Minimum required marking	12
Annex A (normative) Derivation of $S_{calc,max}$	13
Bibliography	16

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

ISO 15876-2 was prepared by the European Committee Standardization (CEN) Technical Committee CEN/TC 155, *Plastics piping systems and ducting systems*, in collaboration with ISO Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 2, *Plastics pipes and fittings for water supplies*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 15876-2:2003), which has been technically revised with the following changes:

- introduction of polybutene random copolymer (PB-R) and renaming existing polybutene (PB) into polybutene homopolymer (PB-H);
- revision of specifications for conditioning of samples.

It also incorporates the Amendment ISO 15876-2:2003/Amd 1:2007.

A list of all parts in the ISO 15876 series can be found on the ISO website.

Introduction

The System Standard ISO 15876, of which this document is Part 2, specifies the requirements for a piping system when made from polybutene (PB). The piping system is intended to be used for hot and cold water installations.

In respect of potential adverse effects on the quality of water intended for human consumption, caused by the product covered by ISO 15876 (all parts):

- ISO 15876 (all parts) provides no information as to whether the product may be used without restriction in any of the Member States of the EU or EFTA;
- it should be noted that, while awaiting the adoption of verifiable European criteria, existing national regulations concerning the use and/or the characteristics of this product remain in force.

Requirements and test methods for material and components, other than pipes, are specified in ISO 15876-1 and ISO 15876-3. Characteristics for fitness for purpose (mainly for joints) are covered in ISO 15876-5. ISO/TS 15876-7 gives guidance for the assessment of conformity.

This document specifies the characteristics of pipes.

At the date of publication of this standard, System Standards for piping systems of other plastics materials used for the same application include ISO 15874, ISO 15875, ISO 15876, ISO 15877, ISO 21003 and ISO 22391.

Plastics piping systems for hot and cold water installations — Polybutene (PB) —

Part 2: Pipes

1 Scope

This document specifies the characteristics of pipes for polybutene-1 (PB-1) piping systems intended to be used for hot and cold water installations within buildings for the conveyance of water whether or not intended for human consumption (domestic systems), and for heating systems, under design pressures and temperatures appropriate to the class of application (see ISO 15876-1).

The designation polybutene is used together with the abbreviation PB throughout this document.

This document covers a range of service conditions (application classes), design pressures and pipe dimension classes. For values of T_D , T_{max} and T_{mal} in excess of those in ISO 15876-1, this document does not apply.

NOTE 1 It is the responsibility of the purchaser or specifier to make the appropriate selections from these aspects, taking into account their particular requirements and any relevant national regulations and installation practices or codes.

It also specifies the test parameters for the test methods referred to in this document.

In conjunction with the other parts of ISO 15876, this document is applicable to PB pipes, their joints and to joints with components of PB, other plastics and non-plastics materials intended to be used for hot and cold water installations.

It is applicable to pipes with or without (a) barrier layer(s).

NOTE 2 In the case of plastics pipes provided with a thin barrier layer, e.g. to prevent or greatly diminish the diffusion of gases and the transmission of light into or through the pipe wall, the design stress requirements are totally met by the base polymer (PB).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1133-1, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 1: Standard method*

ISO 1167-1, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method*

ISO 1167-2, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 2: Preparation of pipe test pieces*

ISO 2505, *Thermoplastics pipes — Longitudinal reversion — Test method and parameters*

ISO 3126, *Plastics piping systems — Plastics components — Determination of dimensions*

ISO 7686, *Plastics pipes and fittings — Determination of opacity*

ISO 9080, *Plastics piping and ducting systems — Determination of the long-term hydrostatic strength of thermoplastics materials in pipe form by extrapolation*

ISO 15876-1:2003, *Plastics piping systems for hot and cold water installations — Polybutene (PB) — Part 1: General*

ISO 15876-3, *Plastics piping systems for hot and cold water installations — Polybutene (PB) — Part 3: Fittings*

ISO 15876-5, *Plastics piping systems for hot and cold water installations — Polybutene (PB) — Part 5: Fitness for purpose of the system*

3 Terms and definitions, symbols and abbreviated terms

For the purposes of this document, the terms and definitions, symbols and abbreviated terms given in ISO 15876-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Pipe material

4.1 General

The pipe material from which the pipe is made shall comply with ISO 15876-1.

After extrusion or moulding, PB undergoes a crystalline phase transition (usually called ageing) before it develops its final properties. The minimum required transition time depends on temperature and product characteristics. The same final material performance is obtained once completion of crystalline phase transition is achieved, irrespective of transition conditions. For quality control purposes, therefore, test specimens shall be taken immediately after processing and be conditioned in accordance with recommendations obtained from the compound supplier prior to testing.

The crystalline phase transition is dependent on time and temperature. For guidance a minimum time of five days for PB-H and one day for PB-R should be allowed at 23 °C, unless accelerated ageing is performed.

NOTE The crystalline phase transition can be considerably accelerated upon applying higher hydrostatic pressure of approx. 1 kbar to 2 kbar. Accelerated ageing at higher pressure can be accepted if test results can be proven reproducible and equal to those obtained at atmospheric pressure.

Because of the slow crystallization, transformation and shrinkage which takes places after PB-H and PB-R plastics are cooled from the melt, physical testing should be delayed after extrusion or moulding until this morphological transition is complete.

4.2 Evaluation of σ_{LPL} -curves

The pipe material shall be evaluated in accordance with ISO 9080 or equivalent where internal pressure tests are made in accordance with ISO 1167-1 and ISO 1167-2 to find the σ_{LPL} -values. The σ_{LPL} -value thus determined shall at least be as high as the corresponding values of the reference curves given in [Figure 1](#) or [Figure 2](#).

NOTE One equivalent way of evaluation is to calculate the σ_{LPL} -value for each temperature (e.g. 20 °C, 60 °C to 70 °C and 95 °C) individually.