Plastics - Recycled plastics - Characterisation of poly(vinyl chloride) (PVC) recyclates

Plastics - Recycled plastics - Characterisation of poly(vinyl chloride) (PVC) recyclates



EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 15346:2008 sisaldab Euroopa standardi EN 15346:2007 ingliskeelset teksti.

Standard on kinnitatud Eesti

Standardikeskuse 28.01.2008 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 01.12.2007.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 15346:2008 consists of the English text of the European standard EN 15346:2007.

This standard is ratified with the order of Estonian Centre for Standardisation dated 28.01.2008 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 01.12.2007.

The standard is available from Estonian standardisation organisation.

ICS 13.030.50, 83.080.20

Võtmesõnad:

Standardite reprodutseerimis- ja levitamisõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega: Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN 15346

December 2007

ICS 13.030.50: 83.080.20

English Version

Plastics - Recycled plastics - Characterisation of poly(vinyl chloride) (PVC) recyclates

Plastiques - Plastiques recyclés - Caractérisation des recyclats de poly(chlorure de vinyle) (PVC)

Kunststoffe - Kunststoff-Rezyklate - Charakterisierung von Polyvinylchlorid (PVC)-Rezyklaten

This European Standard was approved by CEN on 25 October 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

JOHN	ents.	Page
orewo	ord	3
	ction	
	Scope	5
2	Normative references	5
3	Terms, definitions and abbreviated terms	6
ļ	Characterisation of PVC recyclates	6
5	Quality Assurance	9
	A (informative) Typical compositions of PVC compounds	
Annex I	В	11
	C (normative) Impurities contained in recycled PVC compounds by dissolution in tetrahydrofuran	14
	D (normative) Size and distribution of particles contained in micronized recycled PV compounds by sieving	
Annex	E (normative) Size and distribution of recycled PVC crushes by sieving	19
nnex	F (normative) Fitness for processing of PVC recyclates by calendering	22
Annex	G (normative) Fitness for processing of PVC recyclates by extrusion	24
Bibliog	raphy	25
	Θ_{j}	
		1

Foreword

This document (EN 15346:2007) has been prepared by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2008, and conflicting national standards shall be withdrawn at the latest by June 2008.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This standard is one part of series of CEN publications on Plastics Recycling which is structured as follows:

- EN 15342 Plastics—Recycled Plastics—Characterization of polystyrene (PS) recyclates
- EN 15343 Plastics—Recycled Plastics—Plastics recycling traceability and assessment of conformity and recycled content
- EN 15344 Plastics—Recycled Plastics—Characterisation of Polyethylene (PE) recyclates
- EN 15345 Plastics—Recycled Plastics—Characterisation of Polypropylene (PP) recyclates
- EN 15346 Plastics—Recycled plastics—Characterisation of poly(vinyl chloride) (PVC) recyclates
- EN 15347 Plastics Recycled Plastics Characterisation of plastics wastes
- EN 15348 Plastics—Recycled plastics—Characterization of poly(ethylene terephthalate) (PET) recyclates
- CEN/TR 15353 Plastics Recycled plastics Guidelines for the development of standards for recycled plastics

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Introduction

Recycling of plastics waste is one type of material recovery process intended to save resources (virgin raw materials, water, and energy), while minimising harmful emissions into air, water and soil as well as any impacts on human health. The environmental impact of recycling has to be assessed over the whole life cycle of the recycling system (from the waste generation point to the disposal of final residues). To ensure that recycling constitutes the best environmental option for treating the available waste, some prerequisites should preferably be met:

- recycling scheme being contemplated should generate lower environmental impacts than alternative recovery options;
- existing or potential market outlets should be identified that will secure a sustainable industrial recycling operation;
- collection and sorting schemes should be properly designed to deliver recyclable plastics waste fractions fitting reasonably well with the available recycling technologies and with the (changing) needs of the identified market outlets, preferably at minimum costs to society.

This standard has been produced in accordance with the guidance produced by CEN on Environmental Aspects and in accordance with CEN/TR 15353, Plastics—Recycled Plastics—Guidelines for the development of standards relating to recycled plastics.

NOTE CEN/TR 15353 considers the general environmental aspects which are specific to the recycling process.

It is often impossible to trace back each individual product at the end user stage and to check whether the product has been used correctly through its life. Consequently products are out of industrial control for a period of time. It is possible that during this period contamination with other materials may occur that could affect the product's suitability for recycling into the intended application.

1 Scope

This European Standard defines a method of specifying delivery conditions for poly(vinyl chloride) (PVC) recyclates.

It gives the most important characteristics and associated test methods for assessing of PVC recyclates intended for use in the production of semi-finished/finished products.

It is intended to support parties involved in the use of recycled PVC to agree on specifications for specific and generic applications.

This Standard does not cover the characterisation of plastics wastes. See EN 15347.

This standard is applicable without prejudice to any existing legislation.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12099, Plastics piping systems — Polyethylene piping materials and components — Determination of volatile content

EN ISO 306, Plastics — Thermoplastics materials — Determination of Vicat softening temperature (VST) (ISO 306:2004)

EN ISO 472:2001, Plastics — Vocabulary (ISO 472:1999)

EN ISO 527-1, Plastics — Determination of tensile properties — Part 1: General principles (ISO 527-1:1993 including Corr 1:1994)

EN ISO 527-2, Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics (ISO 527-2:1993 including Corr 1:1994)

EN ISO 868, Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness) (ISO 868:2003)

EN ISO 1043-1:2001, Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics (ISO 1043-1:2001)

EN ISO 1183-1, Plastics - Methods for determining the density of non-cellular plastics - Part 1: Immersion method, liquid pyknometer method and titration method (ISO 1183-1:2004)

EN ISO 3451-5, Plastics — Determination of ash — Part 5: Poly(vinyl chloride) (ISO 3451-5:2002)

EN ISO 6186, Plastics — Determination of pourability (ISO 6186:1998)

ISO 182-1, Plastics — Determination of the tendency of compounds and products based on vinyl chloride homopolymers and copolymers to evolve hydrogen chloride and any other acidic products at elevated temperatures. — Part 1:Congo red method

ISO 182-2, Plastics — Determination of the tendency of compounds and products based on vinyl chloride homopolymers and copolymers to evolve hydrogen chloride and any other acidic products at elevated temperatures — Part 2: pH method

ISO 182-3, Plastics — Determination of the tendency of compounds and products based on vinyl chloride homopolymers and copolymers to evolve hydrogen chloride and any other acidic products at elevated temperatures — Part 3: Conductometric method

ISO 182-4 Plastics — Determination of the tendency of compounds and products based on vinyl chloride homopolymers and copolymers to evolve hydrogen chloride and any other acidic products at elevated temperatures — Part 4: Potentiometric method

ISO 565, Test sieves — Metal wire cloth, perforated metal plate and electroformed sheet — Nominal sizes of openings

ISO 1269, Plastics — Homopolymer and copolymer resins of vinyl chloride — Determination of volatile matter (including water)

CEN/TR 15353:2007, Plastics — Recycled plastics — Guidelines for the development of standards for recycled plastics

3 Terms, definitions and abbreviated terms

For the purposes of this European Standard, the terms and definitions given in EN ISO 472:2001 and CEN/TR 15353:2007 and the following apply.

3.1

sieve retention

percentage, in mass, of the recycled test sample retained on a sieve at the end of the test

3.2

container retention

percentage of recycled material retained in the container at the bottom of a stack of sieves, or under a simple sieve, at the end of the testing method compared to the mass of the sample tested

3.3

average particulate dimension

single value of size, expressed to the nearest 0, 001 mm, representing the dominant mass size for the whole test sample

3.4

tetrahydrofuran

THF

tetrahydrofuran

4 Characterisation of PVC recyclates

A single batch is the quantity of recyclate that has homogeneous characteristics within the specified tolerances.

The characteristics of PVC recyclates, given in Table 1, are divided into two types:

- Required characteristics needed to characterize PVC recyclates in general, and required for all recyclates.
- Optional characteristics needed to characterize PVC recyclates according to customer specifications and applications.

These characteristics shall be assessed by using the test methods given in Table 1.