

TERASEST KEEVITATUD SURVETORUD. TEHNILISED TARNETINGIMUSED. OSA 3: ELEKTERKEEVITATUD JA RÄBUSTIKAARKEEVITATUD, TOA- NING KÕRGENDATUD JA MADALAL TEMPERATUURIL KASUTAMISEKS SPETSIFITSEERITUD OMADUSTEGA LEGEERITUD PEENTERATERASEST TORUD

Welded steel tubes for pressure purposes - Technical delivery conditions - Part 3: Electric welded and submerged arc welded alloy fine grain steel tubes with specified room, elevated and low temperature properties

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 10217-3:2019 sisaldab Euroopa standardi EN 10217-3:2019 ingliskeelset teksti.	This Estonian standard EVS-EN 10217-3:2019 consists of the English text of the European standard EN 10217-3:2019.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 17.04.2019.	Date of Availability of the European standard is 17.04.2019.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 23.040.10, 77.140.75

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Welded steel tubes for pressure purposes - Technical delivery conditions - Part 3: Electric welded and submerged arc welded alloy fine grain steel tubes with specified room, elevated and low temperature properties

Tubes soudés en acier pour service sous pression - Conditions techniques de livraison - Partie 3: Tubes en acier en acier allié à grains fins, soudés électriquement et soudés à l'arc immergé avec caractéristiques spécifiées à basse température et température élevée

Geschweißte Stahlrohre für Druckbeanspruchungen - Technische Lieferbedingungen - Teil 3: Elektrisch geschweißte und unterpulvergeschweißte Rohre aus legierten Feinkornbaustählen mit festgelegten Eigenschaften bei Raum-, erhöhten und tiefen Temperaturen

This European Standard was approved by CEN on 25 February 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword.....	4
1 Scope	6
2 Normative references	6
3 Terms and definitions	8
4 Symbols	9
5 Classification and designation	9
5.1 Classification	9
5.2 Designation	9
6 Information to be supplied by the purchaser	9
6.1 Mandatory information	9
6.2 Options	10
6.3 Example of an order	11
7 Manufacturing process	11
7.1 Steelmaking process	11
7.2 Tube manufacture and delivery conditions	11
7.3 Non Destructive Testing Personnel Requirements	12
8 Requirements	13
8.1 General	13
8.2 Chemical composition	13
8.2.1 Cast analysis	13
8.2.2 Product analysis	15
8.3 Grain size	15
8.4 Mechanical properties	15
8.5 Appearance and internal soundness	18
8.5.1 Weld seam	18
8.5.2 Tube surface	18
8.5.3 Internal soundness	19
8.6 Straightness	19
8.7 Preparation of ends	19
8.8 Dimensions, masses and tolerances	20
8.8.1 Diameters and wall thickness	20
8.8.2 Mass	26
8.8.3 Lengths	26
8.8.4 Tolerances	26
9 Inspection	28
9.1 Type of inspection	28
9.2 Inspection documents	29
9.2.1 Types of inspection documents	29
9.2.2 Content of inspection documents	29
9.3 Summary of inspection and testing	29
10 Sampling	32
10.1 Frequency of tests	32
10.1.1 Test unit	32
10.1.2 Number of sample tubes per test unit	32
10.2 Preparation of samples and test pieces	32
10.2.1 Selection and preparation of samples for product analysis	32

10.2.2	Location, orientation and preparation of samples and test pieces for mechanical tests	32
11	Verification of test methods	34
11.1	Chemical analysis	34
11.2	Tensile test.....	34
11.2.1	Tensile test on the tube body	34
11.2.2	Transverse tensile test on the weld.....	35
11.3	Flattening test.....	35
11.4	Ring tensile test.....	35
11.5	Drift expanding test.....	35
11.6	Ring expanding test.....	36
11.7	Weld bend test.....	36
11.8	Impact test	36
11.9	Leak tightness test	37
11.9.1	Hydrostatic test.....	37
11.9.2	Electromagnetic test.....	37
11.10	Dimensional inspection	37
11.11	Visual examination	38
11.12	Non-Destructive Testing.....	38
11.12.1	Non-Destructive Testing of HFW tubes.....	38
11.12.2	Non-destructive testing of SAW tubes	38
11.13	Material identification.....	39
11.14	Retests, sorting and reprocessing.....	39
12	Marking.....	40
12.1	Marking to be applied.....	40
12.2	Additional marking.....	40
13	Protection.....	40
Annex A	(normative) Qualification of welding procedure for SAW tube production.....	41
A.1	General	41
A.2	Welding procedure specification	41
A.3	Preparation of sample tube and sample assessment.....	42
A.4	Inspection and testing of the weld	44
A.5	Weld test pieces	44
A.6	Test methods.....	44
A.7	Test acceptance levels	45
A.8	Range of use of qualified procedures.....	47
A.9	Qualification record	48
Annex B	(normative) Elevated temperature properties for steel grades P275NL1 and NL2	49
Annex C	(informative) Technical changes from the previous edition.....	50
C.1	Introduction	50
C.2	Technical changes	50
Annex ZA	(informative) Relationship between this European Standard and the Essential Requirements of 2014/68/EU	52
Bibliography	53

European foreword

This document (EN 10217-3:2019) has been prepared by Technical Committee CEN/TC 459 “ECISS - European Committee for Iron and Steel Standardization”¹, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2019, and conflicting national standards shall be withdrawn at the latest by October 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10217-3:2002.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive 2014/68/EU.

For relationship with EU Directive 2014/68/EU (formerly 97/23/EC), see informative Annex ZA, which is an integral part of this document.

This European Standard consists of the following parts, under the general title *Welded steel tubes for pressure purposes – Technical delivery conditions*:

Part 1: Electric welded and submerged arc welded non-alloy steel tubes with specified room temperature properties

Part 2: Electric welded non-alloy and alloy steel tubes with specified elevated temperature properties

Part 3: Electric welded and submerged arc welded alloy fine grain steel tubes with specified room, elevated and low temperature properties

Part 4: Electric welded non-alloy steel tubes with specified low temperature properties

Part 5: Submerged arc welded non-alloy and alloy steel tubes with specified elevated temperature properties

Part 6: Submerged arc welded non-alloy steel tubes with specified low temperature properties

Part 7: Stainless steel tubes

Another European Standard series covering tubes for pressure purposes is:

EN 10216, *Seamless steel tubes for pressure purposes*

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia,

¹ Through its subcommittee SC 10 “Steel tubes, and iron and steel fittings” (secretariat: UNI)

France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

This document is a preview generated by EVS

1 Scope

This document specifies the technical delivery conditions for two test categories of electric welded and submerged arc longitudinally (SAWL) or helically (SAWH) welded tubes of circular cross section, made from weldable fine grain steel.

NOTE 1 These tube grades are intended to support the essential requirements of EU Directive 2014/68/EU in respect of pressure equipment covered under all relevant Categories as set out in Article 13 of that Directive.

NOTE 2 Once this standard is published in the Official Journal of the European Union (OJEU), presumption of conformity to the Essential Safety Requirements (ESR) of Directive 2014/68/EU is limited to the technical data for the materials in this standard and does not presume adequacy of the material for a specific item of pressure equipment. Consequently, the assessment of the technical data stated in this material standard against the design requirements of a specific item of equipment to verify that the ESRs of the Pressure Equipment Directive are satisfied, needs to be done by the designer or manufacturer of the pressure equipment, taking also into account any subsequent processing procedures which may affect properties of the base materials.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10020, *Definition and classification of grades of steel*

EN 10021:2006, *General technical delivery conditions for steel products*

EN 10027-1, *Designation systems for steels — Part 1: Steel names*

EN 10027-2, *Designation systems for steels — Part 2: Numerical system*

EN 10168:2004, *Steel products — Inspection documents — List of information and description*

EN 10204:2004, *Metallic products — Types of inspection documents*

EN 10220, *Seamless and welded steel tubes — Dimensions and masses per unit length*

CEN/TR 10261, *Iron and steel — European standards for the determination of chemical composition*

EN 10266, *Steel tubes, fittings and structural hollow sections — Symbols and definitions of terms for use in product standards*

EN ISO 148-1:2016, *Metallic materials — Charpy pendulum impact test — Part 1: Test method (ISO 148-1:2016)*

EN ISO 377:2017, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing (ISO 377:2017)*

EN ISO 643:2012, *Steels — Micrographic determination of the apparent grain size (ISO 643:2012)*

EN ISO 2566-1:1999, *Steel — Conversion of elongation values — Part 1: Carbon and low alloy steels (ISO 2566-1:1984)*

EN ISO 4885, *Ferrous materials — Heat treatments — Vocabulary (ISO 4885)*

EN ISO 5173:2010, *Destructive tests on welds in metallic materials — Bend tests (ISO 5173:2009)*

EN ISO 6892-1:2016, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1:2016)*

EN ISO 6892-2:2018, *Metallic materials — Tensile testing — Part 2: Method of test at elevated temperature (ISO 6892-2:2018)*

EN ISO 8492:2013, *Metallic materials — Tube — Flattening test (ISO 8492:2013)*

EN ISO 8493:2004, *Metallic materials — Tube — Drift-expanding test (ISO 8493:1998)*

EN ISO 8495:2013, *Metallic materials — Tube — Ring-expanding test (ISO 8495:2013)*

EN ISO 8496:2013, *Metallic materials — Tube — Ring tensile test (ISO 8496:2013)*

EN ISO 10893-1:2011, *Non-destructive testing of steel tubes — Part 1: Automated electromagnetic testing of seamless and welded (except submerged arc-welded) steel tubes for the verification of hydraulic leaktightness (ISO 10893-1:2011)*

EN ISO 10893-2:2011, *Non-destructive testing of steel tubes — Part 2: Automated eddy current testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of imperfections (ISO 10893-2:2011)*

EN ISO 10893-3:2011, *Non-destructive testing of steel tubes — Part 3: Automated full peripheral flux leakage testing of seamless and welded (except submerged arc-welded) ferromagnetic steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-3:2011)*

EN ISO 10893-6:2011, *Non-destructive testing of steel tubes — Part 6: Radiographic testing of the weld seam of welded steel tubes for the detection of imperfections (ISO 10893-6:2011)*

EN ISO 10893-7:2011, *Non-destructive testing of steel tubes — Part 7: Digital radiographic testing of the weld seam of welded steel tubes for the detection of imperfections (ISO 10893-7:2011)*

EN ISO 10893-8:2011, *Non-destructive testing of steel tubes — Part 8: Automated ultrasonic testing of seamless and welded steel tubes for the detection of laminar imperfections (ISO 10893-8:2011)*

EN ISO 10893-9:2011, *Non-destructive testing of steel tubes — Part 9: Automated ultrasonic testing for the detection of laminar imperfections in strip/plate used for the manufacture of welded steel tubes (ISO 10893-9:2011)*

EN ISO 10893-10:2011, *Non-destructive testing of steel tubes — Part 10: Automated full peripheral ultrasonic testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-10:2011)*

EN ISO 10893-11:2011, *Non-destructive testing of steel tubes — Part 11: Automated ultrasonic testing of the weld seam of welded steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-11:2011)*

EN ISO 14174:2012, *Welding consumables — Fluxes for submerged arc welding and electroslag welding — Classification (ISO 14174:2012)*

EN ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition (ISO 14284)*

EN ISO 17639:2013, *Destructive tests on welds in metallic materials — Macroscopic and microscopic examination of welds (ISO 17639:2003)*

ISO 11484:2009, *Steel products — Employer's qualification system for non-destructive testing (NDT) personnel*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 10020, EN 10021, EN 10266, EN ISO 4885 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

test category

classification that indicates the extent and level of inspection and testing

3.2

employer

organisation for which a person works on a regular basis

Note 1 to entry: The employer may be either the tube manufacturer or a third party organization providing services, such as Non-Destructive Testing (NDT).

3.3

EW

electric welded tube

tubular product having one longitudinal seam weld produced by electric (resistance) welding where the strip edges to be welded are mechanically pressed together and the heat for the welding process is generated by the resistance to flow of low or high frequency electric current applied by either a conduction or induction process

3.4

HFW

high frequency welded tube

EW tube produced specifically using a welding current frequency equal to or greater than 100kHz

3.5

SAW

submerged-arc welded tube

tubular product having one or two longitudinal seams, or one helical seam, produced using the submerged-arc welding process

3.6

SAWH

submerged-arc helical welded tube

tubular product having one helical weld seam produced using the submerged-arc welding process

3.7

SAWL

submerged-arc longitudinal welded tube

tubular product having one or two longitudinal weld seams produced using the submerged-arc welding process