

**Primers for cold and hot applied joint sealants - Part 2:
Determination of resistance against alkali**

This document is a preview generated by EVS

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 15466-2:2010 sisaldab Euroopa standardi EN 15466-2:2009 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 30.04.2010 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 08.07.2009.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 15466-2:2010 consists of the English text of the European standard EN 15466-2:2009.

This standard is ratified with the order of Estonian Centre for Standardisation dated 30.04.2010 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 08.07.2009.

The standard is available from Estonian standardisation organisation.

ICS 93.080.20

Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

Right to reproduce and distribute Estonian Standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:
Aru str 10 Tallinn 10317 Estonia; www.evs.ee; Phone: +372 605 5050; E-mail: info@evs.ee

ICS 93.080.20

English Version

Primers for cold and hot applied joint sealants - Part 2: Determination of resistance against alkali

Primaires pour produits de scellement de joints appliqués à
froid et à chaud - Partie 2: Détermination de la résistance
aux produits alcalins

Voranstriche für kalt und heiß verarbeitbare Fugenmassen -
Teil 2: Bestimmung der Alkalibeständigkeit

This European Standard was approved by CEN on 6 June 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Principle.....	4
5 Apparatus	4
6 Procedure	5
6.1 Conditioning of primer and glass plates.....	5
6.2 Painting of the glass plates	5
6.3 Immersing of the glass plates	5
6.4 Tests on the solution in glass beaker with immersed glass plates	5
6.5 Tests on the immersed glass plates in wet condition	5
6.6 Tests on the immersed glass plates in dry condition.....	6
7 Expression of results	6
8 Test report	6
Bibliography	7

Foreword

This document (EN 15466-2:2009) has been prepared by Technical Committee CEN/TC 227 "Road Materials", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2010, and conflicting national standards shall be withdrawn at the latest by January 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This European Standard is one of a series of standards as listed below:

- EN 15466-1, *Primers for cold and hot applied joint sealants – Part 1: Determination of homogeneity*
- EN 15466-2, *Primers for cold and hot applied joint sealants – Part 2: Determination of resistance against alkali*
- EN 15466-3, *Primers for cold and hot applied joint sealants – Part 3: Determination of solids content and evaporation behaviour of volatiles.*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard describes a method for determining the resistance against alkali of primers for cold and hot applied joint sealants.

2 Normative references

The following referenced documents are indispensable for the application of this European Standard. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 14188-4:2009, *Joint fillers and sealants – Part 4: Specifications for primers to be used with joint sealants*

EN 15466-3, *Primers for cold and hot applied joint sealants – Part 3: Determination of solids content and evaporation behaviour of volatiles*

3 Terms and definitions

For the purposes of this European Standard, the terms and definitions given in EN 14188-4:2009 and the following apply.

3.1

standard atmosphere

standard atmosphere 23/50, class 2 (see EN ISO 291)

3.2

resistance against alkali

resistance against alkali of a primer defined by the behaviour of the primer painted on a glass surface to insolubility, no changes in hardness and no peelings during immersion in an alkali solution

4 Principle

Two glass plates, each with one side painted with the primer, are immersed, one in a glass beaker filled with water and the other one in a glass beaker filled with a solution of potassium hydroxide in water.

After conditioning in a test enclosure or conditioning room at standard atmosphere for 24 hours record any changes in the condition of the test liquids and the painted glass plates.

5 Apparatus

5.1 Clear glass beaker, diameter approximately 120 mm, height approximately 200 mm, with an upper flat rim, no spout, and with a glass cover.

5.2 Glass plates, without scratches, dimensions approximately 90 mm × 120 mm.

5.3 Preparation needle, (e. g. penetration needle).

5.4 Paint brush

5.5 Water, distilled or totally deionised.

5.6 Solution of potassium hydroxide in water, 0,5 % by mass/volume, freshly prepared.