
**Aluminium oxide primarily used
for the production of aluminium —
Method for the determination of
tapped and untapped density**

*Oxyde d'aluminium principalement utilisé pour la production
d'aluminium — Méthode de détermination de la masse volumique
tassée ou inexploitée*



This document is a preview generated by EMS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Principle.....	1
4 Apparatus.....	1
5 Sample handling and preparation.....	2
6 Procedure.....	2
6.1 Moisture determination.....	2
6.2 Untapped bulk density determination.....	2
6.3 Tapped bulk density determination.....	3
7 Calculation and reporting of results.....	3
8 Precision.....	3
9 Test report.....	4
Bibliography.....	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 226, *Materials for the production of primary aluminium*.

Introduction

This International Standard is based on the Australian Standard AS 2879.8.

This document is a preview generated by EVS

Aluminium oxide primarily used for the production of aluminium — Method for the determination of tapped and untapped density

1 Scope

This International Standard describes methods for the determination of tapped and untapped bulk density of smelter grade aluminium oxide primarily used for the production of aluminium.

Methods using the fall of sample into a receptacle have been found to be sensitive to flow rate variations, which are caused by physical properties of the aluminium oxide.

This International Standard minimizes flow rate variations.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 806, *Aluminium oxide primarily used for the production of aluminium — Determination of loss of mass at 300 °C and 1 000 °C*

AS 4538.2, *Guide to the sampling of alumina — Preparation of samples*

3 Principle

A test portion of the sample is allowed to fall in a narrow stream from a container onto a small metal impact plate from which the stream spreads and falls into a receiving vessel of known volume. The mass of test portion filling the vessel is determined and untapped bulk density is calculated on a moisture-free (300 °C) basis. The material in the receiver is then compacted by tapping the container while further sample is added so that tapped bulk density can be determined, again, on a moisture-free basis. The loss of mass at 300 °C is determined on a test portion of sample, this value is used in the calculation of tapped and untapped bulk density on a moisture-free basis.

4 Apparatus

4.1 Sample delivery apparatus, as shown in [Figure 1](#), constructed entirely of an abrasion resistant material, e.g. stainless steel, brass or aluminium. The orifice plate slides a 5 mm orifice beneath the delivery vessel to begin or terminate sample flow into the delivery tube.

4.2 Receiver, a cylindrical container of volume (200 ± 10) ml, having internal length-to-diameter ratio of approximately 6:1 with the exact volume V determined accurately by temperature corrected water mass and constructed of a material that precludes permanent deformation or damage on moderate tapping of the container. Metal or plastic is preferred.

NOTE An error of 0,5 ml in the volume determination will cause an error of 3,0 kg/m³ in the bulk density.

4.3 Laboratory top-pan balance, capable of weighing 500 g to nearest 0,1 g.

4.4 Metal straight edge.