

Hoonete tehnoseadmete ja tööstuspaigaldiste soojusisolatsioonitooted. Tööstuslikult valmistatud paisutatud perliidist (EP) ja paisutatud vermikuliidist (EV) tooted. Spetsifikatsioon

Thermal insulation products for building equipment and industrial installations - Factory made expanded perlite (EP) and exfoliated vermiculite (EV) products - Specification

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 15501:2013 sisaldab Euroopa standardi EN 15501:2013 ingliskeelset teksti.	This Estonian standard EVS-EN 15501:2013 consists of the English text of the European standard EN 15501:2013.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 24.04.2013.	Date of Availability of the European standard is 24.04.2013.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 91.100.60

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

English Version

Thermal insulation products for building equipment and industrial installations - Factory made expanded perlite (EP) and exfoliated vermiculite (EV) products - Specification

Produits isolants thermiques pour l'équipement du bâtiment et les installations industrielles - Produits manufacturés en perlite expansée (EP) et en vermiculite exfoliée (EV) - Spécification

Wärmedämmstoffe für die Haustechnik und für betriebstechnische Anlagen - Werkmäßig hergestellte Produkte aus Blähperlite (EP) und expandiertem Vermiculit (EV) - Spezifikation

This European Standard was approved by CEN on 10 February 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	5
1 Scope	7
2 Normative references	7
3 Terms, definitions, symbols, units and abbreviated terms	8
3.1 Terms and definitions	8
3.1.1 Terms and definitions as given in EN ISO 9229:2007	8
3.1.2 Additional terms and definitions	9
3.2 Symbols, units and abbreviated terms	10
3.2.1 Symbols and units	10
3.2.2 Abbreviated terms	11
4 Requirements	11
4.1 General	11
4.2 For all applications	12
4.2.1 Thermal conductivity	12
4.2.2 Dimensions and tolerances	12
4.2.3 Dimensional stability	13
4.2.4 Reaction to fire	13
4.2.5 Durability characteristics	13
4.3 For specific applications	14
4.3.1 General	14
4.3.2 Maximum service temperature	14
4.3.3 Minimum service temperature	14
4.3.4 Compressive stress or compressive strength	15
4.3.5 Trace quantities of water soluble ions and the pH value	15
4.3.6 Water vapour diffusion resistance	15
4.3.7 Short term water absorption by partial immersion	15
4.3.8 Dangerous substances	15
4.3.9 Continuous glowing combustion	16
5 Test methods	16
5.1 Sampling	16
5.2 Conditioning	16
5.3 Testing	16
5.3.1 General	16
5.3.2 Thermal conductivity	18
5.3.3 Maximum service temperature	19
5.3.4 Reaction to fire	19
6 Designation code	19
7 Evaluation of conformity	20
7.1 General	20
7.2 Initial Type Testing	20
7.3 Factory Production Control	20
8 Marking and labelling	20
Annex A (normative) Factory production control	21
Annex B (normative) Special conditions for the determination of organic content	24
B.1 Principle	24
B.2 Apparatus	24
B.3 Procedure	24

B.4	Calculation and expression of results	24
B.5	Test report.....	25
Annex C	(informative) Preparation of the test specimens to measure thermal conductivity	26
C.1	Preparation of the test specimens to measure thermal conductivity	26
C.2	Ageing.....	26
Annex D	(informative) Product specific details for mounting and fixing for reaction to fire testing	27
Annex E	(informative) Additional properties	31
E.1	General	31
E.2	Coefficient of thermal expansion.....	31
E.3	Apparent and true porosity	31
E.4	Air flow resistance.....	31
E.5	Creep in compression.....	31
E.6	Permeability to gases.....	31
E.7	Bending strength.....	31
E.8	Apparent density	31
Annex ZA	(informative) Clauses of this European Standard addressing the provisions of the EU Construction Products Directive	33
ZA.1	Scope and relevant characteristics	33
ZA.2	Procedures for attestation of conformity of factory made expanded perlite and exfoliated vermiculite products	35
ZA.2.1	Systems of attestation of conformity	35
ZA.2.2	EC certificate and declaration of conformity.....	37
ZA.3	CE Marking and labelling.....	38
	Bibliography.....	41

Figures

Figure ZA.1 — Example of CE marking information	40
---	----

Tables

Table 1 — Dimensional tolerances.....	12
Table 2 — Levels for maximum service temperatures.....	14
Table 3 — Levels for compressive stress at 10 % deformation or compressive strength	15
Table 4 — Test methods, test specimens and conditions	17
Table A.1 — Minimum product testing frequencies.....	21
Table A.2 — Minimum product testing frequencies for the reaction to fire characteristics	23
Table D.1 — Product parameters for EP / EV - flat products when tested as placed on the market or in standard test configuration of assemblies.....	27
Table D.2 — Installation Parameters for EP / EV - flat products as placed on the market.....	28
Table D.3 — Product parameters for EP / EV - pipe insulation products, as placed on the market.....	28
Table D.4 — Installation Parameters for EP / EV - pipe insulation products, as placed on the market.....	29
Table D.5 — Installation Parameters for EP / EV - flat products in standard test configuration of assemblies simulating end-use applications	29

Table E.1 — Test methods, test specimens, and conditions..... 32

Table ZA.1— Relevant clauses 34

Table ZA.2 — System(s) of attestation of conformity 35

Table ZA.3.1 — Assignment of evaluation of conformity tasks for products under system 1 for reaction to fire
and system 3 for other characteristics..... 36

Table ZA.3.2 — Assignment of evaluation of conformity tasks for products under system 3 or system 3
combined with system 4 for reaction to fire 37

Foreword

This document (EN 15501:2013) has been prepared by Technical Committee CEN/TC 88 “Thermal insulating materials and products”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2013, and conflicting national standards shall be withdrawn at the latest by October 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this document.

Locally responsible authorities and contracting entities, who are bound by EU Directives to specify their requirements using European harmonised product standards, are allowed to demand additional properties outside the provisions of this standard if this is technically necessary because of prevailing operational conditions of the building equipment or the industrial installation projected or because of safety regulations.

This European Standard contains six annexes:

- Annex A (normative), Factory production control
- Annex B (normative), Special conditions to be used for the determination of organic content
- Annex C (informative), Preparation of the test specimens to measure thermal conductivity
- Annex D (informative), Product specific details for mounting and fixing for reaction to fire testing

NOTE This annex will be transferred to Annex A of EN 15715 when this document is being revised.

- Annex E (informative), Additional properties
- Annex ZA (informative), Clauses of this European Standard addressing the provisions of the EU Construction Products Directive

This document includes a bibliography.

This European Standard is one of a series of standards for insulation products used in building equipment and industrial installations, but this standard can be used in other areas, where appropriate.

Other standards in the series include the following group of interrelated standards for the specifications of factory made thermal insulation products, all of which come within the scope of CEN/TC 88:

- EN 14303, *Thermal insulation products for building equipment and industrial installations — Factory made mineral wool (MW) products — Specification*
- EN 14304, *Thermal insulation products for building equipment and industrial installations — Factory made flexible elastomeric foam (FEF) products — Specification*

- EN 14305, *Thermal insulation products for building equipment and industrial installations — Factory made cellular glass (CG) products — Specification*
- EN 14306, *Thermal insulation products for building equipment and industrial installations — Factory made calcium silicate (CS) products — Specification*
- EN 14307, *Thermal insulation products for building equipment and industrial installations — Factory made extruded polystyrene foam (XPS) products — Specification*
- EN 14308, *Thermal insulation products for building equipment and industrial installations — Factory made rigid polyurethane foam (PUR) and polyisocyanurate foam (PIR) products — Specification*
- EN 14309, *Thermal insulation products for building equipment and industrial installations — Factory made products of expanded polystyrene (EPS) — Specification*
- EN 14313, *Thermal insulation products for building equipment and industrial installations — Factory made polyethylene foam (PEF) products — Specification*
- EN 14314, *Thermal insulation products for building equipment and industrial installations — Factory made phenolic foam (PF) products — Specification*

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies the requirements for factory made expanded perlite and exfoliated vermiculite products which are used for the thermal insulation of building equipment and industrial installations with an operating temperature in the range of approximately 0 °C to + 1 100 °C.

Expanded perlite and exfoliated vermiculite products can be used below 0 °C but special tests regarding the suitability of the product in the intended application are advised (e.g. liquefaction of oxygen). Manufacturer's advice should be heeded in all cases.

The products are manufactured in the form of boards, pipe sections, segments, prefabricated ware and special ware.

This European Standard describes product characteristics and includes procedures for testing, evaluation of conformity, marking and labelling.

Products covered by this European Standard are also used in prefabricated thermal insulation systems and composite panels; the structural performance of systems incorporating these products is not covered.

This European Standard does not specify the required level of a given property that is achieved by a product to demonstrate fitness for purpose in a particular application. The levels required for a given application can be found in regulations and invitations to tender.

Products with a declared thermal conductivity greater than 0,6 W/(mK) at 10 °C are not covered by this European Standard.

This European Standard does not cover products intended to be used for the insulation of the building structure.

The European Standard does not cover the following acoustical aspects: direct airborne sound insulation and impact transmission noise index.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 822, *Thermal insulating products for building applications — Determination of length and width*

EN 823, *Thermal insulating products for building applications — Determination of thickness*

EN 824, *Thermal insulating products for building applications — Determination of squareness*

EN 825, *Thermal insulating products for building applications — Determination of flatness*

EN 826, *Thermal insulating products for building applications — Determination of compression behaviour*

EN 1094-6, *Insulating refractory products — Part 6: Determination of permanent change in dimensions of shaped products on heating (ISO 2477)*

EN 1604, *Thermal insulating products for building applications — Determination of dimensional stability under specified temperature and humidity conditions*

EN 1609, *Thermal insulating products for building applications — Determination of short term water absorption by partial immersion*

EN 12086, *Thermal insulating products for building applications — Determination of water vapour transmission properties*

EN 12667, *Thermal performance of building materials and products — Determination of thermal resistance by means of guarded hot plate and heat flow meter methods — Products of high and medium thermal resistance*

EN 12939, *Thermal performance of building materials and products — Determination of thermal resistance by means of guarded hot plate and heat flow meter methods — Thick products of high and medium thermal resistance*

EN 13172:2012, *Thermal insulation products — Evaluation of conformity*

EN 13467, *Thermal insulating products for building equipment and industrial installations — Determination of dimensions, squareness and linearity of preformed pipe insulation*

EN 13468, *Thermal insulating products for building equipment and industrial installations — Determination of trace quantities of water soluble chloride, fluoride, silicate and sodium ions and pH*

EN 13469, *Thermal insulating products for building equipment and industrial installations — Determination of water vapour transmission properties of preformed pipe insulation*

EN 13472, *Thermal insulating products for building equipment and industrial installations — Determination of short term water absorption by partial immersion of preformed pipe insulation*

EN 13501-1:2007+A1:2009, *Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests*

EN 13820, *Thermal insulating materials for building applications — Determination of organic content*

EN 13823, *Reaction to fire tests for building products — Building products excluding floorings exposed to the thermal attack by a single burning item*

EN 15715, *Thermal insulation products — Instructions for mounting and fixing for reaction to fire testing — Factory made products*

EN ISO 8497, *Thermal insulation — Determination of steady-state thermal transmission properties of thermal insulation for circular pipes (ISO 8497)*

EN ISO 8894-1, *Refractory materials — Determination of thermal conductivity — Part 1: Hot-wire methods (cross-array and resistance thermometer) (ISO 8894-1)*

EN ISO 13787, *Thermal insulation products for building equipment and industrial installations — Determination of declared thermal conductivity (ISO 13787)*

3 Terms, definitions, symbols, units and abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1.1 Terms and definitions as given in EN ISO 9229:2007

3.1.1.1

expanded perlite

lightweight granular (insulation) material manufactured from naturally occurring volcanic rock expanded by heat to form a cellular structure

[SOURCE: EN ISO 9229:2007, 2.1.7, modified — removed alternative term "perlite"]