

**Plastics piping systems for the supply of gaseous fuels  
- Polyethylene (PE) - Part 2: Pipes**

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 1555-2:2010 sisaldab Euroopa standardi EN 1555-2:2010 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 31.10.2010 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 08.09.2010.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 1555-2:2010 consists of the English text of the European standard EN 1555-2:2010.

This standard is ratified with the order of Estonian Centre for Standardisation dated 31.10.2010 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 08.09.2010.

The standard is available from Estonian standardisation organisation.

ICS 23.040.20, 91.140.40

### Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:  
Aru 10 Tallinn 10317 Eesti; [www.evs.ee](http://www.evs.ee); Telefon: 605 5050; E-post: [info@evs.ee](mailto:info@evs.ee)

### Right to reproduce and distribute belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:  
Aru str 10 Tallinn 10317 Estonia; [www.evs.ee](http://www.evs.ee); Phone: 605 5050; E-mail: [info@evs.ee](mailto:info@evs.ee)

English Version

**Plastics piping systems for the supply of gaseous fuels -  
Polyethylene (PE) - Part 2: Pipes**

Systèmes de canalisations en plastique pour la distribution  
de combustibles gazeux - Polyéthylène (PE) - Partie 2 :  
Tubes

Kunststoff-Rohrleitungssysteme für die Gasversorgung  
Polyethylen (PE) - Teil 2: Rohre

This European Standard was approved by CEN on 30 July 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: Avenue Marnix 17, B-1000 Brussels**

# Contents

Page

Foreword.....	4
Introduction .....	6
1 Scope .....	7
2 Normative references .....	7
3 Terms and definitions, symbols and abbreviations .....	8
4 Material .....	8
4.1 Compound for pipes .....	8
4.2 Compound for identification stripes .....	9
4.3 External reprocessible and recyclable material .....	9
5 General characteristics .....	9
5.1 Appearance .....	9
5.2 Colour .....	9
6 Geometrical characteristics .....	9
6.1 Measurement of dimensions .....	9
6.2 Mean outside diameters, out-of-roundness (ovality) and tolerances .....	9
6.3 Wall thicknesses and related tolerances .....	10
6.3.1 Minimum wall thicknesses .....	10
6.3.2 Tolerance on the wall thicknesses .....	11
6.4 Circumferential reversion of pipes with a $d_n$ equal to or greater than 250 mm .....	12
6.5 Coiled pipe .....	13
6.6 Lengths .....	13
7 Mechanical characteristics .....	13
7.1 Conditioning .....	13
7.2 Requirements .....	13
7.3 Retest in case of failure at 80 °C .....	15
8 Physical characteristics .....	15
8.1 Conditioning .....	15
8.2 Requirements .....	15
9 Performance requirements .....	16
10 Marking .....	16
10.1 General .....	16
10.2 Minimum required marking .....	17
10.3 Additional marking .....	17
Annex A (normative) Pipes with co-extruded layers .....	18
A.1 General .....	18
A.2 Geometrical characteristics .....	18
A.3 Mechanical characteristics .....	18
A.4 Physical characteristics .....	18
A.5 Marking .....	18
A.6 Delamination .....	18

<b>A.7</b>	<b>Integrity of the structure .....</b>	<b>19</b>
<b>Annex B</b>	<b>(normative) Pipes with peelable layer .....</b>	<b>20</b>
<b>B.1</b>	<b>General .....</b>	<b>20</b>
<b>B.2</b>	<b>Geometrical characteristics .....</b>	<b>20</b>
<b>B.3</b>	<b>Mechanical characteristics .....</b>	<b>20</b>
<b>B.4</b>	<b>Physical characteristics .....</b>	<b>20</b>
<b>B.5</b>	<b>Coating adhesion .....</b>	<b>20</b>
<b>B.6</b>	<b>Marking .....</b>	<b>21</b>
<b>Annex C</b>	<b>(normative) Squeeze-off technique .....</b>	<b>22</b>
<b>C.1</b>	<b>General Squeeze-off technique .....</b>	<b>22</b>
<b>C.2</b>	<b>Definitions .....</b>	<b>22</b>
<b>C.3</b>	<b>Test method .....</b>	<b>22</b>
	<b>Bibliography .....</b>	<b>23</b>

## Foreword

This document (EN 1555-2:2010) has been prepared by Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems", the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2011, and conflicting national standards shall be withdrawn at the latest by March 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1555-2:2002.

It has been prepared in liaison with Technical Committee CEN/TC 234 "Gas infrastructure".

System Standards are based on the results of the work being undertaken in ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids", which is a Technical Committee of the International Organization for Standardization (ISO).

They are supported by separate standards on test methods to which references are made throughout the System Standard.

The System Standards are consistent with general standards on functional requirements and on recommended practice for installation.

EN 1555 consists of the following parts:

- EN 1555-1, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 1: General*;
- EN 1555-2, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 2: Pipes* (this standard);
- EN 1555-3, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 3: Fittings*;
- prEN 1555-4, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 4: Valves*;
- EN 1555-5, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 5: Fitness for purpose of the system*;
- CEN/TS 1555-7, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 7: Guidance for assessment of conformity*.

NOTE EN 12007-2:2000 [1] prepared by CEN/TC 234 "Gas infrastructure" deals with the recommended practice for installation of plastics pipes system in accordance with EN 1555 (all parts).

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

This document is a preview generated by EVS

## Introduction

The System Standard, of which this is Part 2, specifies the requirements for a piping system and its components made from polyethylene (PE) and which is intended to be used for the supply of gaseous fuels.

Requirements and test methods for material and components, other than pipes, are specified in EN 1555-1, EN 1555-3 [7] and prEN 1555-4 [8].

Characteristics for fitness for purpose are covered in EN 1555-5. CEN/TS 1555-7 [2] gives guidance for assessment of conformity. Recommended practice for installation is given in EN 12007-2:2000 [1] prepared by CEN/TC 234.

This part of EN 1555 covers the characteristics of pipes.



## 1 Scope

This part of EN 1555 specifies the characteristics of pipes made from polyethylene (PE) for piping systems in the field of the supply of gaseous fuels.

It also specifies the test parameters for the test methods referred to in this standard.

In conjunction with Parts 1 and 3 to 5 of EN 1555, it is applicable to PE pipes, their joints and to joints with components of PE and other materials intended to be used under the following conditions:

- a) a maximum operating pressure, MOP, up to and including 10 bar <sup>1)</sup>;
- b) an operating temperature of 20 °C as reference temperature.

NOTE 1 For other operating temperatures, derating coefficients should be used, see EN 1555-5.

EN 1555 covers a range of maximum operating pressures and gives requirements concerning colours and additives.

It covers three types of pipe:

- PE pipes (outside diameter  $d_n$ ) including any identification stripes;
- PE pipes with co-extruded layers on either or both the outside and/or inside of the pipe (total outside diameter  $d_n$ ) as specified in Annex A, where all layers have the same MRS rating;
- PE pipes (outside diameter  $d_n$ ) with a peelable, contiguous thermoplastics additional layer on the outside of the pipe ('coated pipe') as specified in Annex B.

NOTE 2 It is the responsibility of the purchaser or specifier to make the appropriate selections from these aspects, taking into account their particular requirements and any relevant national regulations and installation practices or codes.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1555-1:2010, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 1: General*

EN 1555-5, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 5: Fitness for purpose of the system*

EN 12106, *Plastics piping systems — Polyethylene (PE) pipes — Test method for the resistance to internal pressure after application of squeeze-off*

EN ISO 1133:2005, *Plastics — Determination of the melt mass-flow rate (MFR) and the melt volume-flow rate (MVR) of thermoplastics (ISO 1133:2005)*

EN ISO 1167-1:2006, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method (ISO 1167-1:2006)*

---

1) 1 bar = 0,1 MPa.

EN ISO 1167-2, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 2: Preparation of pipe test pieces (ISO 1167-2:2006)*

EN ISO 2505, *Thermoplastics pipes — Longitudinal reversion — Test method and parameters (ISO 2505:2005)*

EN ISO 3126, *Plastics piping systems — Plastics components — Determination of dimensions (ISO 3126:2005)*

EN ISO 6259-1, *Thermoplastics pipes — Determination of tensile properties — Part 1: General test method (ISO 6259-1:1997)*

EN ISO 9969, *Thermoplastics pipes — Determination of ring stiffness (ISO 9969:2007)*

EN ISO 13477, *Thermoplastics pipes for the conveyance of fluids — Determination of resistance to rapid crack propagation (RCP) — Small-scale steady-state test (S4 test) (ISO 13477:2008)*

EN ISO 13478, *Thermoplastics pipes for the conveyance of fluids — Determination of resistance to rapid crack propagation (RCP) — Full scale test (FST) (ISO 13478:2007)*

EN ISO 13479:2009, *Polyolefin pipes for the conveyance of fluids — Determination of resistance to crack propagation — Test method for slow crack growth on notched pipes (ISO 13479:2009)*

EN ISO 13968, *Plastics piping and ducting systems — Thermoplastics pipes — Determination of ring flexibility (ISO 13968:2008)*

ISO 4065:1996, *Thermoplastics pipes — Universal wall thickness table*

ISO 6259-3, *Thermoplastics pipes — Determination of tensile properties — Part 3: Polyolefin pipes*

ISO 11357-6, *Plastics — Differential scanning calorimetry (DSC) — Part 6: Determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT)*

ISO 13480, *Polyethylene pipes — Resistance to slow crack growth — Cone test method*

### **3 Terms and definitions, symbols and abbreviations**

For the purposes of this document the terms and definitions, symbols and abbreviations given in EN 1555-1:2010 apply.

## **4 Material**

### **4.1 Compound for pipes**

The pipes shall be made from virgin material or own reprocessable material from the same PE compound or a mixture of both materials. Reprocessable material from coextruded pipes or from pipes reprocessed with the peelable layer attached shall not be used. Own reprocessed material from the base pipe of peelable layer pipes can be used.

The compound(s) from which the pipes are made shall conform to EN 1555-1.