

**Influence of metallic materials on water
intended for human consumption - Dynamic
rig test for assessment of metal release - Part
1: Design and operation**

Influence of metallic materials on water intended
for human consumption - Dynamic rig test for
assessment of metal release - Part 1: Design
and operation

EESTI STANDARDI EESSÕNA**NATIONAL FOREWORD**

<p>Käesolev Eesti standard EVS-EN 15664-1:2008 sisaldab Euroopa standardi EN 15664-1:2008 ingliskeelset teksti.</p>	<p>This Estonian standard EVS-EN 15664-1:2008 consists of the English text of the European standard EN 15664-1:2008.</p>
<p>Standard on kinnitatud Eesti Standardikeskuse 25.03.2008 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.</p>	<p>This standard is ratified with the order of Estonian Centre for Standardisation dated 25.03.2008 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.</p>
<p>Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 30.01.2008.</p>	<p>Date of Availability of the European standard text 30.01.2008.</p>
<p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>The standard is available from Estonian standardisation organisation.</p>

ICS 67.250, 77.060

Võtmesõnad:

Standardite reprodutseerimis- ja levitamisoigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

ICS 13.060.20; 67.250

English Version

**Influence of metallic materials on water intended for human
consumption - Dynamic rig test for assessment of metal release
- Part 1: Design and operation**

Influence des matériaux métalliques sur l'eau destinée à la
consommation humaine - Banc d'essai dynamique pour
l'évaluation de l'émission de métaux - Partie 1: Conception
et fonctionnement

Einfluss metallischer Werkstoffe auf Wasser für den
menschlichen Gebrauch - Dynamischer Prüfstandversuch
für die Beurteilung der Freisetzung von Metallen - Teil 1:
Auslegung und Betrieb

This European Standard was approved by CEN on 28 October 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	7
4 Principle	9
5 Test rig	9
5.1 General.....	9
5.2 Test rig arrangement	9
5.3 Control line	10
5.4 Test lines	10
5.4.1 General.....	10
5.4.2 Materials in the form of pipes.....	10
5.4.3 Materials in the form of test pieces.....	10
5.5 Reference lines for comparative testing	10
6 Operating conditions	10
6.1 General.....	10
6.2 Conditioning.....	11
6.3 Fractional Sampling	11
6.3.1 General.....	11
6.3.2 Calculation and expression of results for fractional sampling.....	11
6.3.3 Requirements for the hydraulic function of the test rig	13
6.3.4 Determination of sampling volumes.....	13
6.4 Normal operation of the test rig	14
7 Test water	14
7.1 Composition	14
7.2 Check of test water	14
8 Sampling	15
8.1 General.....	15
8.2 Test water sampling	15
8.3 Sampling to determine metal release	15
8.4 Sampling volumes	16
8.4.1 General.....	16
8.4.2 Test lines with test pieces	16
8.4.3 Test pipes	16
9 Analysis	16
10 Expression of results	16
10.1 Metal concentrations after fixed stagnation time.....	16
10.2 Equivalent pipe concentration	17
10.3 Mean concentration after a given operating time.....	17
10.4 Presentation of the test results	17
11 Test report	18
Annex A (normative).....	19
Test rig components and assembly.....	19
A.1 Test rig	19

A.2	Test piece	21
A.3	Connecting piece.....	21
Annex B (normative)		23
Test rig flow regime.....		23
B.1	Test rig flow regime and sampling plan (24 h cycle).....	23
B.2	Test rig flow regime and sampling plan for 16 h stagnation time.....	25
Annex C (normative)		26
Test water monitoring and analysis		26
C.1	Data on test water composition	26
Annex D (informative)		28
Example of graphs for expression of results		28
Bibliography.....		31

Foreword

This document (EN 15664-1:2008) has been prepared by Technical Committee CEN/TC 164 "Water Supply", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2008, and conflicting national standards shall be withdrawn at the latest by July 2008.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This European Standard is one of a series of test methods that supports associated product standards.

The standard has been prepared under the mandate given to CEN by the Commission of the European Communities and the European Free Trade Area and supports essential requirements of the relevant EC-Directives.

With respect to potential adverse effects on the quality of water intended for human consumption caused by metallic materials, attention is drawn to the fact that the relevant national regulations remain in force until the adoption of verifiable European acceptance criteria. Water intended for human consumption is hereafter referred to as "drinking water" and means the same as the definition given at Article 2(1) of the Council Directive 98/83/EC on the quality of water intended for human consumption.

This European Standard has been drafted in accordance with the CEN Internal Regulations, Part 3.

This European Standard is Part 1 of a series dealing with the test method to determine the release of metals from metallic products into drinking water comprising:

- Part 1: Design and operation
- Part 2: Test waters
- Part 3: Guidance on interpretation of results.

Part 1 describes a test method to produce contact waters for the assessment of metal release from metallic materials.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Introduction

The main application of metallic materials in water supply is within the domestic installation. The test method given in this standard is designed to provide information on metal release over time from metallic materials into drinking water.

The test is based on a programme of alternating periods of once-through flow and stagnation in a rig, simulating the conditions in a domestic distribution system.

The test conditions are more relevant than conditions of continuous through-flow or sit and soak tests and are applicable to all metallic materials in distribution systems.

Internal corrosion of metallic products in water conveying systems generally leads to the build-up of layers, which might or might not be protective. The factors influencing corrosion are described in EN 12502-1. Type and rate of the production of corrosion products and the rate of metal release can depend on:

- characteristics of the metallic material;
- characteristics of the water;
- design and construction;
- pressure testing and commissioning;
- operating conditions and duration of operation.

Corrosion product layers begin to form as soon as a metallic material comes into contact with water. Their properties depend on the factors noted above and for a given water/material combination especially on the operating conditions. It is not possible to reproduce the conditions of an actual installation in tests by constant once-through flow or circulation of water. The flow regime (3.16) used in this test simulates the operating conditions in domestic drinking water installations where stagnation times of water considerably exceed the times of through-flow.

An assessment by testing is possible only if the influence of the flow regime (3.16) and the operation period (3.19) is taken into consideration. A compilation of data is needed, which has been determined under defined conditions over a prolonged period of time. In most cases, metal release decreases with operation time. For some alloying elements and impurities, however, an increase in their release can be observed.

1 Scope

This European Standard specifies a procedure to determine the release of metals from metallic materials used in construction products intended to come into contact with drinking water¹.

The test can be used for three purposes:

- a) Assess a material as a reference material for a category of materials using the results of several investigations in different waters covering a broad range of water compositions.
- b) Assess a material for approval by way of comparative testing.
- c) Obtain data on the interaction of local water with a material.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1484, *Water analysis — Guidelines for the determination of total organic carbon (TOC) and dissolved organic carbon (DOC)*

EN 10088-1, *Stainless steels — Part 1: List of stainless steels*

EN 12502-1:2004, *Protection of metallic materials against corrosion — Guidance on the assessment of corrosion likelihood in water distribution and storage systems — Part 1: General*

EN 25813, *Water quality — Determination of dissolved oxygen — Iodometric method (ISO 5813:1983)*

EN 25814, *Water quality — Determination of dissolved oxygen — Electrotechnical probe method (ISO 5814:1990)*

EN 27888, *Water quality — Determination of electrical conductivity (ISO 7888:1985)*

EN ISO 6878, *Water quality — Determination of phosphorus — Ammonium molybdate spectrometric method (ISO 6878:2004)*

EN ISO 8044:1999, *Corrosion of metals and alloys — Basic terms and definitions (ISO 8044:1999)*

EN ISO 9963-1, *Water quality — Determination of alkalinity — Part 1: Determination of total and composite alkalinity (ISO 9963-1:1994)*

EN ISO 10304-1, *Water quality — Determination of dissolved fluoride, chloride, nitrite, orthophosphate, bromide, nitrate and sulphate ions, using liquid chromatography of ions — Part 1: Method for water with low contamination (ISO 10304-1:1992)*

EN ISO 11885, *Water quality — Determination of 33 elements by inductively coupled plasma atomic emission spectroscopy (ISO 11885:1996)*

¹ Water intended for human consumption is referred to as "drinking water" and means the same as the definition given at Article 2(1) of the Council Directive 98/83/EC on the quality of water intended for human consumption. Luxembourg, Office for Official Publications of the European Communities. 3 November 1998.

EN ISO 14911, *Water quality — Determination of dissolved Li^+ , Na^+ , NH_4^+ , K^+ , Mn^{2+} , Ca^{2+} , Mg^{2+} , Sr^{2+} and Ba^{2+} using ion chromatography — Method for water and waste water (ISO 14911:1998)*

EN ISO 15586 *Water quality — Determination of trace elements using atomic absorption spectrometry with graphite furnace (ISO 15586:2003)*

EN ISO 17294-2, *Water quality — Application of inductively coupled plasma mass spectrometry (ICP-MS) — Part 2: Determination of 62 elements (ISO 17294-2:2003)*

ISO 6058, *Water quality — Determination of calcium content — EDTA titrimetric method*

ISO 6059, *Water quality — Determination of the sum of calcium and magnesium — EDTA titrimetric method*

ISO 9297, *Water quality — Determination of chloride — Silver nitrate titration with chromate indicator (Mohr's method)*

ISO 9964-3, *Water quality — Determination of sodium and potassium — Part 3: Determination of sodium and potassium by flame emission spectrometry*

ISO 10523, *Water quality — Determination of pH*

3 Terms and definitions

For the purposes of this European standard the terms and definitions given in EN ISO 8044:1999, EN 12502-1:2004 and the following apply.

3.1

test rig

assembly of test lines, control lines and where necessary reference lines together with test water inlet and discharge arrangements, see Annex A, Figure A.1

3.2

line

continuous part between a check valve and the corresponding flow regulator

3.3

control line

line containing a single length of pipe made of an inert material for the purposes of the test

3.4

test line

line containing test pieces or a test pipe

3.5

reference line

line containing test pieces each made of the same reference material or line containing a single length of pipe made of a reference material

3.6

dummy lines

pipes made of an inert material for the purposes of the test used for the conditioning run of a newly built test rig

3.7

test pipe

specimen that is representative of a construction product in the form of a pipe for use with drinking water in terms of material composition and surface characteristics