

**Bio-based products - Bio-based carbon content -
Determination of the bio-based carbon content using
the radiocarbon method**

This document is a preview generated by EVS

EESTI STANDARDI EESSÕNA**NATIONAL FOREWORD**

See Eesti standard EVS-EN 16640:2017 sisaldab Euroopa standardi EN 16640:2017 ja selle paranduse AC:2017 ingliskeelset teksti.	This Estonian standard EVS-EN 16640:2017 consists of the English text of the European standard EN 16640:2017 and its corrigendum AC:2017.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 22.02.2017.	Date of Availability of the European standard is 22.02.2017.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 13.020.55, 71.040.40, 83.040.01

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN 16640

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2017

ICS 13.020.55; 71.040.40; 83.040.01

Supersedes CEN/TS 16640:2014

English Version

Bio-based products - Bio-based carbon content - Determination of the bio-based carbon content using the radiocarbon method

Produits biosourcés - Teneur en carbone biosourcé -
Détermination de la teneur en carbone biosourcé par la
méthode au radiocarbone

Biobasierte Produkte - Gehalt an biobasiertem
Kohlenstoff - Bestimmung des Gehalts an biobasiertem
Kohlenstoff mittels Radiokarbonmethode

This European Standard was approved by CEN on 4 December 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

This document consolidates EN 16640:2017 and the corrigendum EN 16640:2017/AC:2017



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	4
Introduction	5
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	6
4 Symbols and abbreviations	7
5 Principle	8
Table 1 — Advantages and disadvantages of the methods	8
6 Determination of the ^{14}C content.....	9
6.1 General.....	9
6.2 Principle	9
6.3 Sampling.....	9
6.4 Procedure for the conversion of the carbon present in the sample to a suitable sample for ^{14}C determination	9
6.5 Measurements.....	9
7 Calculation of the bio-based carbon content.....	10
7.1 General.....	10
7.2 Reference value for 100 % bio-based carbon	10
Table 2 — Typical values for biomass fractions.....	11
7.3 Calculation method.....	11
7.3.1 Calculation of the bio-based carbon content by dry mass x_B	11
7.3.2 Calculation of the bio-based carbon content x^{TC}_B as a fraction of TC.....	12
7.3.3 Examples	12
7.3.4 Examples of calculations x^{TC}_B	13
8 Performance characteristics.....	13
9 Test report.....	13
Annex A (informative) Procedures for sampling of products.....	15
A.1 General.....	15
Table A.1. — Sampling procedures	15
Annex B (normative) Procedure for the conversion of the carbon present in the sample to a suitable sample for ^{14}C determination	16
B.1 General.....	16
B.2 Sample preparation.....	16
Table B.1— Sample preparations.....	16
B.3 Preparation for ^{14}C measurement.....	16
B.3.1 General.....	16
B.3.2 Reagents and materials.....	17
B.4 Combustion of the sample.....	17

B.4.1	Combustion of the sample in a calorimetric bomb	17
B.4.2	Combustion of the sample in a tube furnace or a combustion apparatus	18
B.4.3	Direct LSC measurement on the product	19
B.5	Standardization of LSC and BI measurement results	19
B.6	Standardization of AMS measurement results	20
B.7	Symbols and abbreviations	20
	Annex C (normative) Method A - Liquid scintillation-counter method (LSC)	21
C.1	General	21
C.2	Principle	21
C.3	Reagents and materials	21
C.4	Apparatus	21
C.5	Procedure	22
C.5.1	General	22
C.5.2	Benzene conversion	22
C.5.3	Direct absorption of the CO₂ in a carbamate solution	22
C.5.4	Measurement	22
C.5.5	Blank correction	23
C.6	Calculation of the results	23
	Annex D (informative) Method C - Beta-ionization (BI)	24
D.1	General	24
D.2	Principle	24
D.3	Reagents and materials	24
D.4	Apparatus	25
D.5	AC Procedure AC	25
D.6	AC Calculation of the results AC	26
	Annex E (normative) Method B - Accelerator Mass Spectrometry (AMS)	27
E.1	General	27
E.2	AC Principle AC	27
E.3	AC Reagents and materials AC	27
E.4	AC Apparatus AC	27
E.5	AC Procedure AC	28
E.6	AC Calculation of the results AC	29
	Annex F (informative) Performance characteristics	30
	Table F.1 — description of sample types	30
	Table F.2 — Performance data for 14C methods	31
	Bibliography	32

European foreword

This document (EN 16640:2017) has been prepared by Technical Committee CEN/TC 411 “Bio-based products”, the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2017, and conflicting national standards shall be withdrawn at the latest by August 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes CEN/TS 16640:2014.

This document has been prepared under Mandate M/492 “Mandate addressed to CEN, CENELEC and ETSI for the development of horizontal European Standards and other standardization deliverables for bio-based products”.

This document includes the corrigendum EN 16640:2017/AC:2017, which corrects Annexes D and E.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

Bio-based products from forestry and agriculture have a long history of application, such as paper, board and various chemicals and materials. The last decades have seen the emergence of new bio-based products in the market. Some of the reasons for the increased interest lie in the bio-based products' benefits in relation to the depletion of fossil resources and climate change. Bio-based products may also provide additional product functionalities. This has triggered a wave of innovation with the development of knowledge and technologies allowing new transformation processes and product development.

Acknowledging the need for common standards for bio-based products, the European Commission issued Mandate M/492¹⁾, resulting in a series of standards developed by CEN/TC 411, with a focus on bio-based products other than food, feed and biomass for energy applications.

The standards of CEN/TC 411 "Bio-based products" provide a common basis on the following aspects:

- Common terminology;
- Bio-based content determination;
- Life Cycle Assessment (LCA);
- Sustainability aspects;
- Declaration tools.

It is important to understand what the term bio-based product covers and how it is being used. The term 'bio-based' means 'derived from biomass'. Bio-based products (bottles, insulation materials, wood and wood products, paper solvents, chemical intermediates, composite materials, etc.) are products which are wholly or partly derived from biomass. It is essential to characterize the amount of biomass contained in the product by, for instance, its bio-based content or bio-based carbon content.

The bio-based content of a product does not provide information on its environmental impact or sustainability, which may be assessed through LCA and sustainability criteria. In addition, transparent and unambiguous communication within bio-based value chains is facilitated by a harmonized framework for certification and declaration.

This European Standard has been developed with the aim to specify the method for the determination of bio-based carbon content in bio-based products using the ¹⁴C method. This method using the ¹⁴C method is based on the analytical test methods used for the determination of the age of objects containing carbon.

This European Standard provides the reference test methods for laboratories, producers, suppliers and purchasers of bio-based product materials and products. It may be also useful for authorities and inspection organizations.

Part of the research leading to this document has been performed under the European Union Seventh Framework Programme (see <http://www.biobasedeconomy.eu/research/kbbpps/>). This document is based on EN 15440 [1] prepared by CEN/TC 343, "Solid recovered fuels", EN ISO 13833 [2], prepared by ISO/TC 146 "Air quality" and CEN/TC 264 "Air quality", and CEN/TS 16137 [3], prepared by CEN/TC 249, "Plastics".

The analytical test methods specified in this European Standard are compatible with those described in ASTM D 6866-12 [4].

¹⁾ A mandate is a standardization task embedded in European trade laws. Mandate M/492 is addressed to the European Standardization bodies, CEN, CENELEC and ETSI, for the development of horizontal European Standards for bio-based products.

1 Scope

This European Standard specifies a method for the determination of the bio-based carbon content in products, based on the ^{14}C content measurement.

This European Standard also specifies two test methods to be used for the determination of the ^{14}C content from which the bio-based carbon content is calculated:

- Method A: Liquid scintillation-counter method (LSC) ;
- Method B: Accelerator mass spectrometry (AMS).

A third method, Method C: Beta ionization (BI) can also be used for the determination of the ^{14}C content and is described in Annex D (informative)

The bio-based carbon content is expressed by a fraction of sample mass or as a fraction of the total carbon content. This calculation method is applicable to any product containing carbon, including bio composites.

NOTE This European Standard does not provide the methodology for the calculation of the biomass content of a sample see prEN 16785-1 [5] and prEN 16785-2 [6].

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 15400, *Solid recovered fuels - Determination of calorific value*

EN ISO 1716, *Reaction to fire tests for products - Determination of the gross heat of combustion (calorific value) (ISO 1716)*

ISO 1928, *Solid mineral fuels — Determination of gross calorific value by the bomb calorimetric method and calculation of net calorific value*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

organic material

material containing carbon-based compound in which the element carbon is attached to other carbon atoms, hydrogen, oxygen, or other elements in a chain, ring, or three-dimensional structure

3.2

isotope abundance

fraction of atoms of a particular isotope of an element

3.3

percentage modern carbon

pMC

normalized and standardized value for the amount of the ^{14}C isotope in a sample, calculated relative to the standardized and normalized ^{14}C isotope amount of oxalic acid standard reference material, NIST SRM 4990b or NIST SRM 4990c or Sucrose (NIST SRM 8542)

Note 1 to entry: In 2016, the value of 100 % bio-based carbon was set at $101,5 \pm 0,5$ pMC.