

This document is a preview generated by EVS

**Textiles - Test methods for phthalates**

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 15777:2009 sisaldab Euroopa standardi EN 15777:2009 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 30.10.2009 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 26.08.2009.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 15777:2009 consists of the English text of the European standard EN 15777:2009.

This standard is ratified with the order of Estonian Centre for Standardisation dated 30.10.2009 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 26.08.2009.

The standard is available from Estonian standardisation organisation.

ICS 59.080.01

### Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:  
Aru 10 Tallinn 10317 Eesti; [www.evs.ee](http://www.evs.ee); Telefon: 605 5050; E-post: [info@evs.ee](mailto:info@evs.ee)

### Right to reproduce and distribute Estonian Standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:  
Aru str 10 Tallinn 10317 Estonia; [www.evs.ee](http://www.evs.ee); Phone: +372 605 5050; E-mail: [info@evs.ee](mailto:info@evs.ee)

ICS 59.080.01

English Version

## Textiles - Test method for phthalates

Textiles - Méthodes d'essai des phtalates

Textilien - Prüfverfahren für Phthalate

This European Standard was approved by CEN on 24 July 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

<b>Contents</b>	<b>Page</b>
Foreword.....	3
Introduction.....	4
1 Scope.....	5
2 Terms and definitions.....	5
3 Preparation of the test specimens.....	5
4 Apparatus and reagents.....	5
4.1 Apparatus.....	5
4.2 Reagents (analytical grade).....	6
5 Test procedure.....	6
5.1 Principle.....	6
5.2 Reagent (standard solutions).....	6
5.3 Extraction of phthalates.....	7
5.4 Calculation of results.....	7
6 Test report.....	8
Annex A (normative) Calculations.....	9
A.1 Overall treated.....	9
A.2 Locally treated.....	10
Annex B (informative) Suitable Gas Chromatography - Mass Spectrometry (GC-MS) apparatus, method and precision data for determination of phthalate plasticizers [3].....	11
Bibliography.....	13

## Foreword

This document (EN 15777:2009) has been prepared by Technical Committee CEN/TC 248 "Textile and textile products", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2010, and conflicting national standards shall be withdrawn at the latest by February 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway,

## Introduction

This European Standard covers a test method for determination of phthalates in textile articles.

Phthalates are commonly used as plasticizers in polymers. Toxicological concern has arisen due to their potential effect as endocrine disruptors and some of the listed phthalates are toxic in reproduction. The level of media publicity will ensure that their use will continue to be of concern to consumers.

Phthalates are an issue for textile manufacturers and retailers due to their use within motifs, coated fabrics, plastisol prints, buttons, etc. There are textile articles that have to comply with the Directive 2005/84/EC [1] and also articles that fall outside the scope of this legislation, that could be covered by the General Products Safety Directive (2001/95/EC) [2].

**WARNING — Persons using this European Standard should be familiar with normal laboratory practice. This European Standard does not claim to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.**

**This European Standard calls for the use substances and/or procedures that may be injurious to health if appropriate precautions are not observed. It refers only to technical suitability and does not absolve the user from legal obligations relating to health and safety at any stage.**

Phthalates are controversial because high doses of many phthalates have shown hormonal activity in rodent studies. Studies on rodents involving large amounts of phthalates have shown damage to the liver, the kidneys, the lungs, and the developing testes.

**IMPORTANT — It is absolutely essential that tests conducted according to this European Standard be carried out by suitably trained staff.**

## 1 Scope

This standard specifies a test method for taking representative specimens, extraction of phthalates from the material and determination of phthalates by gas chromatography – mass spectrometry.

This standard applies to textiles articles, where there is a possibility of the presence of some phthalates.

## 2 Terms and definitions

For the purposes of this European Standard, the following terms and definitions apply.

### 2.1

#### **blank**

application of the method without test specimen

### 2.2

#### **plasticized or softened materials**

plastic material (coating, pigment print binder, etc) that is treated with chemicals (for this specific standard they are phthalates) to make it more flexible

### 2.3

#### **overall treated textiles**

textiles with a continuous finish, coating or print

### 2.4

#### **locally treated textiles**

textile with a discontinuous finish, coating or print

### 2.5

#### **representative specimen**

specimen obtained by mixing pieces of all the different treated parts and colours

## 3 Preparation of the test specimens

Remove the untreated mass of the specimen if possible (see Annex A). If the untreated mass cannot be removed, see 5.4.

Use a scalpel or other appropriate cutting tool to cut two representative specimens into small pieces.

## 4 Apparatus and reagents

### 4.1 Apparatus

4.1.1 Balance (resolution of 1 mg).

4.1.2 150 ml flask.

4.1.3 Soxhlet extractor with siphon cup of approximately 20 ml.

4.1.4 Soxhlet cellulose thimble, approximately 15 mm in diameter and 50 mm height.

4.1.5 Water-cooled condenser.