

**Plastics - Method for artificial accelerated photoageing
using medium pressure mercury vapour lamps**

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 16472:2014 sisaldab Euroopa standardi EN 16472:2014 inglisekeelset teksti.	This Estonian standard EVS-EN 16472:2014 consists of the English text of the European standard EN 16472:2014.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 02.04.2014.	Date of Availability of the European standard is 02.04.2014.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 83.080.01

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

English Version

Plastics - Method for artificial accelerated photoageing using medium pressure mercury vapour lamps

Plastiques - Méthode de photovieillissement artificiel
accélééré utilisant des lampes à vapeur de mercure à
moyenne pression

Kunststoffe - Verfahren zur künstlich beschleunigten
Alterung bei Verwendung von Quecksilberdampflampen

This European Standard was approved by CEN on 8 February 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 General.....	5
5 Apparatus	6
5.1 Laboratory light source.....	6
5.2 Test chamber.....	8
5.3 Specimen holders	9
5.4 Radiometer	9
5.5 Temperature sensor	9
5.6 Temperature controller	9
5.7 Optional facilities	10
6 Test specimens	10
7 Exposure conditions	10
7.1 Radiation.....	10
7.2 Temperature	10
7.3 Optional facilities	10
8 Procedure	10
8.1 Verification of the apparatus	10
8.2 Mounting the test specimens	11
8.3 Exposure.....	11
8.4 Measurement of radiant exposure	11
8.5 Determination of changes in properties after exposure.....	11
9 Test report	11
Annex A (informative) Additional filtering of lamp UV radiations	13
A.1 Additional filtering of UVB radiations for chromophoric polymers exposed to outdoor conditions.....	13
A.2 Additional filtering of UV radiations for polymers exposed to indoor conditions.....	14
Annex B (informative) Temperature control during photoageing	15
Bibliography	16

Foreword

This document (EN 16472:2014) has been prepared by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2014 and conflicting national standards shall be withdrawn at the latest by October 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

When a polymeric material is exposed to natural UV radiation and other moderate environmental stresses, the change in most physical properties is attributable to chemical ageing, and the extent of the chemical changes can be related to the duration of the exposure under natural outdoor weathering conditions.

This method attempts to maximize the acceleration of photoageing using elevated UV irradiance and temperature that still keep the fundamental photoageing mechanism equivalent to that found in natural ageing. Temperature increase above the natural level should be limited so that the photothermal transformation exceeds any pure thermal conversion. A medium pressure mercury lamp, with radiations of wavelength lower than 290 nm properly filtered out, gives a relevant source with high UV emission intensity and low IR emission.

One of the main interests in use of artificial accelerated photoageing tests is to be able to provide a relevant lifetime estimate of polymeric materials exposed in natural outdoor conditions.

The relevance of artificial ageing can be determined by comparing the chemical changes that occur in the accelerated test to those that occur in natural weathering (see ISO 10640). Kinetic analysis is recommended to determine the rate of degradation under different conditions of ageing in order to rank different formulations or to determine the range of acceleration possible for an artificial ageing test compared to a given natural outdoor weathering exposure (without distortion of the photodegradation mechanism of the polymer).

Chemical changes control the degradation of mechanical properties and contribute to changes in the visual appearance of polymer materials during photoageing. These chemical changes may be analysed primarily by IR spectroscopy, with additional analyses using UV/visible spectroscopy during the photoageing of polymers.

1 Scope

This European Standard specifies a method for carrying out artificial accelerated photoageing of test specimens by exposing them to medium pressure filtered mercury vapour lamp as light source, under controlled temperature conditions.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 4892-1:2000, *Plastics — Methods of exposure to laboratory light sources — Part 1: General guidance (ISO 4892-1:1999)*

ISO 4582, *Plastics — Determination of changes in colour and variations in properties after exposure to daylight under glass, natural weathering or laboratory light sources*

ISO 9370, *Plastics — Instrumental determination of radiant exposure in weathering tests — General guidance and basic test method*

ISO 10640, *Plastics — Methodology for assessing polymer photoageing by FTIR and UV/visible spectroscopy*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

control

material which is of similar composition and construction to the test material and which is exposed at the same time for comparison with the test material

Note 1 to entry: An example of the use of a control material would be when a formulation different from one currently being used is being evaluated. In that case, the control would be the plastic made with the original formulation.

[SOURCE: EN ISO 4892-1:2000]

3.2

reference material

material of known performance

4 General

When correctly powered and maintained, the plasma of a medium pressure mercury arc discharge emits mainly UV and the visible radiation.

This lamp allows the acceleration of the photochemical process by high UV irradiance without high infrared emission.

Specimens of the samples to be tested are exposed to the laboratory light source under controlled temperature condition. The temperature activates the photochemical process.