

**Polymer modified bituminous thick coatings for
waterproofing - Water resistance**

This document is a preview generated by EVS

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 15817:2011 sisaldab Euroopa standardi EN 15817:2011 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 30.04.2011 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 23.03.2011.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 15817:2011 consists of the English text of the European standard EN 15817:2011.

This standard is ratified with the order of Estonian Centre for Standardisation dated 30.04.2011 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 23.03.2011.

The standard is available from Estonian standardisation organisation.

ICS 91.100.50

Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

Right to reproduce and distribute belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:
Aru str 10 Tallinn 10317 Estonia; www.evs.ee; Phone: 605 5050; E-mail: info@evs.ee

ICS 91.100.50

English Version

Polymer modified bituminous thick coatings for waterproofing - Water resistance

Revêtements bitumineux épais modifiés aux polymères
pour imperméabilisation - Résistance à l'eau

Kunststoffmodifizierte Bitumendickbeschichtungen zur
Bauwerksabdichtung - Wasserbeständigkeit

This European Standard was approved by CEN on 13 February 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms und definitions	4
4 Principle.....	4
5 Apparatus	4
6 Procedure	4
6.1 Preparation	4
6.2 Procedure	5
7 Expression of results	5
8 Test report	5

Foreword

This document (EN 15817:2011) has been prepared by Technical Committee CEN/TC 361 "Project Committee — Polymer modified bituminous thick coatings for waterproofing — Definitions/requirements and test methods", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2011, and conflicting national standards shall be withdrawn at the latest by September 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

This European Standard specifies a procedure for determining the water resistance of polymer modified bituminous thick coatings for waterproofing.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

FprEN 15814:2011, *Polymer modified bituminous thick coatings for waterproofing — Definitions and requirements*

ISO 554, *Standard atmospheres for conditioning and/or testing — Specifications*

3 Terms und definitions

For the purposes of this document, the terms and definitions given in FprEN 15814:2011 apply.

4 Principle

After preparing a flexible sheet of polymer modified bitumen-emulsion, the specimen is given in water with a room temperature for 28 days.

After that time a visual assessment is due.

5 Apparatus

5.1 Glass beaker containing 2,5 l tap water; dimensions of sample not less than 90 mm × 250 mm. Position the sample such that 2/3 of the sample is immersed in the water and 1/3 is not immersed.

The sample is suspended in the middle of the beaker so that it is surrounded by water on all sides.

5.2 Magnetic stirrer

6 Procedure

6.1 Preparation

The component of the polymer bitumen-emulsion shall be conditioned in a normal climate of (23 ± 2) °C and a relative humidity of (50 ± 5) % in accordance with ISO 554 for 28 days.

To provide the specified dry layer thickness, $(4 \pm 0,4)$ mm, the wet coating has to be levelled off with the help of a frame or gauge of a foil at room temperature as specified by the manufacturer.

The size of the specimen depends on the container.