
**Lubricants, industrial oils and related
products (class L) — Family T
(Turbines) — Specification for lubricating
oils for turbines**

*Lubrifiants, huiles industrielles et produits connexes (classe L) —
Famille T (Turbines) — Spécifications pour les huiles lubrifiantes pour
turbines*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

This document is a preview generated by EVS

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Sampling.....	4
4 Requirements for turbine oils.....	4
5 Specification tables.....	5
Bibliography.....	16

This document is a preview generated by EVS

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 8068 was prepared by Technical Committee ISO/TC 28, *Petroleum products and lubricants*, Subcommittee SC 4, *Classifications and specifications*.

This second edition cancels and replaces the first edition (ISO 8068:1987), which has been technically revised. ISO 8068:1987 is only dealing with the specifications of TSA and TGA categories of turbine oils. This new edition gives specifications for all the turbine oil categories described in ISO 6743-5:2006.

Introduction

New turbine technologies have emerged in recent years leading to the changes in lubricant requirements. For example, the development of single shaft combined cycle turbines has resulted in the use of a common lubrication system for both the gas and steam turbine. The lubricant should therefore meet the requirements for the lubrication of both pieces of equipment.

The growing concern regarding the environmental behaviour of lubricants is also leading to the use of biodegradable products when there are risks of leakage into soil or surface water. This is particularly the case with hydraulic power plants and lubricants in this application should demonstrate a low ecotoxicity.

This document is a preview generated by EVS

This document is a preview generated by EVS

Lubricants, industrial oils and related products (class L) — Family T (Turbines) — Specification for lubricating oils for turbines

WARNING — The handling and use of products as specified in this International Standard can be hazardous, if suitable precautions are not observed. This International Standard does not purport to address all of the safety problems associated with its use. It is the responsibility of the users of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This International Standard specifies the minimum requirements for turbine lubricants, as delivered. It specifies the requirements for a wide variety of turbines for power generation, including steam turbines, gas turbines, combined-cycle turbines with a common lubrication system and hydraulic (water driven) turbines. This International Standard does not specify the requirements for wind turbines, which are dealt with in ISO 12925-1^[4].

Whilst power generation is the primary application for turbines, steam and gas turbines can also be used to drive rotating equipment, such as pumps and compressors. The lubrication systems of these driven loads can be common to that of the turbine.

Turbine installations incorporate complex auxiliary systems requiring lubrication, including hydraulic systems, gearboxes and couplings. Depending upon the design and configuration of the turbine and driven equipment, turbine lubricants can also be used in these auxiliary systems.

This International Standard should be read in conjunction with ISO 6743-5^[2], the classification of different turbine lubricant types.

The following lubricants are considered in this International Standard:

- mineral oils;
- synthetic lubricants, ester and polyalphaolefin types intended for high-temperature gas turbines;
- synthetic lubricants, ester and polyalphaolefin types, environmentally acceptable for use in hydraulic turbines;
- fire-resistant phosphate-ester type lubricants.

NOTE For the purposes of this International Standard, the term “% (m/m)” is used to represent the mass fraction.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

- ISO 760, *Determination of water — Karl Fischer method (General method)*
- ISO 2049, *Petroleum products — Determination of colour (ASTM scale)*
- ISO 2160, *Petroleum products — Corrosiveness to copper — Copper strip test*
- ISO 2592, *Determination of flash and fire points — Cleveland open cup method*
- ISO 2719, *Determination of flash point — Pensky-Martens closed cup method*
- ISO 2909, *Petroleum products — Calculation of viscosity index from kinematic viscosity.*
- ISO 3016, *Petroleum products — Determination of pour point*
- ISO 3104, *Petroleum product — Transparent and opaque liquids — Determination of kinematic viscosity and calculation of dynamic viscosity*
- ISO 3170, *Petroleum liquids — Manual sampling*
- ISO 3448, *Industrial liquid lubricants — ISO viscosity classification*
- ISO 3675, *Crude petroleum and liquid petroleum products — Laboratory determination of density — Hydrometer method*
- ISO 4259, *Petroleum products — Determination and application of precision data in relation to methods of test*
- ISO 4263-1, *Petroleum and related products — Determination of the ageing behaviour of inhibited oils and fluids — TOST test — Part 1: Procedure for mineral oils*
- ISO 4263-3, *Petroleum and related products — Determination of the ageing behaviour of inhibited oils and fluids — TOST test — Part 3: Anhydrous procedure for synthetic hydraulic fluids*
- ISO 4406, *Hydraulic fluid power — Fluids — Method for coding the level of contamination by solid particles*
- ISO 6072, *Hydraulic fluid power — Compatibility between fluids and standard elastomeric materials*
- ISO 6247, *Petroleum products — Determination of foaming characteristics of lubricating oils*
- ISO 6296, *Petroleum products — Determination of water — Potentiometric Karl Fischer titration method*
- ISO 6341, *Water quality — Determination of the inhibition of the mobility of Daphnia magna Straus (Cladocera, Crustacea) — Acute toxicity test*
- ISO 6614, *Petroleum products — Determination of water separability of petroleum oils and synthetic fluids*
- ISO 6618, *Petroleum products and lubricants — Determination of acid or base number — Colour-indicator titration method*
- ISO 6619, *Petroleum products and lubricants — Neutralization number — Potentiometric titration method*
- ISO 7120, *Petroleum products and lubricants — Petroleum oils and other fluids — Determination of rust-preventing characteristics in the presence of water*
- ISO 7346-2, *Water quality — Determination of the acute lethal toxicity of substances to a freshwater fish [Brachydanio rerio Hamilton-Buchanan (Teleostei, Cyprinidae)] — Part 2: Semi-static method*
- ISO 7537, *Petroleum products — Determination of acid number — Semi-micro colour-indicator titration method*

ISO 7624, *Petroleum products and lubricants — Inhibited mineral turbine oils — Determination of oxidation stability*

ISO 8192, *Water quality — Test for inhibition of oxygen consumption by activated sludge for carbonaceous and ammonium oxidation*

ISO 9120, *Petroleum and related products — Determination of air-release properties of steam turbine and other oils — Impinger method*

ISO 9439, *Water quality — Evaluation of ultimate aerobic biodegradability of organic compounds in aqueous medium — Carbon dioxide evolution test*

ISO 12185, *Crude petroleum and petroleum products — Determination of density — Oscillating U-tube method*

ISO 12937, *Petroleum products — Determination of water — Coulometric Karl Fischer titration method*

ISO 13357-1, *Petroleum products — Determination of the filterability of lubricating oils — Part 1: Procedure for oils in the presence of water*

ISO 13357-2, *Petroleum products — Determination of the filterability of lubricating oils — Part 2: Procedure for dry oils*

ISO 14593, *Water quality — Evaluation of ultimate aerobic biodegradability of organic compounds in aqueous medium — Method by analysis of inorganic carbon in sealed vessels (CO₂ headspace test)*

ISO 14635-1, *Gears — FZG test procedures — Part 1: FZG test method A/8,3/90 for relative scuffing load-carrying capacity of oils*

ISO 14935, *Petroleum and related products — Determination of wick flame persistence of fire-resistant fluids*

ISO 20764, *Petroleum and related products — Preparation of a test portion of high-boiling liquids for the determination of water content — Nitrogen purge method*

ISO 20823, *Petroleum and related products — Determination of the flammability characteristics of fluids in contact with hot surfaces — Manifold ignition test*

ASTM D2272-02, *Standard Test Method for Oxidation Stability of Steam Turbine Oils by Rotating Pressure Vessel*

ASTM D 2711-01a, *Standard Test Method for Demulsibility Characteristics of Lubricating Oils*

ASTM D 2893, *Standard Test Method for Oxidation Characteristics of Extreme-Pressure Lubrication Oils*

ASTM D 4636, *Standard Test Method for Corrosiveness and Oxidation Stability of Hydraulic Oils, Aircraft Turbine Engine Lubricants, and Other Highly Refined Oils*

ASTM D 6081, *Standard Practice for Aquatic Toxicity Testing of Lubricants: Sample Preparation and Results Interpretation*

EN 14832, *Petroleum and related products — Determination of the oxidation stability and corrosivity of fire-resistant phosphate ester fluids*

EN 14833, *Petroleum and related products — Determination of hydrolytic stability of fire-resistant phosphate ester fluids*

DIN 51554-3, *Testing of mineral oils — Test of susceptibility to ageing according to Baader — Testing at 95 °C*