

This document is a preview generated by EVS

Magnesium and magnesium alloys - Magnesium alloys
for cast anodes

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 12438:2017 sisaldab Euroopa standardi EN 12438:2017 ingliskeelset teksti.	This Estonian standard EVS-EN 12438:2017 consists of the English text of the European standard EN 12438:2017.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 06.09.2017.	Date of Availability of the European standard is 06.09.2017.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 77.120.20, 77.150.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Magnesium and magnesium alloys - Magnesium alloys for cast anodes

Magnésium et alliages de magnésium - Alliages de magnésium pour anodes coulées

Magnesium und Magnesiumlegierungen - Magnesiumlegierungen für Gussanoden

This European Standard was approved by CEN on 2 July 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Designations	5
5 Order information	6
6 Manufacture	6
7 Requirements	6
8 Sampling	9
9 Testing	9
10 Inspection documentation	9
11 Packaging and surface protection	9
Annex A (normative) Test method for the determination of the electrode potential of galvanic anodes	10
Annex B (normative) Test method for the determination of the rate of mass loss of galvanic anodes	12
Annex C (informative) Comparison of the designations of magnesium alloy ingots for cast anodes and magnesium alloy cast anodes according to this standard and its previous version	16
Annex D (informative) Significant technical changes between this European Standard and the previous edition	17
Bibliography	18

European foreword

This document (EN 12438:2017) has been prepared by Technical Committee CEN/TC 190 “Foundry technology”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2018, and conflicting national standards shall be withdrawn at the latest by March 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12438:1998.

Within its programme of work, Technical Committee CEN/TC 190 requested CEN/TC 190/WG 9 “Cast magnesium” to revise:

EN 12438:1998, *Magnesium and magnesium alloys — Magnesium alloys for cast anodes*

Annex D provides details of significant technical changes between this European Standard and the previous edition.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

This European Standard classifies magnesium alloys for cast anodes into a number of grades suitable for the applications for which they might be used.

In this European Standard, a new designation system by number, as established in EN 1754 [1], is given.

NOTE This designation system by number is based on the structure and rules of EN 10027-2 [2] and so corresponds with the European numbering system for steel and other materials.

This document is a preview generated by EVS

1 Scope

This European Standard specifies the grades and the corresponding requirements for magnesium alloys for cast anodes.

This European Standard specifies 2 groups of cast magnesium alloy grades by a classification based on chemical composition. The first group deals with magnesium alloy ingots for anodes. The second group deals with magnesium alloy anode castings.

This European Standard specifies chemical composition, designation, testing and inspection documentation.

This European Standard does not cover technical delivery conditions for magnesium alloy anode castings (see EN 1559-1 [3] and EN 1559-5 [4]).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10204, *Metallic products - Types of inspection documents*

EN ISO 80000-1:2013, *Quantities and units - Part 1: General (ISO 80000-1:2009 + Cor 1:2011)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

anode

electrode where oxidation reactions take place

3.2

galvanic anode

anode attached to a metal object to inhibit the corrosion of the object

4 Designations

4.1 Material

The material shall be designated either by symbol or by number as given in Table 1 and Table 2.

NOTE The comparison of EN 12438 grade designations with the designations from the previous version of this European Standard is given in Annex C.

4.2 Casting process

The following symbols shall be used to indicate the different casting processes:

- S Sand casting;
- K Permanent mould casting (gravity);
- C Continuous casting.

NOTE Examples of the use of these designations are given in EN 1559-5 [4].