

Metallic materials - Leeb hardness test - Part 2:
Verification and calibration of the testing devices (ISO
16859-2:2015)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 16859-2:2015 sisaldab Euroopa standardi EN ISO 16859-2:2015 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 16859-2:2015 consists of the English text of the European standard EN ISO 16859-2:2015.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 07.10.2015.	Date of Availability of the European standard is 07.10.2015.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 77.040.10

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Aru 10, 10317 Tallinn, Eesti; koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

**Metallic materials - Leeb hardness test - Part 2:
Verification and calibration of the testing devices (ISO
16859-2:2015)**

Matériaux métalliques - Essai de dureté Leeb - Partie 2
: Vérification et étalonnage des appareils d'essai (ISO
16859-2:2015)

Metallische Werkstoffe - Härteprüfung nach Leeb - Teil
2: Überprüfung und Kalibrierung der Härteprüfgeräte
(ISO 16859-2:2015)

This European Standard was approved by CEN on 10 July 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 16859-2:2015) has been prepared by Technical Committee ISO/TC 164 “Mechanical testing of metals” in collaboration with Technical Committee ECISS/TC 101 “Test methods for steel (other than chemical analysis)” the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2016, and conflicting national standards shall be withdrawn at the latest by April 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 16859-2:2015 has been approved by CEN as EN ISO 16859-2:2015 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 General conditions	1
4 Direct verification	1
4.1 General.....	1
4.2 Calibration parameters.....	2
4.3 Verification of mass and geometry of impact body.....	3
4.4 Verification of geometry and hardness of indenter ball.....	3
4.5 Verification of geometry of support ring.....	3
4.6 Verification of impact velocity.....	3
4.7 Indirect verification of instrument.....	4
5 Indirect verification	4
5.1 General.....	4
5.2 Procedure.....	4
5.3 Variation coefficient (V).....	5
5.4 Error of test instrument.....	5
5.5 Measurement uncertainty.....	6
6 Intervals between verifications	6
7 Verification report/calibration certificate	7
Annex A (informative) Measurement uncertainty of calibration results of Leeb hardness testing instrument	8
Annex B (informative) Direct verification of single coil instrument	11
Bibliography	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary Information](#)

The committee responsible for this document is ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 3, *Hardness testing*.

ISO 16859 consists of the following parts, under the general title *Metallic materials — Leeb hardness test*:

- *Part 1: Test method*
- *Part 2: Verification and calibration of the testing devices*
- *Part 3: Calibration of reference test blocks*

Metallic materials — Leeb hardness test —

Part 2:

Verification and calibration of the testing devices

1 Scope

This part of ISO 16859 specifies methods for direct and indirect verification of test instruments used for determining Leeb hardness in accordance with ISO 16859-1, and also describes when these two types of verification are to be performed.

The direct verification involves checking that individual instrument performance parameters fall within specified limits, whereas the indirect verification utilizes hardness measurements of reference test blocks, calibrated in accordance with ISO 16859-3, to check the overall performance of the instrument for testing in the direction of gravity. The indirect method can be used on its own for the periodic performance checking in service.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 16859-1, *Metallic materials — Leeb hardness test — Part 1: Test method*

ISO 16859-3, *Metallic materials — Leeb hardness test — Part 3: Calibration of reference test blocks*

ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method*

3 General conditions

Before a Leeb hardness testing instrument is verified, the instrument shall be checked to ensure that it is properly set up and operating in accordance with the manufacturer's instructions.

Especially it should be checked that

- a) the impact body is correctly installed in the guide tube,
- b) the support ring is mounted tightly to the bottom of the impact device,
- c) cables are correctly connected, if applicable, and
- d) the settings of the indicating unit are correct.

4 Direct verification

4.1 General

4.1.1 Direct verification should be carried out at a temperature of $(23 \pm 5) ^\circ\text{C}$. If the verification is made outside this temperature range, this shall be reported in the verification report.

4.1.2 The instruments used for verification shall be traceable to national measurement standards.