Non-destructive testing - Ultrasonic testing - Technique of testing claddings produced by welding, rolling and 201.

O CONTROL OF THE CONTROL OF TH explosion (ISO 17405:2014)



### **EESTI STANDARDI EESSÕNA**

### **NATIONAL FOREWORD**

See Eesti standard EVS-EN ISO 17405:2014 sisaldab Euroopa standardi EN ISO 17405:2014 inglisekeelset teksti.	This Estonian standard EVS-EN ISO 17405:2014 consists of the English text of the European standard EN ISO 17405:2014.	
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.	
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 16.07.2014.	Date of Availability of the European standard is 16.07.2014.	
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.	

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 19.100

### Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega: Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

### The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation: Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

### EUROPEAN STANDARD NORME EUROPÉENNE

### **EN ISO 17405**

EUROPÄISCHE NORM

July 2014

ICS 19.100

### **English Version**

## Non-destructive testing - Ultrasonic testing - Technique of testing claddings produced by welding, rolling and explosion (ISO 17405:2014)

Essais non destructifs - Essais par ultrasons - Technique d'essai des placages produits par soudage, laminage et explosion (ISO 17405:2014)

Zerstörungsfreie Prüfung - Ultraschallprüfung - Techniken zur Prüfung von Plattierungen hergestellt durch Schweißen, Walzen und Sprengen (ISO 17405:2014)

This European Standard was approved by CEN on 21 June 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

### **Foreword**

This document (EN ISO 17405:2014) has been prepared by Technical Committee ISO/TC 135 "Nondestructive testing" in collaboration Technical Committee CEN/TC 138 "Non-destructive testing" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2015, and conflicting national standards shall be withdrawn at the latest by January 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

### **Endorsement notice**

n.

Jived by C.

J The text of ISO 17405:2014 has been approved by CEN as EN ISO 17405:2014 without any modification.

Co	ontents	Page
For	reword	iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Ultrasonic test system	1
	4.1 General	
	4.2 Requirements regarding probes Additional requirements	
	4.4 Instrument settings	
5	Preparation of the test object	7
6	Test procedure	
	6.1 General 6.2 Movement of probe	
	6.3 Checking the instrument setting	
	6.4 Recording levels	8
7	Test report	8
	nex A (informative) Determination of focal zone	
Bib	oliography	11
ര IS	50 2014 - All rights reserved	iii

# Non-destructive testing — Ultrasonic testing — Technique of testing claddings produced by welding, rolling and explosion

### 1 Scope

This International Standard specifies the techniques for manual ultrasonic testing of claddings on steel applied by welding, rolling, and explosion using single-element or dual-element probes.

The test is intended to cover detection of two-dimensional or three-dimensional discontinuities in the cladding and in the region of the interface.

This International Standard does not give acceptance criteria nor define the extent of testing.

### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2400, Non-destructive testing — Ultrasonic testing — Specification for calibration block No. 1

EN 1330-4, Non-destructive testing — Terminology — Part 4: Terms used in ultrasonic testing

EN 12668-1, Non-destructive testing — Characterization and verification of ultrasonic examination equipment — Part 1: Instruments

EN 12668-2, Non-destructive testing — Characterization and verification of ultrasonic examination equipment — Part 2: Probes

EN 12668-3, Non-destructive testing — Characterization and verification of ultrasonic examination equipment — Part 3: Combined equipment

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 1330-4 and the following apply.

#### 3.1

### test object

part to be tested

### 3.2

### test surface

areas of the surface of the test object to which probes have to be coupled

### 4 Ultrasonic test system

### 4.1 General

The ultrasonic pulse-echo technique is used. For two-dimensional discontinuities parallel to the test surface and three-dimensional discontinuities, straight beam probes (dual-element or single-element) shall be used for testing with longitudinal waves.