

TÄITEMATERJALIDE KEEMILISTE OMADUSTE
KATSETAMINE. OSA 3: ELUAATIDE VALMISTAMINE
TÄITEMATERJALI LEOSTAMISE TEEL

Tests for chemical properties of aggregates - Part 3:
Preparation of eluates by leaching of aggregates

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 1744-3:2002 sisaldab Euroopa standardi EN 1744-3:2002 ingliskeelset teksti.	This Estonian standard EVS-EN 1744-3:2002 consists of the English text of the European standard EN 1744-3:2002.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 10.07.2002.	Date of Availability of the European standard is 10.07.2002.
Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 91.100.15

Standardite reproduutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autoriõiguse kaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about standards copyright protection, please contact the Estonian Centre for Standardisation and Accreditation:
Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 1744-3

July 2002

ICS 91.100.15

English version

Tests for chemical properties of aggregates - Part 3: Preparation
of eluates by leaching of aggregates

Essais pour déterminer les propriétés chimiques des
granulats - Partie 3: Préparation d'éluats par lixiviation des
granulats

Prüfverfahren für chemische Eigenschaften von
Gesteinskörnungen - Teil 3: Herstellung von Eluaten durch
Auslaugung von Gesteinskörnungen

This European Standard was approved by CEN on 5 March 2002.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Principle	5
5 Reagents	6
6 Apparatus	6
7 Sampling	6
8 Preparation of test portions	6
9 Procedure	7
10 Test report	8
Bibliography	9

Foreword

This document EN 1744-3:2002 has been prepared by Technical Committee CEN/TC 154 "Aggregates", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2003, and conflicting national standards shall be withdrawn at the latest by January 2003.

This standard forms part of a series of tests for chemical properties of aggregates. Test methods for other properties of aggregates will be covered by Parts of the following European Standards:

EN 932	Tests for general properties of aggregates
EN 933	Tests for geometrical properties of aggregates
EN 1097	Tests for mechanical and physical properties of aggregates
EN 1367	Tests for thermal and weathering properties of aggregates
EN 13179	Tests for filler aggregate used in bituminous mixtures

The other parts of EN 1744 are, or will be:

- Part 1: Chemical analysis
- Part 2: Determination of resistance to alkali reaction
- Part 4: Water susceptibility of fillers for bituminous mixtures

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies a method for the preparation of eluates, by leaching of aggregates, for subsequent investigation of physical and chemical properties by existing standard methods for the purpose of compliance testing. It applies to unbound aggregates that have a particle size below 32 mm with or without size reduction (see clause 8).

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 932-1, *Tests for general properties of aggregates — Part 1: Methods for sampling.*

EN 932-2, *Tests for general properties of aggregates — Part 2: Methods for reducing laboratory samples.*

EN 932-5, *Tests for general properties of aggregates — Part 5: Common equipment and calibration.*

EN 933-2, *Tests for geometrical properties of aggregates — Part 2: Determination of particle size distribution — Test sieves, nominal size of apertures.*

EN 1097-5, *Tests for mechanical and physical properties of aggregates — Part 5: Determination of the water content by drying in a ventilated oven.*

EN ISO 3696, *Water for analytical laboratory use — Specification and test methods (ISO 3696:1987).*

3 Terms and definitions

For the purposes of this European Standard, the following terms and definitions apply.

3.1

leachant

liquid used in a laboratory leaching procedure

3.2

eluate

solution remaining after the laboratory leaching procedure of a solid material in contact with a leachant

3.3

constant mass

successive weighings after drying at least 1 h apart not differing by more than 0,1 %.

NOTE In many cases constant mass can be achieved after a test portion has been dried for a pre-determined period in a specified oven at $(110 \pm 5)^\circ\text{C}$. Test laboratories can determine the time required to achieve constant mass for specific types and sizes of sample dependent upon the drying capacity of the oven used.

3.4

laboratory sample

sample intended for laboratory testing

3.5

test portion

sample used as a whole in a single test