

**Flexible sheets for waterproofing -
Determination of length, width and
straightness - Part 1: Bitumen sheets
for roof waterproofing**

Flexible sheets for waterproofing - Determination of
length, width and straightness - Part 1: Bitumen
sheets for roof waterproofing

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN 1848-1:2000 sisaldab Euroopa standardi EN 1848-1:1999 ingliskeelset teksti.</p> <p>Käesolev dokument on jõustatud 17.03.2000 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN 1848-1:2000 consists of the English text of the European standard EN 1848-1:1999.</p> <p>This document is endorsed on 17.03.2000 with the notification being published in the official publication of the Estonian national standardisation organisation.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

<p>Käsitlusala: This European Standard specifies a method for the determination of the length, width and straightness of bitumen sheets for roofing.</p>	<p>Scope: This European Standard specifies a method for the determination of the length, width and straightness of bitumen sheets for roofing.</p>
---	---

ICS 91.100.50

Võtmesõnad:

ICS 91.100.50

English version

Flexible sheets for waterproofing – Determination of
length, width and straightness

Part 1: Bitumen sheets for roof waterproofing

Feuilles souples d'étanchéité –
Détermination de la longueur, de la
largeur et de la rectitude – Partie 1:
Feuilles d'étanchéité de toiture
bitumineuses

Abdichtungsbahnen – Bestimmung
der Länge, Breite und Geradheit –
Teil 1: Bitumenbahnen für Dachab-
dichtungen

This European Standard was approved by CEN on 1999-09-30.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, the Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, the Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, and the United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart 36, B-1050 Brussels

Contents

	Page
Foreword	3
1 Scope	3
2 Normative references	3
3 Definitions	3
4 Principle	3
5 Apparatus	4
6 Sampling and preparation of test specimens	4
7 Procedure	4
8 Expression of results	6
9 Test report	6

This document is a preview generated by EVS

Foreword

This European Standard has been prepared by Technical Committee CEN/TC 254 "Flexible sheets for waterproofing", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2000, and conflicting national standards shall be withdrawn at the latest by September 2001.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies a method for the determination of the length, width and straightness of bitumen sheets for roof waterproofing.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

prEN 13416:—¹⁾

Flexible sheets for waterproofing - Bitumen, plastic and rubber sheets for roof waterproofing - Rules for sampling

3 Definitions

For the purposes of this standard, the definitions indicated in 3.1 to 3.3 apply.

3.1 length: The dimension of the sheet measured in the manufacturing direction.

3.2 width: The dimension of the sheet measured at right angles to the manufacturing direction.

3.3 straightness: The absence of any deviation of the longitudinal edge of the sheet from a straight line.

4 Principle

The selected roll of bitumen sheet is unrolled on a flat surface and the length and width is measured using a metal rule. The straightness of the sheet is determined by measuring deviation from a straight line using a similar measuring device.

¹⁾ standard in preparation