INTERNATIONAL STANDARD

ISO 15877-3

> Second edition 2009-03-15

Plastics piping systems for hot and cold water installations — Chlorinated poly(vinyl chloride) (PVC-C) —

Part 3: **Fittings**

Systèmes de canalisations en plastique pour les installations d'eau chaude et froide — Poly(chlorure de vinyle) chloré (PVC-C) —

Partie 3: Raccords



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below





COPYRIGHT PROTECTED DOCUMENT

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org

Published in Switzerland

Contents

Page

Forev	word	iv
Introd	duction	vi
1	Scope	1
2	Normative references	1
3	Terms, deficitions and symbols	2
3.1	Terms and demitions	
3.2	Symbols	
4	Material characteristics	3
4.1	General	3
4.2	General Fitting material	3
4.3	Evaluation of σ values	3
4.4	Thermal stability Metallic material	7
4.5	Metallic material	8
4.6	Influence on water intended tornuman consumption	9
5	General characteristics	9
5.1	Appearance	9
5.2	Opacity	9
6	Geometrical characteristics General Dimensions of fittings	9
6.1	General	9
6.2	Dimensions of fittings	9
6.3	Dimensions of sockets	16
6.4	Dimensions of flange adaptors and flanges	18
6.5	Dimensions of metallic fittings	20
7	Mechanical characteristics	20
7.1	Resistance to internal pressure	20
7.2	Determination of free lengths	21
7.3	Derivation of the hydrostatic test pressure	22
8	Performance requirements	23
9	Adhesives	23
10	Determination of free lengths Derivation of the hydrostatic test pressure Performance requirements Adhesives Sealing rings Marking General Minimum required marking Additional marking	23
11	Marking	24
11.1	General	24
11.2	Minimum required marking	24
11.3	Additional marking	24
Biblio	paranhy	25

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in Maison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical confinitees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires applying by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 15877-3 was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 155, *Plastics piping systems and ducting systems*, in collaboration with ISO Technical Committee ISO/TC 138, Plastics pipes, fittings and valves for transport of fluids, Subcommittee SC 2, Plastics pipes and fittings for water supplies, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This part of ISO 15877 is part of a System Standard for pastics piping systems of a particular material for a specified application. There are a number of such System Sandards.

The System Standards are consistent with general standards on functional requirements and recommended practices for installation.

This second edition cancels and replaces the first edition (ISO 15877.8.2003).

ISO 15877 consists of the following parts ¹⁾, under the general title *Plastics piping systems for hot and cold water installations* — *Chlorinated polv(vinyl chloride) (PVC-C)*:

- Part 1: General
- Part 2: Pipes
- Part 3: Fittings
- Part 5: Fitness for purpose of the system
- Part 7: Guidance for the assessment of conformity [Technical Specification]

¹⁾ This System Standard does not incorporate a Part 4: Ancillary equipment or a Part 6: Guidance for installation. For ancillary equipment, separate standards can apply. Guidance for installation of plastics piping systems made from different materials, intended to be used for hot and cold water installations, is covered by ENV 12108 [4].

At the date of publication of this part of ISO 15877, System Standards Series for piping systems of other plastics materials used for the same application are the following:

ISO 15874 (all parts), Plastics piping systems for hot and cold water installations — Polypropylene (PP)

ISO 15875 (all parts), Plastics piping systems for hot and cold water installations — Crosslinked polyethylene (PE-X)

ISO 15876 (all parts), Plastics piping systems for hot and cold water installations — Polybutylene (PB)

ISO 22391:—²⁾ parts), Plastics piping systems for hot and cold water installations — Polyethylene of raised temperature resistance (PE-RT)

resista.

Resist

© ISO 2009 - All rights reserved

²⁾ To be published. (Revisions of ISO 22391-1:2007, ISO 22391-2:2007, ISO 22391-3:2007, ISO 22391-5:2007.)

Introduction

The System Standard, of which this is Part 3, specifies the requirements for a piping system when made from chlorinated poly(vinyl chloride) (PVC-C). The piping system is intended to be used for hot and cold water installations and for heating system installations.

In respect of potential adverse effects on the quality of water intended for human consumption caused by the product covered by this part of ISO 15877, the following are relevant.

- This part of ISO 15877 provides no information as to whether the product may be used without restriction in any of the Member States of the EU or EFTA.
- It should be noted that, while awaiting the adoption of verifiable European criteria, existing national regulations concerning the use and/or the characteristics of this product remain in force.

Requirements and test methods for materals and components, other than fittings, are specified in ISO 15877-1 and ISO 15877-2. Characteristics for fitness for purpose (mainly for joints) are covered in ISO 15877-5. Acs of the Acet of the Openion ISO/TS 15877-7 gives guidance for the assessment of conformity.

This part of ISO 15877 specifies the characteristics of the fittings.

νi

Plastics piping systems for hot and cold water installations — Chlorinated poly(vinyl chloride) (PVC-C) —

Part 3: **Fittings**

1 Scope

This part of ISO 15877 specifies the characteristics of fittings made from chlorinated poly(vinyl chloride) (PVC-C) for piping systems intended to be used for hot and cold water installations within buildings for the conveyance of water, whether do not intended for human consumption (domestic systems) and for heating systems under design pressures and temperatures according to the class of application (see Table 1 of ISO 15877-1:2009).

This part of ISO 15877 covers a range of service conditions (application classes) and design pressure classes. For values of $T_{\rm D}$, $T_{\rm max}$ and $T_{\rm mal}$ in excess of those in Table 1 of ISO 15877-1:2009, this part of ISO 15877 does not apply.

NOTE 1 It is the responsibility of the purchaser especifier to make the appropriate selections from these aspects, taking into account their particular requirements and any elevant national regulations and installation practices or codes.

It also specifies the parameters for the test methods the gred to in this part of ISO 15877.

In conjunction with the other parts of ISO 15877, it is applicable to PVC-C fittings, their joints and joints with components of PVC-C, other plastics and non-plastics materials intended to be used for hot and cold water installations.

This part of ISO 15877 is applicable to fittings of the following types:

- fittings for solvent cement joints;
- mechanical fittings;
- fittings with incorporated inserts.

NOTE 2 Fittings made from PVC-C are manufactured by injection-moulding.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 228-1, Pipe threads where pressure-tight joints are not made on the threads — Part 1: Dimensions, tolerances and designation

ISO 580, Plastics piping and ducting systems — Injection-moulded thermoplastics fittings — Methods for visually assessing the effects of heating

ISO 1167-1, Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method

© ISO 2009 – All rights reserved

ISO 1167-2, Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 2: Preparation of pipe test pieces

ISO 2536, Unplasticized polyvinyl chloride (PVC) pressure pipes and fittings, metric series — Dimensions of flanges

ISO 3126, Plastics piping systems — Plastics components — Determination of dimensions

ISO 7686, Plastics pipes and fittings — Determination of opacity

ISO 9080, Plastics piping and ducting systems — Determination of the long-term hydrostatic strength of thermoplastics materials in pipe form by extrapolation

ISO 15877-1:2009, Plastics miping systems for hot and cold water installations — Chlorinated poly(vinyl chloride) (PVC-C) — Part 1. General

ISO 15877-2:2009, Plastics piping systems for hot and cold water installations — Chlorinated poly(vinyl chloride) (PVC-C) — Part 2: Pipes C.

ISO 15877-5, Plastics piping systems for hot and cold water installations — Chlorinated poly(vinyl chloride) (PVC-C) — Part 5: Fitness for purpose of the system

EN 681-1, Elastomeric seals — Material requirements for pipe joint seals used in water and drainage applications — Part 1: Vulcanized rubber

EN 727, Plastics piping and ducting systems — Thermoplastics pipes and fittings — Determination of Vicat softening temperature (VST)

EN 1254-3, Copper and copper alloys — Plumbing fittings — Part 3: Fittings with compression ends for use with plastics pipes

EN 10088-1, Stainless steels — Part 1: List of stainless steel

EN 10226-1, Pipe threads where pressure tight joints are made on the threads — Part 1: Taper external threads and parallel internal threads — Dimensions, tolerances and designation

3 Terms, definitions and symbols

For the purposes of this document, the terms, definitions and symbols given its 150 15877-1 and the following apply:

3.1 Terms and definitions

3.1.1

fitting for solvent cement joints

fitting in which the joint with the pipe or another component is made by means of an adhesing

3.1.2 Mechanical fittings

3.1.2.1

compression fitting

fitting in which the joint is made by the compression of a ring or sleeve on the outside wall of the pipe with or without additional sealing elements and with internal support

3.1.2.2

flanged fitting

fitting in which the pipe connection consists of two mating flanges, which are mechanically pressed together and sealed by the compression of an elastomeric sealing element between them