
**Paper and board — Determination of
colour by diffuse reflectance —**

**Part 1:
Indoor daylight conditions
(C/2°)**

*Papier et carton — Détermination de la couleur par réflectance
diffuse —*

Partie 1: Conditions d'éclairage intérieur de jour (C/2°)



This document is a preview generated by EBS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	3
5 Apparatus.....	3
5.1 Reflectometer.....	3
6 Sampling and conditioning.....	4
7 Preparation of test pieces.....	4
8 Procedure.....	4
9 Calculation.....	4
9.1 CIE tristimulus values.....	4
9.2 CIELAB coordinates.....	5
9.3 Dispersion of the results.....	5
10 Expression of results.....	6
11 Precision.....	6
12 Test report.....	6
Annex A (normative) Spectral characteristics of reflectometers for determining tristimulus values.....	7
Bibliography.....	13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 6, *Paper, board and pulps*.

This second edition cancels and replaces the first edition (ISO 5631-1:2009). The major change is to allow for calculations using ASTM E308 for instruments that have bandpass correction and still maintain the procedure for instruments without bandpass correction.

ISO 5631 consists of the following parts, under the general title *Paper and board — Determination of colour by diffuse reflectance*:

- *Part 1: Indoor daylight conditions (C/2°)*
- *Part 2: Outdoor daylight conditions (D65/10°)*
- *Part 3: Indoor illumination conditions (D50/2°)*

Introduction

The colour of an object can be uniquely characterized by means of a triplet of colour coordinates such as the CIE tristimulus values or the CIELAB 1976 L^* , a^* , b^* coordinates for a specified CIE illuminant and CIE standard observer.

Apart from the optical properties of the sample, the values of such coordinates depend upon the conditions of measurement, particularly the spectral and geometric characteristics of the instrument used. This part of ISO 5631 should therefore be read in conjunction with ISO 2469.

This part of ISO 5631 describes the measurement and description of colour in terms of the CIE illuminant C and the CIE 1931 (2°) standard observer. The other parts of this International Standard describe measurements and calculations carried out in an analogous manner using either the CIE standard illuminant D65 and the CIE 1964 (10°) standard observer or the CIE illuminant D50 and the CIE 1931 (2°) standard observer.

The choice of illuminant conditions is important when determining the colour coordinates of white papers containing a fluorescent whitening agent. In ISO 5631-2, the UV content of the illumination is much higher, approximating UV levels encountered in outdoor viewing conditions.

ISO 5631-3 describes the measurement and description of colour in terms of the CIE illuminant D50 and the CIE 1931 (2°) standard observer. This method is especially applicable to graphic arts situations since these illuminant/observer conditions are used within the graphic arts industry.

Paper and board — Determination of colour by diffuse reflectance —

Part 1: Indoor daylight conditions (C/2°)

1 Scope

This part of ISO 5631 specifies a method for measuring the colour of paper and board by the diffuse reflectance method with the elimination of specular gloss.

This part of ISO 5631 is not applicable to coloured papers or boards which incorporate fluorescent dyes or pigments. It may be used to determine the colour of papers or boards which contain fluorescent whitening agents provided the UV content of the illumination on the test piece has been adjusted to conform to that in the CIE illuminant C, using a fluorescent reference standard that fulfils the requirements for international fluorescent reference standards of level 3 (IR3) as prescribed by ISO 2469 with an assigned ISO brightness value (C/2°) provided by an authorized laboratory, as described in ISO 2470-1.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 2469, *Paper, board and pulps — Measurement of diffuse radiance factor (diffuse reflectance factor)*

ISO 2470-1, *Paper, board and pulps — Measurement of diffuse blue reflectance factor — Part 1: Indoor daylight conditions (ISO brightness)*

ASTM E308, *Standard Practice for Computing the Colors of Objects by Using the CIE System*

CIE Publication 15:2004, *Colorimetry*, 3rd ed

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

radiance factor

β

ratio of the radiance of a surface element of a body in the direction delimited by a given cone, with its apex at the surface element, to that of the perfect reflecting diffuser under the same conditions of illumination

Note 1 to entry: For fluorescent (luminescent) materials, the total radiance factor, β , is the sum of two portions, the reflected radiance factor, β_R , and the luminescent radiance factor, β_L , so that $\beta = \beta_R + \beta_L$.

For non-fluorescent materials, the reflected radiance factor, β_R , is numerically equal to the reflectance factor, R .