INTERNATIONAL STANDARD

ISO 5631-3

> Third edition 2015-11-01

Paper and board — Determination of colour by diffuse reflectance —

Part 3: Indoor illumination conditions (D50/2°)

Papier et carton — Détermination de la couleur par réflectance .itions d'éc diffuse —

Partie 3: Conditions d'éclairage intérieur (D50/2°)





© ISO 2015, Published in Switzerland

voduced or utilized c te internet or an 'nr ISO's memb All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Ch. de Blandonnet 8 • CP 401 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

COI	itents	Page
Fore	word	iv
Intro	oduction	v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	3
5	Apparatus	3
6	Sampling and conditioning	4
7	Preparation of test pieces	4
8	Procedure	4
9	Calculation 9.1 CIE tristimulus values 9.2 CIELAB coordinates 9.3 Dispersion of the results	5 5
10	Expression of results	6
11	Precision	
12	Test report	6
Anne	ex A (normative) Spectral characteristics of reflectometers for determining tristimulus values	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document ISO/TC 6, *Paper, board and pulps*.

This third edition cancels and replaces the second edition (ISO 5631-3:2014). The major change is to allow for calculations using ASTM E308 for instruments that have bandpass correction and still maintain the procedure for instruments without bandpass correction.

ISO 5631 consists of the following parts, under the general title *Paper and board — Determination of* Pu, colour by diffuse reflectance:

- *Part 1: Indoor daylight conditions (C/2°)*
- Part 2: Outdoor daylight conditions (D65/10°)
- Part 3: Indoor illumination conditions (D50/2°)

Introduction

The colour of an object can be uniquely characterized by means of a triplet of colour coordinates such as the CIE X,Y,Z tristimulus values or the CIELAB 1976 L^* , a^* , b^* coordinates for a specified CIE illuminant and CIE standard observer.

Apart from the optical properties of the sample, the values of such coordinates depend upon the conditions of measurement, particularly the spectral and geometric characteristics of the instrument used. This part of ISO 5631 should therefore be read in conjunction with ISO 2469.

This part of ISO 5631 describes the measurement and description of colour in terms of the CIE illuminant D50 and the CIE 1931 (2°) standard observer. The method is especially applicable to the comparison of papers in graphic arts situations since these particular illuminant/observer conditions are required by ISO 13655 for the graphic arts industry. It is, however, emphasized that this is only a partial approach to the graphic arts conditions, since ISO 13655 also specifies measurement with a 45:0 or 0:45 geometry of a single sheet over a specified black backing and also requires that the illumination in the light booth be adjusted to CIE illuminant D50 conditions.

The other parts of this International Standard describe measurements and calculations carried out in an analogous manner using either the CIE illuminant C and the CIE 1931 (2°) standard observer (ISO 5631-1) or the CIE standard illuminant D65 and the CIE 1964 (10°) standard observer (ISO 5631-2). The choice of illuminant conditions is important when determining the colour coordinates of white pc ags icounter papers containing a fluorescent whitening agent. In ISO 5631-2, the UV content of the illumination is much higher, approximating UV levels encountered in outdoor viewing conditions

This document is a preview general ded by tills

Paper and board — Determination of colour by diffuse reflectance —

Part 3:

Indoor illumination conditions (D50/2°)

1 Scope

This part of ISO 5631 specifies a method for measuring the colour of paper and board by the diffuse reflectance method with the elimination of specular gloss.

This part of ISO 5631 is primarily intended for measuring the colour of paper and board to be used in the graphic arts industry, where that industry specifies the measurement of colour under $D50/2^{\circ}$ conditions in accordance with ISO 13655. This method differs from ISO 13655, in that the UV content of the illumination is adjusted to a different level.

The method can be used to determine the colour of papers or boards that contain fluorescent whitening agents, provided the UV content of the illumination on the test piece has been adjusted to conform to that in the CIE illuminant C, using a fluorescent reference standard that fulfils the requirements for international fluorescent reference standards of level 3 (IR3) as prescribed by ISO 2469 with an assigned ISO brightness value $(C/2^{\circ})$ provided by an authorized laboratory, as described in ISO 2470-1.

This part of ISO 5631 is not applicable to coloured papers or boards that incorporate fluorescent dyes or pigments.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, Paper and board — Sampling to determine average quality

ISO 2469, Paper, board and pulps — Measurement of diffuse radiance factor (diffuse reflectance factor)

ISO 2470-1, Paper, board and pulps — Measurement of diffuse blue reflectance factor — Part 1: Indoor daylight conditions (ISO brightness)

ASTM E308, Standard Practice for Computing the Colors of Objects by Using the CIE System

CIE Publication 15:2004, Colorimetry, 3rd ed

3 Terms and definitions

For the purposes of this document, the following terms and definitions.