

ICS 17.040.20; 25.220.99; 81.060.30

English version

**Advanced technical ceramics - Methods of test for ceramic  
coatings - Part 10: Determination of coating thickness by cross  
sectioning**

Céramiques techniques avancées - Méthodes d'essai pour  
les revêtements céramiques - Partie 10: Détermination de  
l'épaisseur du revêtement par découpage transverse

Hochleistungskeramik - Verfahren zur Prüfung keramischer  
Schichten - Teil 10: Bestimmung der Schichtdicke mittels  
Querschliff

This Technical Specification (CEN/TS) was approved by CEN on 2 March 2004 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

## Contents

Page

Foreword .....	4
Introduction .....	5
1 Scope .....	6
2 Normative references .....	6
3 Terms and definitions .....	6
4 Principle .....	6
5 Apparatus .....	6
5.1 Scanning electron microscope (SEM) .....	6
5.2 Optical microscope .....	6
6 Sample preparation .....	7
6.1 Cross-section preparation .....	7
6.2 Surface roughness .....	7
6.3 Taper of cross-section .....	7
6.4 Specimen tilt .....	7
6.5 Coating damage .....	7
6.6 Rounding of edges of the coating .....	7
6.7 Overplating .....	8
6.8 Etching .....	8
6.9 Smearing .....	8
7 Calibration of instruments .....	8
7.1 Procedure .....	8
7.2 Photography .....	8
7.3 Measurement .....	8
7.4 Calculation of magnification .....	8
7.5 Poor contrast .....	9
7.6 Magnification .....	9
7.7 Uniformity of magnification .....	9
7.8 Stability of magnification .....	9
8 Test procedure .....	9
8.1 General .....	9
8.2 Preparation of images .....	10
8.2.1 General .....	10
8.2.2 Conventional photographic micrograph .....	10
8.2.3 Digital images .....	10
8.3 Measurement .....	10
8.4 Thickness calculation .....	10
8.5 Correction procedures .....	11
9 Measurement uncertainty .....	11
10 Expression of results .....	11
11 Reporting of results .....	11
Annex A (informative) General guidance on the preparation and measurement of cross-sections .....	13
A.1 Introduction .....	13
A.2 Cutting .....	13
A.3 Mounting .....	13

A.4	Grinding and polishing.....	14
A.5	Use of the scanning electron microscope.....	14
	Bibliography .....	15

This document is a preview generated by EVS

## Foreword

This document CEN/TS 1071-10:2004 has been prepared by Technical Committee CEN/TC 184 "Advanced technical ceramics", the secretariat of which is held by BSI.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

EN 1071 *Advanced technical ceramics — Methods of test for ceramic coatings* consists of 11 parts:

- Part 1: *Determination of coating thickness by contact probe profilometer*
- Part 2: *Determination of coating thickness by the crater grinding method*
- Part 3: *Determination of adhesion and other mechanical failure modes by a scratch test*
- Part 4: *Determination of chemical composition*
- Part 5: *Determination of porosity*
- Part 6: *Determination of the abrasion resistance of coatings by a micro-abrasion wear test*
- Part 7: *Determination of hardness and Young's modulus by instrumented indentation testing*
- Part 8: *Rockwell indentation test for evaluation of adhesion<sup>1)</sup>*
- Part 9: *Determination of fracture strain*
- Part 10: *Determination of coating thickness by cross sectioning*
- Part 11: *Measurement of internal stress with the Stoney formula<sup>1)</sup>*

Parts 7 to 11 are Technical Specifications.

This document includes a bibliography.

---

1) In preparation at the time of publication of this document.

## Introduction

The thickness of a coating is an important property that controls its functional behaviour. Thickness determinations are also used as part of quality control in the production of coatings. It is normal to specify a thickness when defining a coating, so that valid methods of measurement are required. The method described here is direct, but is destructive, requiring preparation of a metallographic cross-section. A number of other standard non-destructive methods exist and some of these are listed in the Bibliography (references [1] to [7]).

## 1 Scope

This document specifies a method of measuring the thickness of ceramic coatings by means of examination of a metallographically prepared cross-section of the coating in a calibrated optical or scanning electron microscope. It draws strongly on EN ISO 9220 [8], modifying and updating as required to be relevant to ceramic coatings and current best practice.

## 2 Normative references

The following referenced document is indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ENV 13005, *Guide to the expression of uncertainty in measurement*

## 3 Terms and definitions

For the purposes of this document, the following term and definition apply.

### 3.1

#### **local thickness**

mean of the thickness measurements, of which a specified number is made within a reference area [EN ISO 2064:2000, 3.4]<sup>[5]</sup>

## 4 Principle

This test procedure covers the measurement of coating thickness by examination of a cross-section in an optical or scanning electron microscope. Preparation of the cross-section requires care to ensure that the total thickness is revealed and that when viewed it is normal to the axis of the microscope. After proper calibration of the microscope, it is a simple matter to determine the coating thickness from knowledge of the magnification used. This can be done directly using a modern measuring microscope, or indirectly from photographic images obtained from an optical or scanning electron microscope.

## 5 Apparatus

### 5.1 Scanning electron microscope (SEM)

The SEM shall have a spatial resolution of 50 nm or better. Suitable instruments are available commercially.

### 5.2 Optical microscope

The optical microscope shall have a spatial resolution of 500 nm or better. Suitable instruments are available commercially.

NOTE 1 Microscopes that incorporate a system to automatically record the XY coordinates are available and if the stage movement has been calibrated, can be used directly to measure coating thickness without the need to take photographs. This method is particularly useful where coating thickness variations around a component are likely.