

Coil coated metals - Test methods - Part 22: Colour difference - Visual comparison

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 13523-22:2017 sisaldab Euroopa standardi EN 13523-22:2017 ingliskeelset teksti.	This Estonian standard EVS-EN 13523-22:2017 consists of the English text of the European standard EN 13523-22:2017.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 22.02.2017.	Date of Availability of the European standard is 22.02.2017.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 25.220.60

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Coil coated metals - Test methods - Part 22: Colour difference - Visual comparison

Tôles prélaquées - Méthodes d'essai - Partie 22:
Différence de couleur - Comparaison visuelle

Bandbeschichtete Metalle - Prüfverfahren - Teil 22:
Farbabstand - Visueller Vergleich

This European Standard was approved by CEN on 9 January 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword	3
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principle	6
5 Illumination for colour matching	6
5.1 Natural daylight.....	6
5.2 Artificial daylight	6
5.3 Colour-matching booth.....	6
6 Observer	7
7 Sampling	7
8 Test specimens and reference standards	7
9 Procedure	7
9.1 General.....	7
9.2 Day-to-day routine.....	7
9.3 Referee procedure	8
10 Expression of results	8
11 Precision	8
12 Test report	8
Bibliography	9

European foreword

This document (EN 13523-22:2017) has been prepared by Technical Committee CEN/TC 139 “Paints and varnishes”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2017, and conflicting national standards shall be withdrawn at the latest by August 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13523-22:2010.

The main changes are:

- a) a reference to EN 13523-0 concerning conditioning of the test panels was added;
- b) the requirement for ambient and panel temperature and relative humidity during measurement has been stated more precisely;
- c) the text was revised editorially and the normative references were updated.

The EN 13523 series, *Coil coated metals — Test methods*, consists of the following parts:

- *Part 0: General introduction*
- *Part 1: Film thickness*
- *Part 2: Gloss*
- *Part 3: Colour difference — Instrumental comparison*
- *Part 4: Pencil hardness*
- *Part 5: Resistance to rapid deformation (impact test)*
- *Part 6: Adhesion after indentation (cupping test)*
- *Part 7: Resistance to cracking on bending (T-bend test)*
- *Part 8: Resistance to salt spray (fog)*
- *Part 9: Resistance to water immersion*
- *Part 10: Resistance to fluorescent UV radiation and water condensation*
- *Part 11: Resistance to solvents (rubbing test)*
- *Part 12: Resistance to scratching*
- *Part 13: Resistance to accelerated ageing by the use of heat*

- *Part 14: Chalking (Helmen method)*
- *Part 15: Metamerism*
- *Part 16: Resistance to abrasion*
- *Part 17: Adhesion of strippable films*
- *Part 18: Resistance to staining*
- *Part 19: Panel design and method of atmospheric exposure testing*
- *Part 20: Foam adhesion*
- *Part 21: Evaluation of outdoor exposed panels*
- *Part 22: Colour difference — Visual comparison*
- *Part 23: Resistance to humid atmospheres containing sulfur dioxide*
- *Part 24: Resistance to blocking and pressure marking*
- *Part 25: Resistance to humidity*
- *Part 26: Resistance to condensation of water*
- *Part 27: Resistance to humid poultice (Cataplasma test)*
- *Part 29: Resistance to environmental soiling (Dirt pick-up and striping)*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This part of the EN 13523 series specifies the procedure for determining the difference in the colour of an organic coating on a metallic substrate by visual comparison against a standard using either diffuse natural daylight or artificial daylight in a standard booth.

NOTE Results might differ between natural and artificial daylight.

It might be that two colour specimens will match in daylight but not under another light source. This phenomenon is known as metamerism (see EN 13523-15).

If a metameric match is to be reported in objective terms, spectrophotometric measurements (using CIE Standard Illuminants D65 and A) should be made, in accordance with EN 13523-15.

No statement is made about either the precision or the accuracy of this procedure since the results derived are neither in numerical form nor do they provide a pass/fail evaluation in objective terms. Therefore, this procedure should only be used where the use of colour measuring instruments is not recommendable (evaluation of colour matches, inspection of metallic colours, etc.).

The standardization of such visual comparisons, by light sources, illuminating and viewing geometry and specimen size, provides for improved uniformity of results. This practice is essential for critical colour matching and is highly recommended for colour inspections.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13523-0:2014, *Coil coated metals — Test methods — Part 0: General introduction*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 13523-0 and the following apply.

3.1 colour

sensation resulting from the visual perception of light of a given spectral composition by the human eye

Note 1 to entry: The use of the German term “Farbe” alone, i.e. not in combination of words, for coating materials is deprecated.

Note 2 to entry: A colour is characterized by hue, chroma, and lightness.

[SOURCE: EN ISO 4618:2014, 2.58]

3.2 metamerism

phenomenon characterized by the difference in colour observed when two specimens visually matching under a given light source are viewed under another light source with different spectral characteristics

[SOURCE: EN 13523-15:2015, 3.1]