

ICS 83.180

English Version

**Adhesives for thermoplastic piping systems - Accelerated ageing
test of adhesives**

Adhésifs pour réseaux de tuyauteries en matières
thermoplastiques - Essai de vieillissement accéléré des
adhésifs

Klebstoffe für thermoplastische Rohrleitungssysteme -
Prüfung von Klebstoffen bei künstlicher Alterung

This Technical Specification (CEN/TS) was approved by CEN on 9 November 2004 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Principe	4
5 Safety clause	4
6 Apparatus	4
7 Sampling	5
8 Procedure	5
9 Test Report	5

Foreword

This document (CEN/TS 14999:2006) has been prepared by Technical Committee CEN/TC 193 “Adhesives”, the secretariat of which is held by AENOR.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this CEN Technical Specification: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

This Technical Specification (TS) describes a method for an accelerated ageing test of an adhesive in its container. The result provides the manufacturer with an indication of the storage stability of the adhesive and container combination and their ability to retain adhesive properties.

The method described is intended for solvent based adhesives for thermoplastic piping systems but may be applied to other adhesive types if appropriate.

The method described in this TS does not give a correlation between the results obtained after the accelerated aging test and after the shelf life of the adhesive at the ambient conditions defined by the manufacturer in the data sheet.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 923:2005, *Adhesives - Terms and definitions*

EN ISO 9311-2, *Adhesives for thermoplastic piping systems - Part 2: Determination of shear strength (ISO 9311-2:2002)*

EN 12092, *Adhesives - Determination of viscosity*

3 Terms and definitions

For the purposes of this Technical Specification, the terms and definitions given in EN 923:2005 apply.

4 Principle

The sample is subjected to a combination of temperature and time under specified conditions, followed by comparison of the viscosity and the shear strength of the aged sample with those of a reference sample that has been maintained under standard reference conditions (23 ± 2 °C and 50 ± 5 % relative humidity).

5 Safety clause

Persons using this standard shall be familiar with normal laboratory practice.

This standard does not purport to address all the safety problems, if any, associated with its use.

It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any European or national regulatory conditions.

6 Apparatus

6.1 Oven, able to maintain a temperature of $50^{\circ}\text{C} \pm 2^{\circ}\text{C}$ or $40^{\circ}\text{C} \pm 2^{\circ}\text{C}$.