

---

---

## Rubber — Determination of frictional properties

*Caoutchouc — Détermination des propriétés frictionnelles*



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

This document is a preview generated by EVS

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

Foreword.....	iv
Introduction .....	v
1 Scope .....	1
2 Normative references .....	1
3 Terms and definitions.....	1
4 Principle.....	2
5 Apparatus .....	3
6 Test surfaces .....	3
7 Preparation .....	4
8 Conditioning.....	6
9 Test parameters .....	6
10 Cleaning or renewal of the test track.....	7
11 Procedure A (initial friction measurements).....	7
12 Procedure B (service behaviour) .....	8
13 Procedure C (tests with added lubricants or contaminants) .....	8
14 Stick-slip .....	9
15 Presentation of results .....	9
16 Test report .....	12
Annex A (informative) Design principles .....	13
Annex B (informative) Ball-on-flat geometry .....	15
Annex C (informative) Static friction and “stiction” .....	16
Annex D (informative) Other parameters .....	17
Bibliography .....	20

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 15113 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This second edition cancels and replaces the first edition (ISO 15113:1999), of which it constitutes a minor revision, the main purpose of which was to update the normative references clause. It also incorporates Technical Corrigendum ISO 15113:1999/Cor. 1:2001.

## Introduction

Various geometrical arrangements can be used when measuring friction, but each is likely to give a different value for  $\mu$ , the coefficient of friction. Each may be appropriate in particular circumstances, but it is desirable that some standard method utilizing specified test conditions be employed when comparisons between materials are undertaken.

Rubber samples are most readily available in sheet form, and for many practical applications measurement between two planar surfaces most nearly approaches service behaviour. Consequently, this is the most widely used geometry. For this geometry, the apparatus used needs careful design in order to ensure reproducible contact between the surfaces, and this is discussed in Annex A.

Where rubber moulding facilities are available, some workers prefer to use a hemispherical rubber slider and a planar test track. This gives a more definable contact area and minimizes the errors involved if the friction plane does not contain both the line of action of the load cell and that of the towing force. However, when this geometry is used, the frictional force is not proportional to the normal load (see Annex B), and the contact area is estimated from a knowledge of the modulus of the rubber. Hence care should be taken when quoting values for coefficients of friction. The big disadvantage of the method is that special test pieces need to be moulded from unvulcanized rubber, and rubber products cannot be accommodated. Finally, since some degree of wear is inseparable from friction, extended testing will produce a "flat" on the hemispherical test piece. Frequent inspection of the test surface is recommended, therefore, to ensure that the initial contact geometry is maintained.

The alternative "ball-on-flat" geometry where a hard ball slides on a flat rubber surface is not an exact equivalent. The ploughing action of the ball through the rubber results in an energy loss by hysteresis which gives a higher measured coefficient of friction. However, in some circumstances this may be an appropriate test procedure.

Although there may be some uncertainty in the contact area using plane-on-plane geometry, this International Standard is based on this geometry because of its wide practical applicability. However, it is emphasized that it is necessary to have a well designed apparatus with the line of action of the load cell included in the plane of contact of the test pieces (see Annex A). The method can be adapted to cover other contact geometries to suit particular products, including the ball-on-flat geometry set out in Annex B.

This International Standard is based on linear motion, and guidance on the experimental arrangement is given in Annex A. Because friction generates heat, it is usual to restrict testing to velocities typically below 1 000 mm/min in order to avoid a large temperature rise at the interface. If service conditions involve high speeds, then an entirely different method based on rotary motion is more appropriate as discussed in Annex A. The method of test set out here enables kinetic friction to be measured at a number of fixed velocities. It can be arranged that the lowest velocity is such that movement is barely discernible, and this gives an approximation to frictional behaviour close to zero velocity (static friction). This may be different from the starting friction, which may involve some element of adhesion (stiction) as discussed in Annex C. This method is suitable for measuring the initial friction only if the machine has a constant rate-of-load facility and a sufficiently compliant load cell. A discussion on static friction and the correct approach to its measurement is given in Annex C.

Rubber friction is complex, and the coefficient of friction is dependent on the contact geometry, normal load, velocity and temperature, as well as the composition of the rubber. A discussion of the influence of these parameters and some other factors which affect measurement is presented in Annex D.

This document is a preview generated by EVS

# Rubber — Determination of frictional properties

## 1 Scope

This International Standard outlines the principles governing the measurement of coefficient of friction and describes a method suitable for measuring the coefficient of friction of a rubber against standard comparators, against itself, or against any other specified surface.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5893:2002, *Rubber and plastics test equipment — Tensile, flexural and compression types (constant rate of traverse) — Specification*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 3.1

#### **coefficient of friction**

ratio of the frictional force opposing motion between two surfaces to the normal force between the surfaces under specified test conditions

NOTE Coefficient of friction is dimensionless and its value is not restricted to numbers less than unity.

### 3.2

#### **area of contact**

whole of the apparent area made between the two test surfaces (test track and test piece)

NOTE The real area of contact (see 3.3) may well be less than this.

### 3.3

#### **real area of contact**

sum total of the minute contact areas at which the two test surfaces touch

### 3.4

#### **velocity of test**

velocity with which one surface is driven relative to the other

NOTE If stick-slip (see 3.5) occurs, this will then be the mean velocity with which one surface moves relative to the other.