
**Hard coal and coke — Determination of
ash fusibility**

Houille et coke — Détermination de la fusibilité des cendres



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

This document is a preview generated by EVS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	2
5 Reagents.....	2
6 Apparatus.....	2
7 Test conditions.....	4
7.1 Test atmosphere.....	4
7.2 Shape of test piece.....	4
8 Calibration check.....	7
9 Preparation of the test piece.....	7
10 Procedure.....	7
11 Precision of the method.....	8
11.1 Repeatability limit.....	8
11.2 Reproducibility limit.....	8
12 Test report.....	8
13 Precision statement.....	9
Bibliography.....	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 540 was prepared by Technical Committee ISO/TC 27, *Solid mineral fuels*, Subcommittee SC 5, *Methods of analysis*.

This fourth edition cancels and replaces the third edition (ISO 540:1995), which has been technically revised.

Introduction

The method for determination of the fusibility temperatures of coal ash and coke ash described in this International Standard provides information about the fusion and melting behaviour of the composite inorganic constituents of the ash at high temperatures. The standard method is based on the “Seeger Cone” method, which is well known in the ceramic industry, the use of which predates the year 1900. The conditions of the test, as well as basic studies on the influence of ash chemistry and of gas composition on ash fusibility temperatures (which have led to the standardization of the method), arose from the pioneering work of Fieldner, Hall and Field [1].

In the laboratory, the ash used for the test is a homogeneous mixture prepared from a representative sample of the coal or coke, and the determination is performed at a controlled rate of heating in either a reducing or an oxidizing atmosphere. In contrast, under industrial conditions, the complex processes of combustion and fusion involve heterogeneous mixtures of particles, heating rates (that can be several orders of magnitude greater than those used in the standard test) and variable gas composition.

During the first quarter of the 20th century, laboratory, pilot-scale and field studies were undertaken to establish that the ash fusibility test can provide a reasonable indication of the propensity of ash to form fused deposits (referred to as “clinker”) in stoker and other fuel-bed type furnaces (Nicholls and Selvig [2]). Subsequently, the test has been used as a general indicator of the tendency for ash to fuse on heating and of ash slagging propensity in pulverized coal-fired furnaces.

This document is a preview generated by EVS

Hard coal and coke — Determination of ash fusibility

1 Scope

This International Standard specifies a method of determining the characteristic fusion temperatures of ash from coal and coke.

NOTE Descriptors: fossil fuels, solid fuels, ash, ashes, tests, high temperature tests, determination, and fusibility.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1171, *Solid mineral fuels — Determination of ash*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

deformation temperature

DT

temperature at which the first signs of rounding, due to melting, of the tip or edges of the test piece occur

NOTE Shrinkage or distortion of the test piece, or rounding of cracks and fins, are not criteria for deformation and should be ignored if the tip and edges remain sharp. However, for some solid mineral fuels, the temperature at which the test piece shrinkage begins can be of interest and should be reported as a feature noted during the determination.

3.2

sphere temperature

ST

in the case of pyramidal and truncated-cone test pieces, the temperature at which the height is equal to the width of the base, and in the case of cubical or cylindrical test pieces, the temperature at which the edges of the test pieces become completely round with the height remaining unchanged

3.3

hemisphere temperature

HT

temperature at which the test piece forms approximately a hemisphere, i.e. when the height becomes equal to half the base diameter

3.4

flow temperature

FT

temperature at which the ash melt is spread out over the supporting tile in a layer, the height of which is one-third of the height of the test piece at the hemisphere temperature