
Ophthalmic optics and instruments — Correlation of optotypes

Optique et instruments ophtalmiques — Corrélation des optotypes



This document is a preview generated by EBS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 General requirements for optotypes	1
3 Correlation of optotypes	1
3.1 Selection of optotypes for correlation testing.....	1
3.2 Test area.....	1
3.3 Presentation of the optotypes.....	1
3.4 Corrective lenses.....	2
3.5 Test distance.....	2
3.6 Luminance.....	2
4 Assignment of an acuity score	2
5 Assessing the equivalence of two kinds of optotype	3
6 Significance of the difference between the two means	3
Bibliography	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 172, *Optics and photonics*, Subcommittee SC 7, *Ophthalmic optics and instruments*.

Ophthalmic optics and instruments — Correlation of optotypes

1 Scope

This Technical Report specifies a method of correlation between a given set of optotypes and the standard optotype (Landolt ring) formed and presented as specified in ISO 8596.

All test methods are type tests and suitable equivalent test methods may be substituted.

2 General requirements for optotypes

Each size of a set of optotypes is specified in terms of the size of the standard Landolt ring that is equally recognizable as determined according to the method of [Clause 3](#).

This means that the size of a set of optotypes is the size of the nominal 1,0 acuity set magnified or minified by a multiple of the ratio 1,2589 (see ISO 8596:2009, Clause 4).

3 Correlation of optotypes

3.1 Selection of optotypes for correlation testing

Sufficient grades or steps should be used to establish a frequency of seeing curve for the standard optotype and the optotype being investigated.

A recommended range of decimal acuity sizes to use is 2,0 to 0,4 in Log MAR steps of 0,1.

3.2 Test area

The test area is circular with a diameter of $4^\circ \pm 1^\circ$. The surrounding field has a diameter of $15^\circ \pm 1,5^\circ$ and is illuminated homogeneously so that it does not influence the measurement. The luminance of the surrounding field does not exceed that of the test area.

3.3 Presentation of the optotypes

3.3.1 When a measurement of visual acuity is made with the eight-position Landolt ring for purposes of correlation, 120 presentations are made one ring at a time with the ring positions for successive presentations arranged in random order. The optotypes to be correlated are also presented one at a time in random order until a series of 120 presentations has been completed. In the 120 presentations, the different optotypes in each set are represented approximately the same number of times.

3.3.2 The number 120 is divisible by 2, 3, 4, 6, 8, 10, 12, 15, 20, 30, 40, and 60. Hence, with sets of optotypes having any of these numbers of different optotypes, it is possible for each optotype to be represented the same number of times in 120 presentations. The comparison is started with a grade of optotypes large enough to yield a frequency of seeing of 100 %. Measurements are made with both eight-position Landolt rings and the optotypes of the same size being correlated. When this has been completed, the procedure is repeated with smaller and smaller sizes until the failure rate corresponds to the level of guessing of 0,125. The probability of guessing p of 0,125 results from the choice of eight different optotypes per acuity grade and the definition of p given in [4.2](#). Each optotype is exposed for 3 s with an interval of 4 s between exposures.