# Aerospace series - Aluminium alloy AL-P2618A - T851 - Hand and die forgings a £ 150 mm

Aerospace series - Aluminium alloy AL-P2618A - T851 - Hand and die forgings - a £ 150 mm



## **EESTI STANDARDI EESSÕNA**

# **NATIONAL FOREWORD**

Käesolev Eesti standard EVS-EN
2086:2005 sisaldab Euroopa standardi EN
2086:2004 ingliskeelset teksti.

2086:2004 ingliskeelset teksti.

Käesolev dokument on jõustatud

teade Eesti standardiorganisatsiooni ametlikus väljaandes.

25.01.2005 ja selle kohta on avaldatud

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 2086:2005 consists of the English text of the European standard EN 2086:2004.

This document is endorsed on 25.01.2005 with the notification being published in the official publication of the Estonian national standardisation organisation.

The standard is available from Estonian standardisation organisation.

### Käsitlusala:

This standard specifies the requirements relating to: Aluminium alloy AL-P2618A T851 Hand and die forgings a £ 150 mm for aerospace application.

### Scope:

This standard specifies the requirements relating to: Aluminium alloy AL-P2618A T851 Hand and die forgings a £ 150 mm for aerospace application.

ICS 49.025.20

Võtmesõnad:

# EUROPEAN STANDARD NORME EUROPÉENNE

**EUROPÄISCHE NORM** 

**EN 2086** 

December 2004

ICS 49.025.20

#### **English version**

# Aerospace series - Aluminium alloy AL-P2618A - T851 - Hand and die forgings - $a \le 150 \text{ mm}$

Série aérospatiale - Alliage d'aluminium AL-P2618A - T851 - Pièces forgées et matricées - a ≤ 150 mm

Luft- und Raumfahrt - Aluminiumlegierung AL-P2618A - T851 - Freiform- und Gesenkschmiedestücke - a  $\leq$  150 mm

This European Standard was approved by CEN on 15 July 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Con	tents	Page
Forew	vord	3
	luction	
1	Scope	4
2	Normative references	4
	South Braining of the Monte of	

# **Foreword**

This document (EN 2086:2004) has been prepared by the European Association of Aerospace Manufacturers - Standardization (AECMA-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of AECMA, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2005, and conflicting national standards shall be withdrawn at the latest by June 2005.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, al Pola. Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

### Introduction

This standard is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

This standard has been prepared in accordance with EN 4500-2.

# 1 Scope

This standard specifies the requirements relating to:

Aluminium alloy AL-P2618A T851 Hand and die forgings  $a \le 150 \text{ mm}$ 

for aerospace applications.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2486, Aerospace series – Aluminium alloy AL-P2618A – Forging stock 1)

EN 4258, Aerospace series – Metallic materials – General organization of standardization – Links between types of EN standards and their use

EN 4400-7, Aerospace series – Aluminium and aluminium- and magnesium- alloys – Technical specification – Part 7: Aluminium alloy forgings <sup>2)</sup>

EN 4500-2, Aerospace series – Metallic materials – Rules for drafting and presentation of material standards – Part 2: Specific rules for aluminium, aluminium alloys and magnesium alloys <sup>1)</sup>

<sup>1)</sup> Published as AECMA Prestandard at the date of publication of this standard

<sup>2)</sup> In preparation at the date of publication of this standard

1	1 Material designation			Aluminium alloy AL-P2618A											
2	Chemical	Element		Si	Fe	Cu	Mn	Mg	Ni	Zn	Ti + Zr	Ti	Oth	ners	Al
	composition			Si	16	Cu	IVIII	ivig	INI	211	11+21	"	Each	Total	Ai
	%	min.		0,15	0,9	1,8	_	1,2	0,8	-	-	-	-	-	Base
	6	max.		0,25	1,4	2,7	0,25	1,8	1,4	0,15	0,25	0,20	0,05	0,15	Dase
3	3 Method of melting				-										
4.1	I.1 Form				Hand and die forgings										
4.2	.2 Method of production				Forged from forging stock to EN 2486										
4.3	Limit dimension(s)	mm	a ≤ 150												
5	5 Technical specification				Technical specification EN 4400-7										

6.1	Delivery condition	T351	T851					
	Heat treatment	525 °C $\leq \theta \leq$ 535 °C a / WQ Boiling water + 1 % $\leq$ controlled stretched $\leq$ 5 % + $\theta$ = ambient / t $\geq$ 5 d	525 °C $\leq \theta \leq$ 535 °C a / WQ Boiling water + 1 % $\leq$ controlled stretched $\leq$ 5 % + 185 °C $\leq \theta \leq$ 195 °C / 16 h $\leq$ t $\leq$ 24 h					
6.2	Delivery condition code	К	U					
7	Use condition	T851	T851					
	Heat treatment	Delivery condition + 185 °C $\leq \theta \leq$ 195 °C / 16 h $\leq$ t $\leq$ 24 h	Delivery condition					

# Characteristics

8.1	Τe	est sample(s)			See EN 4400-7.									
8.2	Te	est piece(s)			See EN 4400-7.									
8.3	3 Heat treatment				Use condition									
9	Dimensions concerned mm					<i>a</i> ≤ 90			90 < a ≤ 120	)	120 < a ≤ 150			
10	Thickness of cladding on each face %			-				0 -		-				
11	Direction of test piece			L	LT	ST	L	LT	ST	L	LT	ST		
12		Temperature	θ	°C	Ambient			Ambient			Ambient			
13		Proof stress	R <sub>p0,2</sub>	MPa	≥ 385	≥ 375	≥ 375	≥ 380	≥ 370	≥ 365	≥ 370	≥ 360	≥ 355	
14	Т	Strength	R <sub>m</sub>	MPa	≥ 440	≥ 435	≥ 425	≥ 430	≥ 425	≥ 415	≥ 420	≥ 415	≥ 405	
15		Elongation	Α	%	≥ 6	≥ 4,5	≥ 3	≥ 6	≥ 4,5	≥ 3	≥ 6	≥ 4,5	≥ 3	
16		Reduction of area	Z	%					_	O				
17	На	ardness							-	-	6			
18	Sł	near strength	Rc	MPa					_					
19	Ве	ending	k	_	-									
20	lm	pact strength							-					
21		Temperature	θ	°C					_			40		
22		Time		h					-			O,		
23	С	Stress	σa	MPa					-					
24		Elongation a % –												
25		Rupture stress	$\sigma_{\text{R}}$	MPa					_					
26		Elongation at rupture	Α	%					_					
27	No	otes (see line 98)							а					
													F	