TECHNICAL SPECIFICATION SPÉCIFICATION TECHNIQUE

CEN/TS 15901-1

TECHNISCHE SPEZIFIKATION

November 2009

ICS 93.080.20

English Version

Road and airfield surface characteristics - Part 1: Procedure for determining the skid resistance of a pavement surface using a device with longitudinal fixed slip ratio (LFCS): RoadSTAR

Caractéristiques de surface des routes et aéroports - Partie 1 : Partie 1: Mode opératoire de détermination de l'adhérence d'un revêtement de chaussée à l'aide d'un dispositif à coefficient de frottement longitudinal fixe (CFLS): le RoadSTAR Oberflächeneigenschaften von Straßen und Flugplätzen -Teil 1: Verfahren zur Bestimmung der Griffigkeit von Fahrbahndecken durch Verwendung eines Geräts mit festgelegtem Schlupf in Längsrichtung (LFCS): das RoadSTAR-Gerät

This Technical Specification (CEN/TS) was approved by CEN on 27 June 2009 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Con	itents	Page
Foreword		3
1	Scope	4
2	Recommended dises	4
3	Terms and definitions	4
4	Safety	8
5	Safety Principle Principle of measurements Operating principle Key characteristics General Test speed Gear box – Braking system Static wheel force Dynamic wheel force Test wheel assembly Test tyre Torque-measuring transducer	8
5.1	Principle of measurements	8
5.2	Operating principle	8
6	Key characteristics	10
6.1	General	10
6.2	Test speed	10
6.3	Gear box – Braking system	10
6.4	Static wheel force	10
6.5	Dynamic wheel force	10
6.6	Test wheel assembly	10
6.7	Test tyre	10
6.8	Torque-measuring transducer	11
6.9	Water supply and flow control	11
6.10	Laser equipment for macro texture measure to the pits	11
6.11	General requirements for measuring system	12
7	General requirements for measuring system Test procedure Prior to testing	12
7.1	Prior to testing	12
7.2	Tasting	12
7.3	Standard testing conditions (routine testing)	12
_		
8	Data recording	13
9	Calibration	13
9.1	General	13
9.2	Calibration of the static vertical test wheel force	14
9.3	Calibration of the braking torque	14
9.4	Calibration of the dynamic force offset	15
9.5	Calibration of the position encoder (distance calibration)	15
10	Prior to testing Testing Standard testing conditions (routine testing) Data recording Calibration General Calibration of the static vertical test wheel force Calibration of the braking torque Calibration of the dynamic force offset Calibration of the position encoder (distance calibration) Accuracy	15
11	Test report	15
• •	1 OSC TOPOTC	13
Biblio	Accuracy Test report ography	17

This document (CEN/TS 15901-1:2009) has been prepared by Technical Committee CEN/TC 227 "Road

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

Jument (CEN/TS 15.

Is*, the secretariat of wh.

Jon is drawn to the possibility h.

Jording to the OEN/CENELEC Internal Rejuntries are bound to announce this Tecnic, sepublic, Denmark, Estonia, Finland, France, G.

Lithuania, Luxembourg, Walta, Netherlands, Norway, Sweden, Switzerland and the United Kingdom. According to the CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Walta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain,

3

1 Scope

This Technical Specification describes a method for determining the skid resistance of a paved surface by measurement of the longitudinal friction coefficient LFCS. This Technical Specification covers the operation of the Road Surface Tester of arsenal research (RoadSTAR).

The method "RoadSTAR" provides a measure of the skid resistance properties of a bound surface by measurement of the longitudinal friction coefficient using a continuous reading car-sized braked wheel fixed-slip device.

The method "RoadSTARK provides skid resistance measurements of pavements by using the modified Stuttgart skiddometer (Stuttgarter Reibungsmesser). RoadSTAR utilizes a measurement representing the steady-state friction on a baked test wheel at a slip ratio of 82 % (for standard conditions), 37,5 %, 50 %, 75 % (for comparison measurements), with locked wheel or under ABS-braking conditions (for research measurements). The test wheels dragged over a pre wetted pavement surface under controlled load and speed conditions while the test type is parallel to the direction of motion and perpendicular to the pavement.

Three different slip ratios are tained in order to use the same slip speed for the three different nominal NOTE testing speeds of 40 km/h, 60 km/h and 80 km/h for comparison measurements. The common slip speed is chosen equal to 30 km/h:

- for a testing speed of 40 km/h a slip ratio of 5% should be applied;
- for a testing speed of 60 km/h a slip ratio of 50 % should be applied;
- for a testing speed of 80 km/h a slip ratio of 37,5% should be applied.

A machine conforming to the general characteristics of the RoadSTAR and the specific provisions of this Technical Specification should be used for the tests.

In addition to friction measurements, to estimate the macro texture of the pavement surface, a laser system is used. This system is placed in front of the test wheel in order to be able to measure macrotexture (mean profile depth – MDP) on the dry surface and on the same path as the skid resistance measurements. The HSC Ocherated by the standard for this measurement and the device is described in EN 1SO 13473-1 and ISO 13473-2.

2 Recommended uses

RoadSTAR may be used in the following fields of application:

- determining the skid resistance of surfaces in service;
- approval of new surfacing;
- type approval purposes;
- investigation of surface skid resistance;
- measurements on project-level compliance;
- comparative measurements among different devices;
- research measurements.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

skid resistance

characterisation of the friction of a road surface when measured in accordance with a standardised method

3.2

friction

resistance to relative motion between two bodies in contact, the frictional force being the force which acts tangentially in the contact area

3.3

wet road skid resistance

property of a trafficked surface that limits relative movement between the surface and the part of a vehicle tyre in contact with the surface, when lubricated with a film of water

NOTE Factors that contribute to skid resistance include the tyre pressure, contact area, tread pattern and rubber composition; the alignment fexture, surface contamination, and characteristics of the road surface; the vehicle speed; and the weather conditions.

The skid resistance of a road surface in Europe varies seasonally. Generally, wet skid resistance is higher in winter as a result of the effects of wet detritus and the effects of frost and wear by tyres on microtexture and macrotexture. Wet skid resistance is lower in summer as a scult of dry polishing by tyres in the presence of fine detritus.

The change in skid resistance of a sociace in service is affected by the volume of traffic and the composition of the traffic, i.e. cars, buses, commercial vehicles of different sizes, as the tyres of these vehicles polish and/or wear away the surfacing material in different ways. The geometry of the road will affect the change in skid resistance. Generally, tyres polish less on straight roads than on bends

Where the surface contains aggregate with scoating of binder, e.g. bitumen, resin or Portland cement, the skid resistance will change as the coating is worn away by tyres

3.4

bound surface

top layer or surface course of a road with the aggregates secured permanently in place

NOTE Aggregates are commonly secured in place by themen or Portland cement.

3.5

vertical force

load

force applied by the wheel assembly (the static and dynamic force on the test tyre, the test tyre weight and the rim weight) on the contact area

NOTE Some devices (not RoadSTAR) use an assumed load based on the static load

3.6

horizontal force

drag

horizontal force acting tangentially on the test wheel in line with the direction of trave

3.7

fixed-slip friction

friction between a test tyre and a road surface when the wheel is controlled to move at a fixed proportion of its natural speed

3.8

fixed slip

condition in which a braking system forces the test wheel to roll at a fixed reduction of its operating speed

3.9

operating speed

speed at which the device traverses the test surface