

Rubber hose assemblies for oil suction and discharge services - Specification for the assemblies

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN 1765:2016 sisaldab Euroopa standardi EN 1765:2016 ingliskeelset teksti.	This Estonian standard EVS-EN 1765:2016 consists of the English text of the European standard EN 1765:2016.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 17.08.2016.	Date of Availability of the European standard is 17.08.2016.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 23.040.70, 75.200

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Aru 10, 10317 Tallinn, Eesti; koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

English Version

## Rubber hose assemblies for oil suction and discharge services - Specification for the assemblies

Flexibles en caoutchouc pour chargement et  
déchargement des produits pétroliers - Spécifications  
pour les flexibles

Gummischlauchleitungen für das Ansaugen und  
Fördern von Öl - Anforderungen an die  
Schlauchleitungen

This European Standard was approved by CEN on 25 June 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

# Contents

Page

European foreword.....	4
Introduction .....	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions .....	7
4 Classification.....	7
4.1 General.....	7
4.2 End – use.....	7
4.3 Pressure ratings and designations .....	8
5 Materials and construction.....	9
5.1 Materials.....	9
5.1.1 Lining.....	9
5.1.2 Reinforcing plies.....	9
5.1.3 Wire helices.....	9
5.1.4 Internal and armouring wire helices.....	9
5.1.5 Cover .....	9
5.2 Construction.....	9
5.2.1 Type R: Electrically continuous.....	9
5.2.2 Type A: Electrically continuous.....	10
5.2.3 Type S: Electrically continuous or electrically discontinuous.....	10
5.2.4 Type L: Electrically continuous or electrically discontinuous.....	11
6 End connections.....	12
6.1 Nipples and flanges.....	12
6.2 Method of attachment of end connections to the hose .....	12
6.3 Electrical discontinuous assemblies .....	12
6.4 Electrical continuous assemblies with built-in nipples .....	13
7 Dimensions and tolerances .....	13
7.1 Diameters.....	13
7.2 Length.....	13
8 Physical properties.....	14
8.1 Rubber compounds .....	14
8.2 Finished hose assemblies.....	14
9 Test report.....	16
10 Type testing.....	16
11 Frequency of testing.....	16
12 Marking.....	16
Annex A (informative) Information to be supplied by the purchaser.....	18
Annex B (informative) Recommendations for packaging and transportation of oil suction and discharge hose assemblies.....	19
B.1 National.....	19

<b>B.2</b>	<b>International .....</b>	<b>19</b>
	<b>Annex C (informative) Masses.....</b>	<b>20</b>
	<b>Annex D (normative) Wet adhesion test .....</b>	<b>21</b>
<b>D.1</b>	<b>Scope .....</b>	<b>21</b>
<b>D.2</b>	<b>Terms and definitions.....</b>	<b>21</b>
<b>D.3</b>	<b>Principle.....</b>	<b>21</b>
<b>D.4</b>	<b>Apparatus .....</b>	<b>21</b>
<b>D.5</b>	<b>Test specimens .....</b>	<b>21</b>
<b>D.6</b>	<b>Procedure .....</b>	<b>22</b>
<b>D.7</b>	<b>Report .....</b>	<b>22</b>
	<b>Annex E (normative) Hydrostatic test for suction and discharge hose assemblies.....</b>	<b>23</b>
<b>E.1</b>	<b>Principle.....</b>	<b>23</b>
<b>E.2</b>	<b>Apparatus .....</b>	<b>23</b>
<b>E.3</b>	<b>Test medium.....</b>	<b>23</b>
<b>E.4</b>	<b>Procedure .....</b>	<b>23</b>
<b>E.5</b>	<b>Calculation .....</b>	<b>24</b>
<b>E.6</b>	<b>Test report .....</b>	<b>24</b>
	<b>Annex F (normative) Minimum bend radius test.....</b>	<b>25</b>
	<b>Annex G (normative) Burst test.....</b>	<b>27</b>
	<b>Annex H (normative) Test frequency for type testing and routine test.....</b>	<b>28</b>
	<b>Annex I (informative) Test frequency for production acceptance tests.....</b>	<b>29</b>

## European foreword

This document (EN 1765:2016) has been prepared by Technical Committee CEN/TC 218 “Rubber and plastics hoses and hose assemblies”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2017, and conflicting national standards shall be withdrawn at the latest by February 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1765:2004.

Compared to EN 1765:2004 the following changes have been made:

- a) Clause 2: the normative references have been updated;
- b) Subclause 4.2: hose assemblies type S and L were subdivided into two grades Grade M (electrically bonded) and Grade  $\Omega$  (electrically conductive);
- c) Subclause 5.2.3.2: one type of hose assembly assembled with hose nipples in accordance to EN 14420-2 and swaged or crimped ferrules has been added;
- d) Table 4: for the electrical properties (continuity) the maximum electrical resistance  $10^6$  per assembly for grade  $\Omega$  was added;
- e) Clause 12: the requirements for marking have been amended.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Introduction

This document specifies minimum requirements for the satisfactory performance of wire or textile reinforced rubber hose assemblies of both smooth and rough bore types for oil suction and discharge services. The hoses are commonly used for transferring crude oil and liquid petroleum products, other than liquefied petroleum gas and natural gas, to and from tanker and bunkering vessels or for similar duties ashore.

Specific details of the construction of hoses are not rigidly defined in this document since it is felt that this could restrict the introduction of improved methods of construction. The hose assemblies have been classified and designated in terms of service pressure, which includes an allowance for surge pressure and which equates to the factory test pressure. To keep this specification in line with other documents this factory test pressure is also defined as the maximum working pressure (see Table 1). It is the responsibility of the user to determine the appropriate working pressure, which will depend on the severity of the user's operating conditions and on the service life that is expected of the hose assembly.

It is essential that the purchaser provides certain information about the hose assembly and its intended use at the time of enquiry and/or order; this information is listed in Annex A (informative). Recommendations concerning packaging and transportation are given in Annex B (informative) and expected masses of hoses, in kilograms per metre of free length, are given in Annex C (informative).

## 1 Scope

This European Standard specifies the characteristics of four types of oil suction and discharge hose assemblies used for the conveyance of petroleum, including crude oils and other liquid petroleum products containing a maximum aromatics content of 50 % (v/v). It is not suitable for liquefied petroleum gas and natural gas.

Hose assemblies to this document can be used in the temperature range  $-20\text{ }^{\circ}\text{C}$  to  $82\text{ }^{\circ}\text{C}$ .

The hoses specified are in the size range of nominal bore 50 to 500 and may be smooth bore, rough bore or armoured rough bore.

Hoses for use with petroleum products having an aromatic content greater than 50 % (v/v) are outside the scope of this document but the requirements may be used as a basis for such hoses on request to the manufacturer.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 14420-2, *Hose fittings with clamp units - Part 2: Hose side parts of hose tail*

EN 14420-3 *Hose fittings with clamp units - Part 3: Clamp units, bolted or pinned*

EN 14420-4, *Hose fittings with clamp units - Part 4: Flange connections*

EN ISO 1402, *Rubber and plastics hoses and hose assemblies - Hydrostatic testing (ISO 1402)*

EN ISO 1460, *Metallic coatings - Hot dip galvanized coatings on ferrous materials - Gravimetric determination of the mass per unit area (ISO 1460)*

EN ISO 1461, *Hot dip galvanized coatings on fabricated iron and steel articles - Specifications and test methods (ISO 1461)*

EN ISO 7233, *Rubber and plastics hoses and hose assemblies - Determination of resistance to vacuum (ISO 7233)*

EN ISO 8031:2009, *Rubber and plastics hoses and hose assemblies - Determination of electrical resistance and conductivity (ISO 8031:2009)*

EN ISO 8033, *Rubber and plastics hoses - Determination of adhesion between components (ISO 8033)*

EN ISO 8330:2014, *Rubber and plastics hoses and hose assemblies - Vocabulary (ISO 8330:2014)*

EN ISO 15614-1:2004, *Specification and qualification of welding procedures for metallic materials - Welding procedure test - Part 1: Arc and gas welding of steels and arc welding of nickel and nickel alloys (ISO 15614-1:2004)*

ISO 1431-1, *Rubber, vulcanized or thermoplastic — Resistance to ozone cracking — Part 1: Static and dynamic strain testing*

ISO 1817, *Rubber, vulcanized or thermoplastic — Determination of the effect of liquids*

ISO 4649, *Rubber, vulcanized or thermoplastic — Determination of abrasion resistance using a rotating cylindrical drum device*

ISO 7005-1, *Pipe flanges — Part 1: Steel flanges for industrial and general service piping systems*

ASME B.1.20.1, *Pipe Threads, General Purpose, Inch*

BS 3592-1, *Steel wire for hose reinforcement — Part 1: Specification for coated round and flat steel wire for rubber hose reinforcement*

EN ISO 2063, *Thermal spraying - Metallic and other inorganic coatings - Zinc, aluminium and their alloys (ISO 2063)*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN ISO 8330:2014 and the following apply.

#### 3.1

##### **electrically bonded hose assembly**

hose assembly that uses a metallic wire connection to create a low-resistance electrical connection between the end connections

#### 3.2

##### **electrically discontinuous hose assembly**

hose assembly that incorporates an electrical insulation between the end of the helical wire or/and wire cord reinforcement and one or both couplings

### 4 Classification

#### 4.1 General

**WARNING — Careful consideration needs to be given before the use of electrically discontinuous hoses for transferring liquids known to generate static charges. In no circumstances should more than one length of electrically discontinuous hose be used in an individual transfer pipeline and effective electrical continuity to earth from both ends of the electrically discontinuous hose should be maintained.**

#### 4.2 End - use

Hose assemblies for this application are classified according to end-use as follows:

- **Type R**, rough bore hose assemblies for dock operation and intended for situations where a relatively stiff, heavy and robust assembly can be used. The lining of the rubberized fabric is supported and reinforced by an internal (hot-dipped) zinc coated steel wire helix. Type R assemblies are electrically continuous;
- **Type A**, armoured rough bore hose assemblies for dock operation. In addition to an internal zinc coated steel wire helix there shall be external helical armour of a similar material. Type A hoses are electrically continuous and may be lighter and more flexible than type R;
- **Type S**, smooth bore hose assemblies for dock operation where flexibility and lightness are important. Type S hose assemblies may be electrically continuous or electrically discontinuous (see Warning in 4.1);