

Bitumen and bituminous binders - Determination of storage stability of modified bitumen

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 13399:2017 sisaldab Euroopa standardi EN 13399:2017 ingliskeelset teksti.	This Estonian standard EVS-EN 13399:2017 consists of the English text of the European standard EN 13399:2017.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 06.12.2017.	Date of Availability of the European standard is 06.12.2017.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 75.140, 91.100.50

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Bitumen and bituminous binders - Determination of storage stability of modified bitumen

Bitumes et liants bitumineux - Détermination de la stabilité au stockage des bitumes modifiés

Bitumen und bitumenhaltige Bindemittel - Bestimmung der Lagerbeständigkeit von modifiziertem Bitumen

This European Standard was approved by CEN on 15 October 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents		Page
European foreword		3
1	Scope	4
2	Normative references	4
3	Principle	4
4	Apparatus	4
5	Procedure	5
5.1	General.....	5
5.2	Filling of the tube	5
5.3	Closing of the tube	5
5.4	Test conditions.....	5
5.5	Recovery of the sample.....	5
6	Test report	6
Bibliography		7

European foreword

This document (EN 13399:2017) has been prepared by Technical Committee CEN/TC 336 “Bituminous binders”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2018, and conflicting national standards shall be withdrawn at the latest by June 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13399:2010.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

Significant changes in this edition are:

- Closing the filled tube with forceps is described.
- Recovery of the sample by cutting off top and bottom section of the cooled aluminium tube with a knife is introduced.
- Melting temperature for the top and bottom parts after storage is given.
- More test methods to indicate separation are included.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies a method for measuring the storage stability of modified bitumen at high temperatures.

NOTE Modified bitumen and, in particular, polymer-modified bitumen, which consist of mainly bitumen and at least one additional agent, are known to display phase separation under certain conditions.

WARNING — The use of this European Standard can involve hazardous materials, operations and equipment. This European Standard does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this European Standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 58, *Bitumen and bituminous binders - Sampling bituminous binders*

EN 12594, *Bitumen and bituminous binders - Preparation of test samples*

3 Principle

A homogeneous sample of modified bitumen is maintained in a vertical vessel at 180 °C, or at a temperature specified by the producer, for 3 days. After the sample has cooled down, it is cut into three equal parts. The two ends (top and bottom) are analysed further to evaluate possible differences in characteristics.

If the chosen temperature differs from 180 °C, it shall be mentioned in the test report.

4 Apparatus

Usual laboratory apparatus and glassware, together with the following:

4.1 Tube, of thin unvarnished aluminium, of height 160 mm minimum and of diameter between 25 mm and 40 mm, closed at one end (bottom end) and typically “toothpaste tube”.

4.2 Oven, maintained at a temperature of (180 ± 5) °C or other chosen test temperature ± 5 °C for three consecutive days.

4.3 Tins, one to be marked “top” and one to be marked “bottom” (see 5.5), each of sufficient capacity to contain the combined upper and lower parts of different tubes.

4.4 Forceps or pliers, of steel, (e.g. forceps: straight and of length 200 mm - 250 mm), for closing the aluminium tube filled with sample.

4.5 Cutting tool, a broad-bladed knife or sharpened filling knife, for cutting the aluminium tube containing the sample at a low temperature.

4.6 Heating tool, gas flame, heating plate or similar for heating the cutting tool