

**Tehnilised tselluloosid. Laboratoorne jahvatamine. Osa
3: Jokro veski meetod**

Pulps - Laboratory beating - Part 3: Jokro mill method

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 25264-3:2000 sisaldab Euroopa standardi EN 25264-3:1994 ingliskeelset teksti.	This Estonian standard EVS-EN 25264-3:2000 consists of the English text of the European standard EN 25264-3:1994.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 30.06.1994.	Date of Availability of the European standard is 30.06.1994.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 85.040

Võtmesõnad: jokro mill method, laboratory beating, pulps,

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN 25264-3

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 1994

UDC 676.1:542.67

Descriptors: Paper pulps, test specimen conditioning, refining, laboratory equipment

English version

**Pulps - Laboratory beating - Part 3: Jokro mill
method (ISO 5264-3:1979)**

Pâtes - Raffinage de laboratoire - Partie 3:
Méthode au moulin Jokro (ISO 5264-3:1979)

Zellstoff - Labormahlung - Teil 3:
Jokro-Mühle-Verfahren (ISO 5264-3:1979)

This European Standard was approved by CEN on 1994-06-27. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Foreword

This European Standard has been taken over by CEN/TC 172 "Pulp, paper and board" from the work of ISO/TC 6 "Paper, board and pulps" of the International Organization for Standardization (ISO).

This document was submitted to the Unique Acceptance Procedure (UAP) and was approved without any modification.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 1994, and conflicting national standards shall be withdrawn at the latest by December 1994.

In accordance with the CEN/CENELEC Internal Regulations, following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice

The text of the international standard ISO 5264-3:1979 has been approved by CEN as a European Standard without any modification.

NOTE: Normative references to international publications are listed in annex ZA (normative).

Annex ZA (normative)
Normative references to international publications
with their relevant European publications

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN</u>	<u>Year</u>
ISO 638		Pulps - Determination of dry matter content	EN 20638	

INTERNATIONAL STANDARD



5264 / III

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Pulps — Laboratory beating — Part III : Jokro mill method

*Pâtes — Raffinage de laboratoire —
Partie III : Méthode au moulin Jokro*

First edition — 1979-05-01

FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 5264/III was developed by Technical Committee ISO/TC 6, *Paper, board and pulps*, and was circulated to the member bodies in December 1977.

It has been approved by the member bodies of the following countries :

Austria	India	South Africa, Rep. of
Belgium	Iran	Spain
Canada	Ireland	Sweden
Chile	Kenya	Switzerland
Czechoslovakia	Mexico	Turkey
Finland	Netherlands	USA
France	Norway	USSR
Germany, F.R.	Poland	
Hungary	Romania	

The member body of the following country expressed disapproval of the document on technical grounds :

Italy

Pulps — Laboratory beating — Part III : Jokro mill method

0 INTRODUCTION

It has been agreed that the ultimate aim of standardization of laboratory beating should be to develop one test method which is internationally acceptable and which, if possible, allows the energy consumption during beating to be measured. For practical reasons it has not proved possible to achieve this at present. Therefore, as an interim measure, in view of the widespread use of the following methods

- Valley beater,
- PFI mill,
- Jokro mill,

it has been decided to provide agreed guidance on the use of these equipments in order to achieve consistency of results with each instrument. While all three methods will show a similar trend in respect of the pulp tested, the actual results cannot be correlated between different types of beater¹⁾. The position will be kept under review, and the methods will be replaced by a single method as soon as practicable.

1 SCOPE

This International Standard specifies a method, using a Jokro mill, for the laboratory beating of pulp. The description is limited to the disintegrating and beating of the stock, the withdrawal and distribution of samples, and the beating equipment.

The beating is a preliminary step in testing the physical properties of pulp.

Part I specifies a method of laboratory beating using a Valley beater and Part II a method using a PFI mill.

2 FIELD OF APPLICATION

In principle, this method is applicable to all kinds of pulp.

NOTE — In practice, the method may not give satisfactory results with certain extremely long-fibred pulps, such as cotton linter.

3 REFERENCES

ISO 638, *Pulps — Determination of dry matter content.*

ISO 4119, *Pulps — Determination of stock concentration (Rapid method).*

ISO 5263, *Pulps — Laboratory wet disintegration.*²⁾

4 PRINCIPLE

A measured amount of pulp of specified stock concentration is beaten between the inner wall of a cylindrical beating box which revolves with a planetary rotation around a central shaft, and a grooved roll loosely placed in the box.

5 APPARATUS AND AUXILIARY MATERIALS

Ordinary laboratory equipment and

5.1 **Jokro mill**, as described in the annex.

5.2 **Standard distintegrator**, as described in ISO 5263.

5.3 **Balance**, capable of weighing the sample to an accuracy of 0,2 g.

5.4 **Distilled water**, or water of similar quality.

NOTE — Distilled water, or water of similar quality, is particularly recommended with a view to obviating any difficulties that might arise from the use of different qualities of water by the interested parties.

1) Should one of the three methods listed become the future standard method, the method chosen should be the one which works in the most economical way and yields the highest reproducibility of results obtained in different laboratories.

At present, some countries are of the opinion that the PFI mill described in ISO 5264/II meets these requirements best of all.

2) At present at the stage of draft.