
**Metallic and other inorganic coatings —
Electroplated coatings of zinc with
supplementary treatments on iron or
steel**

*Revêtements métalliques et autres revêtements inorganiques — Dépôts
électrolytiques de zinc avec traitements supplémentaires sur fer ou
acier*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

This document is a preview generated by EVS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

| | |
|--|----|
| Foreword..... | iv |
| Introduction | v |
| 1 Scope | 1 |
| 2 Normative references | 1 |
| 3 Terms, definitions, abbreviated terms and symbols..... | 2 |
| 3.1 Terms and definitions..... | 2 |
| 3.2 Abbreviated terms | 2 |
| 3.3 Symbols | 3 |
| 4 Information to be supplied by the purchaser to the electroplater..... | 3 |
| 4.1 Essential information | 3 |
| 4.2 Additional information..... | 3 |
| 5 Designation | 4 |
| 5.1 General..... | 4 |
| 5.2 Designation specification | 4 |
| 5.3 Designation of the basis material..... | 5 |
| 5.4 Designation of heat treatment requirements | 5 |
| 5.5 Examples | 5 |
| 6 Requirements | 6 |
| 6.1 Appearance | 6 |
| 6.2 Thickness | 6 |
| 6.3 Conversion coatings and other supplementary treatments..... | 6 |
| 6.4 Adhesion of zinc and chromate coatings..... | 7 |
| 6.5 Accelerated corrosion testing | 7 |
| 6.6 Stress relief heat treatments before cleaning and metal deposition | 9 |
| 6.7 Hydrogen-embrittlement-relief heat treatments after electroplating..... | 9 |
| 7 Sampling..... | 9 |
| Annex A (normative) Designation of chromate conversion coatings and other supplementary treatments | 10 |
| Annex B (normative) Measurement of average thickness of coating on small articles | 12 |
| Annex C (informative) Additional information on corrosion resistance, rinsing and drying, processing parts in bulk and dyeing of chromate conversion coatings | 13 |
| Bibliography | 15 |

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2081 was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*, Subcommittee SC 3, *Electrodeposited coatings and related finishes*.

This third edition cancels and replaces the second edition (ISO 2081:1986), which has been technically revised.

Introduction

Zinc coatings are applied to iron or steel articles for protective and decorative purposes by electrodeposition from acid zinc chloride, alkaline non-cyanide zinc, and alkaline zinc cyanide solutions. Electroplated, bright zinc coatings are popular and the processes for preparing bright zinc coatings are widely used.

The ability of a zinc coating to prevent corrosion is a function of its thickness and the type of service conditions to which it is exposed. For example, the rate of corrosion of zinc will generally be greater in industrial exposures than in rural ones. The type of service condition should, therefore, be taken into consideration when specifying the minimum coating thickness. Chromate conversion coatings and other supplementary treatments enhance the corrosion resistance of electrodeposited zinc coatings and are commonly applied after electroplating.

Because the appearance and serviceability of zinc coatings depends on the surface condition of the basis metal, agreement should be reached between the interested parties that the surface finish of the basis metal is satisfactory for electroplating.

Chromate conversion coatings are omitted, or replaced by other conversion coatings, at the specific request of the purchaser. This International Standard provides the codes for all types of chromate conversion and other supplementary coatings.

Chemical conversion coatings that do not contain hexavalent chromium or are chromium-free, conforming to this International Standard, are commercially available. The appearance of these substitutes may be different from those produced with hexavalent chromium. All forms of chromate conversion coatings, alternative conversion coatings or substitutes, with the exception of phosphate coatings, can be used and are required to satisfy the corrosion requirements given in this International Standard.

Standard designations for metals and alloys can be found in References [6] to [10] in the Bibliography.

This document is a preview generated by EVS

Metallic and other inorganic coatings — Electroplated coatings of zinc with supplementary treatments on iron or steel

WARNING — This International Standard may not be compliant with some countries' health, safety and environmental legislations and calls for the use of substances and/or procedures that may be injurious to health if adequate safety measures are not taken. This International Standard does not address any health hazards, safety or environmental matters and legislations associated with its use. It is the responsibility of the producers, purchasers and/or user of this International Standard to establish appropriate health, safety and environmentally acceptable practices and take appropriate actions to comply with any national, regional and/or international rules and regulations. Compliance with this International Standard does not, of itself, confer immunity from legal obligations.

1 Scope

This International Standard specifies requirements for electroplated coatings of zinc with supplementary treatments on iron or steel. It includes information to be supplied by the purchaser to the electroplater, and the requirements for heat treatment before and after electroplating.

It is not applicable to zinc coatings applied

- to sheet, strip or wire in the non-fabricated form
- to close-coiled springs, or
- for purposes other than protective or decorative.

This International Standard does not specify requirements for the surface condition of the basis metal prior to electroplating with zinc. However, defects in the surface of the basis metal can adversely affect the appearance and performance of the coating.

The coating thickness that can be applied to threaded components can be limited by dimensional requirements, including class or fit.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1463, *Metallic and oxide coatings — Measurement of coating thickness — Microscopical method*

ISO 2064, *Metallic and other inorganic coatings — Definitions and conventions concerning the measurement of thickness*

ISO 2080, *Metallic and other inorganic coatings — Surface treatment, metallic and other inorganic coatings — Vocabulary*

ISO 2177, *Metallic coatings — Measurement of coating thickness — Coulometric method by anodic dissolution*

ISO 2178, *Non-magnetic coatings on magnetic substrates — Measurement of coating thickness — Magnetic method*

ISO 2819, *Metallic coatings on metallic substrates — Electrodeposited and chemically deposited coatings — Review of methods available for testing adhesion*

ISO 3497, *Metallic coatings — Measurement of coating thickness — X-ray spectrometric methods*

ISO 3543, *Metallic and non-metallic coatings — Measurement of thickness — Beta backscatter method*

ISO 3613, *Chromate conversion coatings on zinc, cadmium, aluminium-zinc alloys and zinc-aluminium alloys — Test methods*

ISO 3892, *Conversion coatings on metallic materials — Determination of coating mass per unit area — Gravimetric methods*

ISO 4518, *Metallic coatings — Measurement of coating thickness — Profilometric method*

ISO 4519, *Electrodeposited metallic coatings and related finishes — Sampling procedures for inspection by attributes*

ISO 9587, *Metallic and other inorganic coatings — Pretreatment of iron or steel to reduce the risk of hydrogen embrittlement*

ISO 9588, *Metallic and other inorganic coatings — Post-coating treatments of iron or steel to reduce the risk of hydrogen embrittlement*

ISO 10289, *Methods for corrosion testing of metallic and other inorganic coatings on metallic substrates — Rating of test specimens and manufactured articles subjected to corrosion tests*

ISO 10587, *Metallic and other inorganic coatings — Test for residual embrittlement in both metallic-coated and uncoated externally-threaded articles and rods — Inclined wedge method*

ISO 15724, *Metallic and other inorganic coatings — Electrochemical measurement of diffusible hydrogen in steels — Barnacle electrode method*

ASTM B117, *Standard Practice for Operating Salt Spray (Fog) Apparatus*

3 Terms, definitions, abbreviated terms and symbols

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 2064 and ISO 2080 apply.

3.2 Abbreviated terms

| | |
|----|--|
| C | iridescent conversion coating |
| D | opaque chromate conversion coating |
| ER | hydrogen embrittlement relief heat treatment |
| NM | non-metallic materials |
| PL | plateable plastics materials |
| SR | stress relief heat treatment |
| T2 | organic sealant |