# INTERNATIONAL STANDARD

Third edition 2009-06-15

# Destructive tests on welds in metallic materials — Bend tests

Essais destructifs des soudures sur matériaux métalliques — Essais de pliage



Reference number ISO 5173:2009(E)

#### PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below

This document is a preview denerated by Fig.



#### **COPYRIGHT PROTECTED DOCUMENT**

#### © ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org Published in Switzerland

#### Contents

Page

Foreword iv	
1	Scope1
2	Terms and definitions1
3	Principle
4 4.1 4.2 4.3	Symbols and abbreviated terms
5 5.1 5.2 5 3	Preparation of test specimens
5.4 5.5 5.6	Heat treatment and/or ageing
6 6.1 6.2 6.3 6.4 6.5 6.6	Conditions of testing 10   Etching 10   Testing 10   Diameter of former and roller 16   Distance between rollers 16   Bending angle 16   Bending elongation 16
7	Test results
8	Test report
Annex	A (informative) Example of a test report

5

#### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in Haison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 5173 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 5, *Testing and inspection of welds*.

This third edition cancels and replaces the second edition (ISO 5173:2000) which has been technically revised.

Requests for official interpretations of any aspect of this international Standard should be directed to the Secretariat of ISO/TC 44/SC 5 via your national standards body, of which a complete listing can be found at www.iso.org.

Generated by FLS

#### Destructive tests on welds in metallic materials — Bend tests

#### 1 Scope

This International standard specifies a method for making transverse root, face and side bend tests on test specimens taken from butt welds, butt welds with cladding (subdivided into welds in clad plates and clad welds) and cladding without butt welds, in order to assess ductility and/or absence of imperfections on or near the surface of the test specimen. It also gives the dimensions of the test specimen.

In addition, this International Standard specifies a method for making longitudinal root and face bend tests to be used instead of transverse bend tests for heterogeneous assemblies when base materials and/or filler metal have a significant difference in their physical and mechanical properties in relation to bending.

This International Standard applies to metallic materials in all forms of product with welded joints made by any fusion arc welding process.

#### 2 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

#### 2.1

### transverse face bend test specimen for a butt we

specimen for which the surface in tension is the side that contains the greater width of the weld or the side from which the welding arc was first applied, applicable to the sverse butt weld specimens

See Figure 1.

#### 2.2

transverse root bend test specimen for a butt weld TRBB

specimen for which the surface in tension is the side opposite to that of the face butt weld bend test specimen, applicable to transverse butt weld specimens

See Figure 2.

#### 2.3

## transverse side bend test specimen for a butt weld SBB

specimen for which the surface in tension is a cross-section of the weld

See Figure 3.

#### 2.4

longitudinal face test specimen for a butt weld root bend test specimen for a butt weld LFBB LRBB

specimen whose direction is parallel to butt weld direction, applicable to face and root bend specimens

See Figure 4.