

INTERNATIONAL STANDARD

ISO
105-Z01

Second edition
1993-10-01

Textiles — Tests for colour fastness —

Part Z01:

Colour fastness to metals in the dye-bath:
Chromium salts

Textiles — Essais de solidité des teintures —

*Partie Z01: Solidité des teintures aux métaux dans les bains de teinture:
Sels de chrome*



Reference number
ISO 105-Z01:1993(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 105-Z01 was prepared by Technical Committee ISO/TC 38, *Textiles*, Sub-Committee SC 1, *Tests for coloured textiles and colorants*.

This second edition cancels and replaces the first edition (included in ISO 105-Z:1978), of which it constitutes a minor revision.

ISO 105 was previously published in thirteen "parts", each designated by a letter (e.g. "Part A"), with publication dates between 1978 and 1985. Each part contained a series of "sections", each designated by the respective part letter and by a two-digit serial number (e.g. "Section A01"). These sections are now being republished as separate documents, themselves designated "parts" but retaining their earlier alphanumeric designations. A complete list of these parts is given in ISO 105-A01.

© ISO 1993

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Textiles — Tests for colour fastness —

Part Z01:

Colour fastness to metals in the dye-bath: Chromium salts

1 Scope

This part of ISO 105 specifies a method for determining the effect, on the colour of a dye, of dyeing in the presence of hexavalent chromium salts. It is applicable to wool. An alternative method is specified in 6.3 to provide a milder test suitable for assessing the effect of chromium salts in such concentrations as might be found when shading.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 105. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 105 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 105-A01:1989, *Textiles — Tests for colour fastness — Part A01: General principles of testing*.

ISO 105-A02:1993, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*.

3 Principle

The difference in colour between dyeings made with and without potassium dichromate is assessed with the grey scale.

4 Apparatus and reagents

4.1 Two pieces of undyed light wool fabric, of a size suitable for laboratory dyeing.

4.2 Two dye-baths, and solutions usual for the dye.

4.3 Potassium dichromate ($K_2Cr_2O_7$), 10 g/l solution.

4.4 Grey scale for assessing change in colour, complying with ISO 105-A02.

5 Test specimens

See 4.1.

6 Procedure

6.1 Dyeing

Make two dyeings of the dye at the standard depth of colour on the wool fabric using the normal method for the dye under examination at a liquor ratio of 40:1.

6.2 Method 1

On completion of the dyeing, add to one of the dye-baths sufficient potassium dichromate solution to give 1 % of $K_2Cr_2O_7$ on the mass of the wool. Maintain both baths at the boil for a further 60 min.